

Peripheral Oxide


Utility: Comanche 2 Cleaned

Assembly: HH83

Face: 3


Date: 21-Oct-2003

Elevation	R02	R06	R08	R10	R12	R14
111.9	43.6	32.7	39.4	35.4	29.4	27.1
112.9	57.2	39.2	45.5	37.9	32.3	33.6
113.9	69.9	44.2	51.8	46.9	35.1	39.6
114.9	80.0	49.6	52.9	55.1	35.2	46.0
115.9	80.9	52.1	54.2	57.8	29.9	50.1
116.9	85.2	57.6	60.5	60.6	35.0	56.1
117.9	88.0	59.3	59.7	66.0	30.1	59.8
118.9	90.1	61.2	58.4	64.8	37.4	58.9
119.9	88.4	60.0	56.4	65.2	47.3	59.8
120.9	86.2	56.4	53.7	62.1	50.8	58.9
121.9	80.7	52.0	50.0	60.1	49.9	55.6
122.9	73.2	48.4	47.6	54.8	48.5	48.4
123.9	62.1	42.3	40.5	47.0	43.0	39.1
124.9	49.2	37.5	35.5	39.2	36.3	30.5
125.9	44.2	38.1	34.2	35.0	33.4	28.6
max	90.1	61.2	60.5	66.0	50.8	59.8




---

**Peripheral Rod Oxide After Crud Clean (Comanche Peak 2, FA HH83, FA**



HH83, FACE 3)



R14