5 CRITICAL CRACK SIZE CALCULATIONS

This section describes the development of a conservative critical crack size methodology specific to the subject nozzle-to-safe-end geometry and materials. This methodology is based on the net section collapse (NSC) equations for an arbitrary circumferential crack profile in a thin-walled pipe. For the purposes of this project, normal thermal piping loads were included in the crack stability calculations, and a Z-factor approach reducing the NSC failure load was implemented in consideration of the possibility of an EPFM failure mechanism. Finally, in support of the methodology, available experimental failure data for complex cracks in materials similar to Alloy 82/182 were evaluated.

5.1 Methodology

Critical crack sizes were computed using a spreadsheet implementation of the Net Section Collapse (NSC) solution for an arbitrary circumferential crack profile, assuming thin wall equilibrium [24]. Since crack front coordinates were available for each step of the crack growth simulations, stability calculations could be performed at every increment of crack growth with the net section collapse model. Combined with the leak rate simulations discussed in Section 6, which could also be performed at each increment of through-wall crack growth, evolutions of leak rate and stability margin on load versus time were computed and are presented in Section 7. The NSC solution presented in Reference [24] allows for the calculation of net section collapse loads under three different scenarios. The first is used when the crack is entirely in tension. The second and third scenarios are used when part of the crack is on the compressive side of the neutral axis of the cracked section; the second scenario allows the crack to take compression (i.e., crack closure allows transmission of any compressive forces) while the third scenario assumes that the crack cannot take compression (i.e., crack is sufficiently blunt not to allow any contact between the crack faces). For all calculations in this report, if part of the crack was on the compressive side of the neutral axis of the cracked section, it was conservatively assumed not to take compression.

Given that any hypothetical stress corrosion cracking could be located near the safe end, the flow strength used in the critical crack size calculations was based on the safe end material. Based on design drawings and certified material test report (CMTR) information for the nine plants considered in this analysis, most of the stainless steel safe ends were constructed from SA182 Grade F316L. The remaining safe ends were constructed from SA182 Grade F316 except for the safe ends for the Plant I surge and safety/relief nozzles, which are cast stainless steel SA-351 Grade CF8M. The room-temperature yield and ultimate tensile strengths obtained from the various CMTRs are plotted in Figure 5-1 along with the flow strength calculated as the average of the yield strength and ultimate tensile strength. These were adjusted to a temperature of

Critical Crack Size Calculations

650°F based on the relative dependence of yield strength and ultimate tensile strength on temperature in the ASME Boiler & Pressure Vessel Code per Equation [5-1]:

$$S_{650^{\circ}\mathrm{F}} = CMTR \times \left(\frac{Code_{650^{\circ}\mathrm{F}}}{Code_{RT}}\right)$$
[5-1]

The resulting at-temperature properties are plotted in Figure 5-2, which supports the use of 45.6 ksi for the flow strength in the limit load calculations. This also corresponds to the flow stress used as an input to the Z-factor EPFM calculations discussions below in Section 5.4.

5.2 Applied Loads

The loads used as a basis for the critical crack size calculations are taken from the appropriate sensitivity study case discussed in Section 7. These loads are taken from the piping loads provided for each plant, as summarized in Section 2.2. All critical crack size calculations in the case matrix were performed using primary (deadweight plus pressure) and normal thermal expansion piping loads, with the exception of Cases 49, 50, and 51, which were explicitly designated to not consider thermal loads as a sensitivity study.

Using the supplied load data from all nine plants, the effective moments were calculated from the bending moment components for each nozzle based on a Von Mises stress approach using Equation [5-2]:

$$M_{eff} = \sqrt{\left(\frac{\sqrt{3}}{2}M_x\right)^2 + M_y^2 + M_z^2}$$
[5-2]

where M_x (torsion, T), M_y , and M_z are taken as the sum of the individual moment components (i.e., dead weight + thermal expansion).

Similarly, as shown in Equation [5-3], the total axial force was taken as the scalar sum of the relevant individual axial forces (dead weight + thermal expansion), plus the end cap pressure (p) load calculated based on the pressure times the cross sectional area of the weld inside diameter plus the area of the crack face.

$$F_{tot} = F_{x_{DW}} + F_{x_{NOT}} + p\left(\frac{\pi D_i^2}{4} + f_{cracked} \frac{\pi (D_o^2 - D_i^2)}{4}\right)$$
[5-3]

5.3 Load Considerations

The inclusion of full normal thermal expansion loads is considered a conservatism for the critical flaw size calculations. Appendix B and Appendix C include separate evaluations detailing how thermal bending loads would be expected to significantly relax in the presence of a large circumferential flaw. Of particular interest are the surge nozzle thermal loads, which generate larger stresses than the thermal loads for the safety/relief and spray nozzles. The Appendix B study reviews test data from the NRC-sponsored Degraded Piping Program and provides analysis results from piping models for the surge lines of two representative plants. The results of this study support the conclusion that the surge nozzle piping thermal loads are completely relieved prior to nozzle rupture since the supportable crack plane rotation is greater than the imposed rotation due to thermal expansion. Appendix C describes a set of elastic and elastic-plastic finite element analyses of a pipe with an idealized through-thickness crack that were used to determine the effect on bending moment and crack driving force due to an imposed end rotation. The analyses performed in Appendix C result in a similar amount of crack plane rotation as the Appendix B results. As discussed in Section 2.2.2, the additional conservatism introduced by including the normal thermal loads bounds the potential effects of potentially higher thermal loads in the surge line during heat and cooldown due to stratification.

Welding residual stresses and through-wall bending stresses caused by radial differential thermal expansion between the stainless steel piping and the carbon steel nozzle were likewise not included as part of the limit load analyses since they are local secondary stresses. Seismic loads were also neglected from the critical crack size calculations since it was considered overly conservative to consider such an unlikely event given the time frame under investigation (~6 months). It should be noted that the loads resulting from an SSE event were not significantly higher than those resulting from the combination of pressure, dead weight, and normal operation thermal.

5.4 EPFM Considerations

Though the crack growth calculations were performed elastically, the critical crack size calculations included elastic-plastic considerations through the use of a Z factor. The Z factor acts as a correction factor on the limit load solution and is a function of the material toughness and pipe diameter. It is used to reduce the supportable moment when elastic-plastic fracture mechanics conditions control rather than limit load conditions. Per Reference [25], for a given material, the Z factor is solely a function of the size of a weld (NPS). For the case of Alloy 82/182, Z factor curves were calculated [26,27] using the stainless steel base metal strength and the toughness of the Alloy 182 weld metal. Fits to the calculation results yielded Equation [5-4].

$$Z = \begin{cases} 0.00065NPS^{3} - 0.01386NPS^{2} + 0.1034NPS + 0.902 & , & NPS \le 8" \\ 0.0000022NPS^{3} - 0.0002NPS^{2} + 0.0064NPS + 1.1355 & , & NPS > 8" \end{cases}$$
[5-4]

In this analysis, the Z factor as calculated using Equation [5-4] was used to reduce the supportable moment, thereby reducing the margin on stability for a given crack profile. However, experimental evidence suggests that a Z factor needs only be applied when the

Critical Crack Size Calculations

Dimensionless Plastic Zone Parameter (DPZP), an empirically based parameter providing a measure of the size of the plastic zone at the crack tip relative to the pipe size (see Section 5.6), is less than unity. In the analyses conducted, a Z factor was conservatively applied to all limit load calculations regardless of the DPZP for the case under consideration.

5.5 Calculations Verification

The Arbitrary Net Section Collapse (ANSC) software [28] was used to validate the spreadsheet implementation of the NSC solution to an arbitrary crack profile. Unlike the model developed in [24], the ANSC software allows the moment loading to be arbitrarily positioned around the pipe relative to the location of the crack. However, when half symmetry conditions exist in the pipe cross-section and the moment is applied such that its axis is perpendicular to the symmetry plane, as is assumed throughout this report, the ANSC program's solution should default to that of the regular NSC model implemented in spreadsheet form in support of this project. Several crack profiles under various loads were investigated and in all cases, exact agreement (within three significant figures) was obtained between the results of the ANSC program and the spreadsheet implementation of the NSC solution.

5.6 Model Validation Comparison with Experiment

The predictions obtained from the spreadsheet implementation of the net section collapse model were also compared to experimental complex crack data from bending failure tests [29,30,31]. Complex crack data were deemed most applicable to this project since the model predictions for the majority of cases investigated resulted in either complex cracks or through-wall cracks with a long ID surface component. The data from the test programs [29,30,31] were taken for materials with higher toughness (Alloy 600 and Stainless Steel) than those considered here.

Using the geometric data from each test, the DPZP was calculated as in Appendix B (see Equation [5-5]) using the C(T) toughness and not the possibly reduced apparent toughness for complex cracks. Then, the moment corresponding to net section collapse was computed with DEI's spreadsheet implementation of the net section collapse model. These calculated moments were then compared with the maximum moments obtained from the experimental programs. The results of this comparison are shown in Figure 5-3 and Figure 5-4. As shown, the net section collapse model in which the crack is not allowed to take compression provides a better and more conservative estimate of the experimental maximum moments. Hence, this version of the net section collapse model was used for all the stability calculations in this report. Additionally, the results shown in Figure 5-3 and Figure 5-4 appear to support the need for a correction factor (i.e., Z factor) at DPZP's below unity. Hence, the Z-factor was conservatively applied in all cases considered in this report.

[5-5]

$$DPZP = \begin{cases} \left(\frac{EJ_i}{2\pi\sigma_f^2}\right) / \left(\frac{\pi-\alpha}{4}\right)D &, \text{ for surface cracks} \\ \left(\frac{EJ_i}{2\pi\sigma_f^2}\right) / \left[\left(\frac{\pi+\left(\frac{d}{t}\right)\alpha}{\pi}\right)\frac{D\pi}{4}\right] &, \text{ for through-wall cracks} \\ \left(\frac{EJ_i}{2\pi\sigma_f^2}\right) / \left\{\left[\pi-\left(\alpha+\frac{d}{t}(\pi-\alpha)\right)\right]\frac{D}{4}\right\} &, \text{ for complex cracks} \end{cases}$$

Critical Crack Size Calculations



Figure 5-1 Available CMTR Strength Data for Subject Stainless Steel Safe Ends



Figure 5-2

Available CMTR Strength Data for Subject Stainless Steel Safe Ends Adjusted to a Temperature of 650°F Based on the Relative Dependence of Yield Strength and Ultimate Tensile Strength on Temperature in the ASME Boiler & Pressure Vessel Code [11] Critical Crack Size Calculations



Figure 5-3 Maximum Experimental Moment Divided by NSC Predicted Moment for Available Complex Crack Tests

5-8



Figure 5-4 NSC Predicted Moment Divided by Maximum Experimental Moment for Available Complex Crack Tests

6 LEAK RATE MODELING

This section describes the leak rate calculation procedure applied to the through-wall portion of the crack growth simulations using EPRI's PICEP software. The crack opening area at the weld OD calculated in the crack growth finite-element simulations was applied directly in the PICEP leak rate calculations. NRC's SQUIRT software was also applied in a scoping study for the purpose of comparison.

6.1 PICEP Modeling

The leak rates discussed in this report were calculated using EPRI's Pipe Crack Evaluation Program (PICEP), a computer program developed for LWR pipe and SG tube leaks [32]. Although PICEP can be used to compute crack opening displacements and leak rates (see Section 6.3), in this analysis, it was used solely to model leak rates since the crack opening displacements calculated during the crack growth modeling were used to generate the required crack opening displacement (COD) inputs. Therefore, no material property inputs were required for the leak rate calculations and the effects of pipe loads on leak rates were captured through the crack opening displacements calculated during crack growth.

All leak rate simulations were performed using crack opening displacements at the outside diameter of the fracture mechanics models described in Sections 4 and 7. Specifically, the outer diameter crack opening displacements from the fracture mechanics FEA model were used to compute a crack opening area, which was then used in conjunction with the OD length of the crack and an assumed crack shape (normally elliptical) to calculate the single-value crack opening displacement input for PICEP. In the PICEP calculations, a uniform length through the weld thickness was assumed.

For longer through-wall cracks predicted in this project (which are mostly complex or through wall with a long ID surface component), the crack opening area is generally smallest at the OD. However, as shown in Figure 6-2, under some conditions, crack opening displacements near the mid-wall were computed to be less than those at the OD. Even though the circumferential extent of cracking is somewhat greater at the mid-wall in comparison to the OD, in some cases the crack opening area at the mid-wall was found to be somewhat smaller than the opening area at the OD. In order to quantify the impact of using the OD crack opening displacements rather than those at the mid-wall, crack opening displacements at the mid-wall were extracted from the structural calculations for one case (Case 1) and used to calculate a leak rate taking into account the difference in area between the mid-wall and the OD. Though the crack opening area at the outside diameter was 1.5 times that at the mid-wall, the flow rate calculated assuming the crack to have a constant cross sectional area equal to that at the OD was only 20% greater than that calculated using the crack with variable cross sectional area. Given that this effect is

Leak Rate Modeling

considerably smaller than the expected accuracy of the leak rate simulations, the more readily available outside diameter crack opening displacements were used to compute the leak rates in Tables 7-5 and 7-6. No comparisons were made using crack opening displacements at the inside diameter since, as stated earlier, most cases exhibited either complex cracks or through-wall cracks with long ID surface components leading to even larger crack opening areas than those at the outside diameter.

The inputs to the leak rate calculations are listed in Table 6-1. The crack morphology parameters (surface roughness and number of turns) were selected to be representative of PWSCC cracks [32,33]. The results of the leak rate simulations are included with the stability results in Tables 7-5 and 7-6.

6.2 Scoping Results

As part of the leakage calculations, scoping analyses were performed to confirm the appropriate selection of inputs. Specifically, the effect of assuming the crack shape to be elliptical was investigated. The choice of an elliptical shape was motivated by the actual crack opening displacements computed during the crack growth simulations. A plot showing the shape of the crack opening at the OD for Case 1 when the leak rate was calculated to be 1 gpm is shown in Figure 6-3 along with the elliptical, diamond, and rectangular profiles which correspond to the actual profile's crack opening area and length. As seen in the figure, the actual shape of the crack is very well approximated by an ellipse.

In order to quantify the effect of assumed crack shape, leakage simulations were conducted for one case using rectangular and diamond shaped crack openings rather than the default ellipse. The results showed the ellipse to be conservative (i.e., result in lower flow rate) by 2% relative to the other two crack shapes. Therefore, the elliptical crack shape was used to generate all of the leak rate results shown in Tables 7-5 and 7-6.

6.3 Comparison with SQUIRT Modeling

As part of leakage calculation verification studies, comparisons were made between leak rates predicted using PICEP and those predicted using the NRC's Seepage Quantification of Upsets in Reactor Tubes (SQUIRT) program [34]. Since these calculations were performed prior to the crack growth calculations, a slightly different approach than that described in Section 6.1 was used. Specifically, PICEP was used to calculate both crack opening displacement and leakage for a given crack length, loading condition, and assumed crack shape. A summary of the structural inputs used in the crack opening displacement calculations is provided in Table 6-2. The crack opening displacement and assumed crack shape were then used to calculate the leak rate using the SQUIRT code for the same assumed crack shape.

When specifying the crack geometry, PICEP allows the user to vary the crack opening area linearly from the ID to the OD whereas SQUIRT allows the user to linearly vary the crack length and opening independently through the thickness. In order to be compatible with the inputs used in PICEP, the crack length and opening used in SQUIRT were kept constant through the thickness resulting in a constant crack cross-sectional area through the thickness. The assumed

crack shape for this study was taken to be rectangular. As described in Section 6.2, the shape of the crack was concluded to have a minimal effect on the predicted leak rates.

The PICEP modeling used the same fluid friction inputs as those used in the final leakage calculations presented in Tables 7-5 and 7-6. The SQUIRT simulations were conducted using its built-in PWSCC modeling inputs.

The leak rate calculations were done for cracks ranging in length from 1 to 10 inches using the geometry and loading applicable to the Wolf Creek relief nozzle, and the results are shown in Figure 6-1. As shown in the figure, the PICEP calculations spanned a range of applied bending moments, whereas the SQUIRT calculations were performed only for the full moment case. It is clear from the figure that the leak rates obtained using the SQUIRT code, albeit consistently greater than those obtained using PICEP (1% to 30% greater in the figure), are generally in good agreement with those obtained from PICEP. The results in Figure 6-1 also clearly demonstrate the effect of the applied bending moment to increase the crack opening area and, thus, leak rate.

6.4 Leak Rate Predication Uncertainty

An estimate of the uncertainty associated with the leak rate calculations described above is presented in Appendix D of this report. This appendix describes a statistical study of experimental leak rate data for through-wall cracks having an IGSCC morphology. The study shows that a multiplicative factor of 1.5 to 2.0 on the leak rate calculated using the NRC SQUIRT code describes the uncertainty in leak rate due to scatter in the test data for the IGSCC samples tested. As noted in Section 7.2.3, a leak rate margin factor of 4.0 is applied in recognition of other sources of uncertainty in the leak rate calculation not addressed by this statistical evaluation such as the variability in the PWSCC crack morphology parameters (e.g., crack surface roughness and tortuosity) versus the PWSCC type assumptions described in this section.

Quantity	Units	Safety, Relief, and Spray Nozzles	Surge Nozzles
Outside Diameter	in	Case-specific	
Thickness	in	Case-specific	
Crack Orientation	-	Circumferential	
Crack Cross-Sectional Shape	-	Elliptical	
Crack Opening Displacement	in	Case- and Step-specific	
Crack Length	in	Case- and Step-specific	
Fluid Conditions Inside Pipe	in	Wet Steam	Saturated Liquid
Fluid Stagnation Pressure	psia	2250	
Steam Quality	-	100%	-
Stagnation Temperature	°F	_	653
External Pressure	psia	14.7	
Surface Roughness	in	3.94E-04	
Exit to Inlet Crack Area Ratio	-	1	
Number of 45° turns	per inch	24	
Entrance loss coefficient	-	0.61	

Table 6-1

Input Parameters to PICEP Leak Rate Calculations Based on PWSCC Flaw Morphology

Table 6-2

Input Parameters to PICEP Crack Opening Displacement Calculations Used in Leakage Comparison Study with SQUIRT Code

Quantity	Units	Value
Outside Diameter	in	7.75
Thickness	in	1.29
Young's Modulus	ksi	28300
Yield Stress	ksi	34.2
Flow Stress	ksi	45.6
Crack Shape	-	Rectangular
Ramberg-Osgood Exponent (α)	-	3.25
Ramberg-Osgood Parameter (n)	-	3.56
Non-pressure Axial Load	kips	5.41
Effective Bending Moment	in-kips	275.235

Leak Rate Modeling



Figure 6-1 Scoping Leak Rate Results Based on Wolf Creek Relief Nozzle Dissimilar Metal Weld Dimensions and Crack Opening Displacement Calculated by PICEP and SQUIRT





Case 12 - Critical for 1.2 Load Margin Factor

Figure 6-2 Crack Opening Displacement Contours for Example Case (Actual COD is Twice Shown Because of Symmetry Condition)



Figure 6-3 Example of Crack Opening Shape on Weld OD

7 SENSITIVITY CASE MATRIX

This section discusses the development and application of an extensive crack growth sensitivity matrix covering the geometry, load, and fabrication factors for each of the 51 subject welds, as well as the uncertainty in key modeling parameters such as those associated with welding residual stress, initial crack shape and depth, the K-dependence of the crack growth rate equation, and the effect of multiple flaw initiation sites in a single weld. Section 7 also presents a set of evaluation criteria that was developed to guide interpretation of the matrix results. The evaluation criteria provide safety margins based on explicit consideration of leak rate detection sensitivity, plant response time, and uncertainty in the crack stability calculations. This section begins with a description of the key modeling outputs that are developed using the crack growth (Section 4), crack stability (Section 5), and leak rate (Section 6) models described in previous sections.

7.1 Modeling Procedure and Outputs

In order to evaluate each crack growth sensitivity case, the following general procedure was applied based on the crack growth, crack stability, and leak rate submodels described in the previous sections:

- Step 1. Using FEACrack, the assumed initial crack is grown as a part-depth surface crack until the crack reaches a depth of about 93% of the wall thickness. This is the maximum depth for which the surface crack can be reliably meshed. In the case of partial-arc surface cracks, if the ends of the crack are calculated to join up, then the partial-arc model is transitioned to a 360° surface crack by assuming that the relatively small ligament between the ends of the partial-arc crack is instantaneously eliminated. In some cases, the surface crack may be observed to arrest prior to growing through-wall due to decay in the driving stress intensity factor to zero. In such cases, the analysis case is terminated at this step.
- *Step 2.* The surface crack profile is extended from the 93% depth to 100% depth based on a single step using the stress intensity factors along the crack front at the 93% depth.
- Step 3. The final 100% deep surface crack, which intersects the OD surface at a single point, is converted to an initial through-wall or complex crack by eliminating the thin ligament between the final surface crack and the OD surface. It is assumed that this surface ligament between the final 100% deep surface crack and the weld OD is instantaneously cracked in the region in which it is thinner than about 10% of the wall thickness. (In some cases, the surface ligament is assumed to be instantaneously cracked out to a significantly thicker ligament location.) For the case of surge nozzles the initial through-wall total opening angle was typically about 26°, while for the safety/relief and spray nozzles the initial through-wall total opening angle was typically about 42°. However, for the ID repair cases the initial

Sensitivity Case Matrix

through-wall total opening angle was often about 20° because of the difference in ligament geometry specific to the repair cases.

- Step 4. Using FEACrack, the initial through-wall or complex crack profile from Step 3 is grown until the point that subsequent post-processing shows the crack to reach its stability limit. In a few cases in which the initial through-wall crack is much longer on the inside surface than on the outside surface (e.g., 180° compared to 40°), the initial through-wall crack may be converted to a complex crack because of the difficulty in properly meshing the highly slanted through-wall crack geometry. This was applied in the following cases: 28b, 37c, 38c, 39c, 40c, and 41c. This conversion is a conservative assumption given that the complex crack envelopes the through-wall crack, reducing crack stability while not having a significant effect on the calculated leak rate.
- Step 5. The crack stability load margin factor and leak rate are determined for various steps in the through-wall or complex crack progression as a post-processing calculation as described in Sections 5 and 6. In the crack stability model, the crack face pressure is applied as an increase in the axial end cap load. The total axial load considers the operating pressure acting on the inside diameter cross section and on the crack face, as well as the dead weight and normal operating piping thermal constraint axial forces. Note that in the crack stability calculation the sum of dead weight and normal thermal axial forces is always taken based on the maximum reported for each geometry configuration, even though the typical (i.e., midrange) axial stress is usually assumed in the crack growth calculations. This approach is conservative because a higher axial load will always lead to reduced crack stability, whereas the effect of the axial load magnitude on the overall analysis through its effect on crack growth was not known with certainty before the matrix was substantially completed.

Step 5 facilitates calculating the time from detectable leakage to rupture based on different choices for margin factors on the calculated leak rate and on the loads used to calculate crack stability. Closely related to this time interval output are the calculated leak rates at the beginning and end of this interval. In some cases, the initial leak rate upon cracking of the thin surface ligament between the final surface flaw and OD surface may be greater than the detectable leak rate, including consideration of a margin factor applied to the calculated leak rate. Another key output is the load stability margin factor at the time that the leaking flaw produces a detectable level of leakage. A secondary key output parameter is the time from the initial assumed surface flaw until stable through-wall penetration, or alternatively until rupture. This time may be compared to the operating age of the subject weld as a secondary evaluation.

7.2 Evaluation Criteria

7.2.1 Introduction

In order to facilitate interpretation of the main analysis results of this study, a set of evaluation criteria were developed based on input from the EPRI expert panel and industry representatives. Consideration was given to the many modeling uncertainties addressed in the detailed calculations performed, with explicit treatment of uncertainties in the crack stability and leak rate

calculations. Attributes related to RCS leak rate detection sensitivity and plant response times were derived from current licensing commitments of the subject plants.

Hence, analytical case results of this study that meet these evaluation criteria fulfill the objective of this project as stated in Section 1.2 by demonstrating the viability of leakage detection to preclude the potential for rupture. However, these results should be applied by others to make a final determination regarding the timing of the initial PDI examination or mitigation for each of the subject welds.

7.2.2 Criteria

(

Figure 7-1 illustrates the evaluation criteria that were developed from the calculated development of increasing leak rate and decreasing stability margin with time for the through-wall phase of the crack growth progression. The criteria can be stated in either of two equivalent ways:

1. Are there at least 7 days after the calculated leak rate reaches 1.0 gpm prior to the critical crack size being reached based on a margin factor of 1.2 applied to the applicable loads?

or equivalently

2. Is the crack stability margin factor on the applicable loads at least 1.2 at a time seven days after the calculated leak rate reaches 1.0 gpm?

In Figure 7-1, the line with square markers reflects the calculated leak rate for the predicted through-wall crack as a function of time. The line with circular markers reflects the ratio of the critical supportable load versus the reported operating load (i.e., stability load margin) for the cracked nozzle weld also as a function of time. The plot begins at the time of the initial leaking through-wall crack. Applying a margin factor of four to a detection limit of 0.25 gpm accounts for the analytical uncertainties in calculating the leak rate, and results in a value of 1.0 gpm. Where the leak rate curve intersects 1.0 gpm establishes the beginning time when the hypothetical plant initially identifies the existence of this small leak and initiates its actions in response to a potential unidentified leak source. Conservatively, the plant would be in Mode 5 within the seven day period. The final criterion evaluates the stability margin on load. This is graphically illustrated by plotting a stability margin value of 1.2 on the seven-day line previously established and determining where the stability curve resides relative to this point. If this point is below the stability curve, then plant shutdown prior to rupture is indicated.

7.2.3 Basis

The technical basis for the evaluation criteria are as follows:

• Seven days are conservatively required for the plant to shut down in response to a slowly increasing leak rate after it reaches 0.25 gpm more than the baseline leak rate. In early 2007 US PWRs committed to implement enhanced leakage monitoring programs until completion of inspection / mitigation actions on their pressurizer nozzles. These commitments include daily measurement of RCS leakage and specific timetables for plant actions to identify and respond to a change in RCS leakage relative to a baseline value. The baseline leakage for

Sensitivity Case Matrix

each plant is established using leak rates measured within 7 days after achieving Mode 1 100% power operation following the most recent bare metal visual examination of the pressurizer Alloy 82/182 butt weld locations. Two leakage thresholds were established: a 0.25 gpm leak rate above the plant baseline that is sustained for 72 hours; or a 0.1 gpm leak rate change from one day to the next, which is sustained for 72 hours. If either of these thresholds is exceeded, and it cannot be confirmed that it is from sources other than pressurizer nozzle welds, then the unit will be placed in Mode 3 within 6 hours and Mode 5 within 36 hours. Therefore, the cumulative total elapsed time, assuming that a through-wall leak occurs just after the daily leakage measurement, would be approximately 6 days. However, because key actions in this sequence occur on roughly a daily basis, an additional full day has been included to conservatively define a minimum plant response period for application within the evaluation criteria.

- A margin factor of 4.0 is applied to a level of leakage (0.25 gpm) that plant detection systems can confidently detect to account for uncertainty in the calculated leak rate. A statistical study comparing the predictions of the SQUIRT leak rate code to leak rate measurements for IGSCC samples (see Appendix D) shows that for measured leak rates greater than about 0.1 gpm, there is a 95% probability that the predicted leak rate is within a factor of 1.5 to 2.0 of the measured value. The EPRI PICEP code, which was used in this study to calculate the leak rate for the matrix of crack growth sensitivity cases, conservatively tends to predict a slightly lower leak rate compared to the SQUIRT code given the modeling inputs appropriate to PWSCC presented in Section 6. The final leak rate margin factor of 4.0 is applied in recognition of other sources of uncertainty in the leak rate calculation not addressed by the statistical evaluation cited above such as the variability in the PWSCC crack morphology parameters (e.g., crack surface roughness and tortuosity) versus the PWSCC type assumptions in Section 6. This margin factor is also judged adequate to account for any delayed plant response that might result if sustained daily average leakage declines below the defined baseline leakage. However, to place normal plant RCS unidentified leakage in context, typical baseline leakage rates within several of the subject plants reported in a recent informal poll were on the order of 0.1 gpm or less.
- The margin factor of 1.2 on the loads applied in the critical crack size calculation accounts for uncertainty in these loads and in the critical crack size calculation methodology. The stability margin factor is the factor that when multiplied with each of the nozzle load components results in the critical loading that produces crack instability and rupture. The factor of 1.2 is appropriate in consideration of the significant conservatisms implemented in the critical crack size calculation methodology of Section 5. First, the secondary normal operating piping thermal constraint loads are included in the critical crack size calculation on an equal basis with the primary pressure and dead weight loads, although evaluations tend to demonstrate that such secondary loads are expected to be significantly or completely relaxed prior to failure. Second, the critical supportable load is reduced using a Z-factor approach to account for the possibility of an EPFM failure mechanism, although there is no clear evidence that a purely limit load based approach is insufficient. (It is recognized that there are no experimental data specific to circumferential cracks in Alloy 82/182 piping butt welds verifying that limit load rather than elastic-plastic fracture conditions control for this specific material.) Third, the safe end strength properties are applied in the critical crack size calculation. This has been shown to be appropriate for cracks located close to the safe end material. However, the WRS simulations tend to show that the highest axial stresses are

located toward or within the butter weld material built up on the low alloy steel nozzle material, consistent with the reported location of the Wolf Creek indications. In addition, the statistical crack stability model implemented as part of the complementary statistical evaluations presented in Appendix E supports the conclusion that the load margin factor of 1.2 bounds the prediction of rupture with high confidence. Moreover, the value of the factor of 1.2 reflects the degree to which modeling uncertainties have been addressed in the extensive matrix of crack growth cases considered. Given these considerations, the factor of 1.2 was selected as the midpoint between 1.0 and 1.4. The factor of 1.4 has historically been applied as one consideration in the critical crack size calculations of regulatory leak before break (LBB) evaluations [35].

• Extensive sensitivity cases are investigated to examine the effect of other modeling uncertainties such as in the basic weld dimensions, welding residual stress, other loads that drive crack growth, and stress intensity factor dependence of the crack growth rate equation.

7.2.4 Application

The general procedure for application of the evaluation criteria discussed above is as follows:

- Analysis sensitivity cases showing stable crack arrest prior to through-wall penetration are acceptable.
- For each analysis sensitivity case, additional margin beyond the evaluation criteria values may be identified in terms of:
 - a. Additional time beyond 7 days after the calculated leak rate reaches 1.0 gpm prior to the critical crack size being reached based on a load factor of 1.2, and
 - b. The stability load factor 7 days after a leak rate of 1.0 gpm is reached.
- Additional margin is also indicated by the increased magnitude of the calculated leak rate as the stability margin factor decreases toward 1.2. For some cases, the calculated leak rate may reach several tens of gallons per minute prior to the load margin factor decreasing to 1.2. For such relatively high calculated leak rates, prompt action is required by plant Technical Specifications with the added reinforcement of the recent plant commitments to enhanced leakage monitoring.
- Sensitivity cases not satisfying the above evaluation criteria may be investigated in greater detail through additional cases and/or types of analyses. Such additional analyses may identify unnecessary overconservatisms in the inputs or assumptions of the initial sensitivity case. (However, for the current study all sensitivity cases satisfied the above evaluation criteria, with the exception of Cases S1b and S2b, which are not credible cases as discussed in Section 7.5.13.)
- As discussed above, application of the evaluation criteria provides information for guiding a final determination as to the issue of timing of the initial PDI examination or mitigation for each of the subject welds.

7.3 Sensitivity Parameters

A matrix of 119 crack growth sensitivity cases was developed in order to cover the range of design, load, and fabrication conditions, as well as to address key modeling uncertainties. The 119 cases are defined in Table 7-1. Each of the key sets of sensitivity parameters addressed in this table is discussed below (moving from the leftmost columns toward the right). Each case is numbered sequentially from top to bottom (1 through 53), with the supplemental cases S1 through S9 at the bottom of the table. Up to three different welding residual stress (WRS) assumptions are considered for each line in the table, resulting in the total number of 119 analysis cases.

7.3.1 Fracture Mechanics Model Type

For all cases except for 52c, 52d, and 53b, the simplified cylindrical component geometry is assumed as discussed in Section 4. The effect of this assumption is investigated in Cases 52c and 53b through application of a nozzle-to-safe-end geometry in the fracture mechanics crack growth model.

7.3.2 Geometry Cases

The weld OD and thickness are the main required geometry inputs. In Table 7-1, the relative curvature of the cylindrical geometry is expressed in terms of the inside-radius-to-thickness-ratio (R/t). The R/t ratio expresses the relative distance for crack growth to through-wall penetration (leakage) versus the distance for crack growth around the circumference (increased crack size and reduced crack stability). Table 7-1 also lists the EPFM Z-factor calculated on the basis of the equivalent nominal pipe size of the weld as discussed in Section 5.

7.3.3 Piping Load Cases

The next set of inputs relate to the piping loads assumed in each particular case. The nominal axial stress loading (Pm) is based on the nominal operating pressure applied to the weld inside diameter cross sectional area plus the combination of dead weight axial and normal operating piping thermal constraint axial forces, applied over the intact weld cross sectional area. The bending moment listed is based on the effective moment calculated from the two bending moment components and the torsion component as discussed in Section 5. The bending stress (Pb) shown in the table is per the thick-walled section modulus of the weld cross section.

7.3.4 Welding Residual Stress Cases

The WRS assumptions are based on the results of the WRS FEA simulations presented in Section 3 for the fabrication conditions relevant to each nozzle type. The polynomial curve fits shown in Figures 7-2 through 7-9 were applied to develop the temperature inputs to the various FEACrack models to simulate the various WRS profiles. The "a" cases generally reflect nominal WRS modeling assumptions, in which the effect of the stainless steel weld is modeled. The "b" and "c" cases reflect the assumption of more conservative WRS profiles. It is noted that because the axisymmetric WRS results for the safety and relief WRS FEA cases were observed to result in crack arrest for all the safety/relief and spray crack growth cases (even without the benefit of the stainless steel weld assumed), the "modified ASME" WRS profile developed by EMC² [3] was assumed as the "c" case in many instances. This profile becomes compressive at a greater depth than the profiles calculated in Section 3 for the safety and relief WRS FEA cases. EMC² developed the "modified ASME" WRS profile based on the "thick-wall" stress data from stress measurements performed on BWR piping weld mockups [42,43], scaled to account for the higher yield strength of Alloy 182 weld material.

Figure 7-8 is included for the specific purpose of comparing the WRS profile assumed in Case 17b and its derivative sensitivity cases versus three other key profiles. As discussed below, the surge nozzles covered by Case 17, which have a thermal sleeve fill-in weld and a relatively high normal operating thermal piping bending moment, tend to have the most limiting results in the crack growth sensitivity matrix. In Figure 7-8, the heavy unmarked line is the profile assumed in Case 17b based on the fit from Figure 7-7. The other profiles in Figure 7-8 are the profiles calculated by DEI and the NRC contractor EMC² [36] for the complete set of nominal fabrication steps for the surge nozzles with fill-in welds (including the beneficial effect of the stainless steel weld), along with the ASME profile as modified by EMC² [3]. Figure 7-8 shows that the WRS profile applied in Case 17b is conservative with respect to all three of these key profiles. Because the WRS profile applied in Case 17b is shifted significantly in the conservative direction (i.e., tensile for a greater distance radially from the ID) versus each of these three profiles, it appropriately addresses the effect of WRS uncertainty. The size of the shift versus the other profiles is consistent with the level of WRS uncertainty indicated in a comparison study of WRS measurements and multiple predictions for a similar application [37]. Furthermore, it is noted that assumption of the EMC² WRS FEA results shown in Figure 7-8 leads to stable crack arrest if assumed for the Case 17 set of modeling inputs. Finally, it is emphasized that WRS distributions for actual components are expected to show circumferential variations even in the absence of weld repairs because of the starts and stops required by the welding process. The tendency of start/stop locations to drive a flaw locally through-wall is conservatively not credited when axisymmetric profiles such as those in Figure 7-8 are applied.

Note that the actual as-built configuration for the Plant E and H surge nozzles does not include a thermal sleeve fill-in weld. As discussed under "Bounded Cases" in Section 3.1.1, the surge nozzles at Plants E and H have a machined ID, and as such are expected to have a through-wall WRS distribution similar to that of a CE-design Type 9 surge nozzle. Therefore, the surge nozzles for Plants E and H are conservatively bounded by the WRS profiles assumed for the Type 8 surge nozzles (base Cases 17 and 18).

7.3.5 K-Dependence of Crack Growth Rate Equation

The standard power-law form of the MRP-115 deterministic crack growth rate equation is assumed in the crack growth simulations. Table 7-1 shows the assumed exponent applied to the Mode-I stress intensity factor and the power-law constant corresponding to the nominal nozzle operating temperature of 650°F, based on the standard thermal activation energy of 31 kcal/mole from MRP-115. No credit is taken in the crack growth calculations for the possibility of the temperature of the surge nozzle weld being somewhat reduced from the nominal pressurizer temperature. Likewise, no credit is taken in the crack growth calculations for the possibility of

Sensitivity Case Matrix

the temperature of the spray nozzle weld being reduced by the small steady spray flow that is typical of spray line operation.

7.3.6 Initial Flaw Cases

At the rightmost section of Table 7-1, the initial flaw geometry assumptions are listed for each case. For most cases a full arc 360° flaw having a depth of 10% of the wall thickness was assumed as the starting flaw. The Phase I scoping calculations indicated that in many cases a relatively long partial-arc surface flaw tends to grow to the same initial through-wall profile as an initial 360° flaw. Thus, the initial 360° flaw geometry was assumed in most cases in order to simplify the calculations. The assumption of an initial 360° flaw is also a conservative approach to addressing the concern for multiple flaw initiation and growth.

The flaw shape factor listed in Table 7-1 refers to the area of the initial flaw in comparison to a uniform depth flaw having the same ID length and depth. The "natural" shape refers to the shape that was found to grow in a self-similar manner for the beginning stages of growth under the Phase I set of geometry and load assumptions. This "natural" shape has a somewhat larger shape factor in comparison to the semi-elliptical flaw shape.

For the cases in which a partial-arc flaw is assumed as the initial flaw, the flaw is assumed to be centered at the circumferential location that is coincident with the maximum bending stress location. The point of maximum bending stress on the weld ID is the most likely point of crack initiation if an axisymmetric WRS profile is assumed. For example, for Case 17 the assumed bending moment (Pb = 13.57 ksi) results in a difference in axial stress of about 21 ksi between the maximum and minimum stress locations on opposites side of the ID. Based on experimental data (e.g., [40]), a stress exponent of 4 is typically assumed in the calculation of relative time to PWSCC initiation. The 21 ksi difference results in about a 45% higher (elastic) stress maximum versus minimum, considering the membrane axial stress loading and an assumed 54 ksi WRS at the ID. The 45% higher total axial stress corresponds to a factor of 4.5 on relative time to crack initiation assuming the stress exponent of 4. Finally, it is noted that Case S9b assumes that two identical initial partial-arc cracks are located on opposite side of the ID, one centered at the point of maximum total axial stress and the other centered at the point of minimum total axial stress. This case, which is discussed in Sections 7.4.13 and 7.5.13 below, is included as part of the investigation of the effect of multiple flaws for the limiting surge nozzle cases.

7.3.7 Consideration of Multiple Flaws

In the main matrix (Cases 1-53), the effect of multiple initiation is considered either through the assumption of an initially very long partial-arc surface crack (i.e., length-to-depth aspect ratio of 21:1) that can be considered to envelope a series of individual flaws (which typically have an aspect ratio in the range from 2:1 to 6:1 based on plant experience), or through the conservative assumption of an initial 360° full-arc flaw. In the supplemental cases (S1 through S9), alternative approaches are taken specific to the limiting surge nozzle cases in which either a set of two or three assumed flaws are grown in separate models and then combined into one weld cross section for application of the crack stability calculation. This approach is discussed further in Section 7.4.13 below.

7.4 Definition of Case Matrix

This subsection describes each subset of the 119 sensitivity cases, moving from Case 1 at the top of Table 7-1 down to Case S9 at the bottom. Note that the matrix was developed in an adaptive manner in which the initial cases (1-26) were used to determine the most limiting geometry, piping load, and WRS parameters. Then the most limiting conditions were applied to the remainder of the sensitivity matrix to ensure that the overall matrix covers modeling uncertainties in a robust manner.

7.4.1 Geometry and Load Base Cases (1-20)

These cases cover the design dimensions for each of the design configurations per the Westinghouse transmittal package of design sketches (see Section 2). Cases 1-9 cover the safety and relief nozzle configurations, Cases 10-16 cover the variety of spray nozzle configurations, and Cases 17-20 cover the surge nozzle configurations. In the case that the DM weld OD has a designed taper, the average weld thickness was assumed in the setting of the simplified cylindrical geometry. Cases 1-20 also cover the range of bending loads for each geometry configuration. The high load case is for the highest reported effective bending moment for the group of subject welds having the relevant geometry type. The low bending moment case was generally picked to have a value high enough to avoid crack arrest for at least some of the WRS input cases. It is emphasized that the reported moment loads for each subject weld may reflect conservative assumptions taken in piping analyses, and as such should be considered upper bound type values. The variability in axial membrane stress is much lower than the variability in bending stress, so the sensitivity to this other load factor is investigated separately in Section 7.4.5 below. Finally, it is noted that Configurations 2a and 2b are combined in the matrix because they correspond to the same basic weld ID and OD dimensions.

7.4.2 ID Repair Base Cases (21-26)

These cases reflect five different patterns of non-axisymmetric WRS profiles based on the part circumference ID repair WRS cases discussed in Section 3, with applied stresses as described in Section 4.1 and demonstrated in Figure 4-3. The nomenclature for these cases describe the repair case followed by the "baseline" stress for the remainder of the model. Figure 4-3 represents Cases 21a, 22a, 23a, and 24a where the stresses local to a 20° (about 0.9") ID repair in the safety/relief nozzle are considered versus a "baseline" stress for the nozzle model without a stainless steel weld. As shown in this figure, the repair portion of the model extends over about 10° (due to half symmetry), followed by a 20° zone that includes the compressive effects of the repair region, with the remainder of the model equal to the "baseline" stress state. Case 23b evaluates the same repair condition with a "baseline" stress equal to the ASME distribution considered in other analysis cases. Case 23c evaluates three ID repairs evenly spaced around the nozzle circumference. Cases 25a and 26a consider a 40° (about 4.1") ID repair of the surge nozzle using a baseline stress for the nozzle model with a stainless steel weld, and Case 25b is the same repair with a baseline stress without a stainless steel weld. While a part circumference repair WRS FEA case was not performed for the surge nozzles, a repair stress distribution was assumed based on the axisymmetric surge nozzle repair case in combination with the relative

circumferential stress dependence observed for the case of a part circumference repair in a safety/relief nozzle.

7.4.3 Further Bending Moment Cases (27-30)

These cases examine in greater detail the effect of a variable bending moment for the case of surge nozzles having a fill-in weld. This type of nozzle is shown in the matrix results to be one of the most limiting cases. These cases ensure that the detailed dependence of the results on bending moment is determined. Although not presented in this report, an additional set of detailed sensitivity cases were also run for the case of the Phase I calculation inputs to investigate the effect of a variable bending moment.

7.4.4 Cases to Investigate Potential Uncertainty in As-Built Dimensions (31-32)

A review of available as-built dimensions for two of the nine subject plants did not reveal any obvious inconsistencies versus the design dimensions. In general, the design dimensions are believed to be the most accurate dimensional data because of the difficulty in accurately determining the locations of the various material interfaces within the joint configuration based on the outside surface appearance of the joint. As a hypothetical exercise, these two cases assume that the weld thickness varies $\pm 10\%$, while maintaining the same inside diameter and piping loads (axial force and effective moment).

7.4.5 Axial Membrane Load Sensitivity Cases (33-34)

These two cases vary the membrane stress loading based on Case 4. Case 4 covers geometry Configuration 1b, which corresponds to one of the greatest ranges in membrane stress loading as shown in Table 7-2. Configuration 2a/2b corresponds to a larger range of Pm values, but Case 6 explicitly bounds the weld with the highest Pm+Pb stress loading. The other geometry configurations tend to correspond to a relatively tight range on membrane stress loading.

7.4.6 Effect of Length Over Which Thermal Strain Simulating WRS is Applied (35)

This case investigates the effect of the distance over which the temperature load is applied in the cylindrical crack growth model in order to simulate the desired WRS profile. In the sensitivity case, this distance is reduced from 1.0 inch to 0.5 inch in the half-symmetric model (2.0 inch to 1.0 inch for the full geometry). The nominal distance of 2.0 inches is based on the typical axial length of weld metal.

7.4.7 Simulation of Elastic-Plastic Redistribution of Stress at ID (36)

This case is included to investigate the potential effect of elastic-plastic redistribution of stress at locations near the ID surface on the tensile side of the neutral bending axis, where the high assumed tensile WRS combines with tensile bending and axial membrane stresses. A circumferentially varying WRS profile is assumed in this case in order to maintain the maximum

total axial stress anywhere on the weld cross section to 54 ksi. It is noted that only a small portion of the cross section, at the immediate ID surface, exceeds the nominal maximum stress of 54 ksi when the axial and bending loads are applied. The desired stress distribution was therefore achieved by adjusting the input thermal distribution at the ID surface such that when the axial and bending loads are applied, the ID surface stress does not exceed the nominal maximum. The compressive side of the bending moment is not adjusted.

7.4.8 Effect of Initial Crack Shape and Depth (37-41)

These cases are included to investigate the sensitivity of the main leakage and stability analysis results to the assumed initial flaw shape and depth given a fixed aspect ratio for the initial flaw. Case 6 was chosen as the base case conditions for this sensitivity study because it was observed to be the most limiting of the safety/relief and spray nozzle cases.

7.4.9 Effect of Stress Intensity Factor Dependence of Crack Growth Rate Equation (42-47)

These six cases investigate the effect of uncertainty in the K-dependence of the MRP-115 crack growth rate equation. The limiting safety/relief, spray, and surge nozzle configurations are investigated in these cases.

Figures 7-10 through 7-13 illustrate the new Alloy 182 crack growth rate curves developed for the low and high K-exponent cases. Figure 7-10 shows the new crack growth rate curves, and Figures 7-11 through 7-13 show the "weld factor" fits used to develop the deterministic 75^{th} percentile power-law constants corresponding to each new K-exponent. The K-exponent value (*n*) cannot sensibly be varied independently of the power-law constant *C* as the units for *C* depend on the K-exponent *n*. The procedure to develop the two new curves is identical to that described in detail in MRP-115, except that the K-exponent for the two new cases was forced to be either the 5^{th} (1.0) or 95^{th} (2.2) percentile K-exponent value rather than the best-fit exponent (1.6). The 5^{th} and 95^{th} percentile K-exponent values themselves are based on the standard error for the K-exponent (s.e. = 0.3474) from the original MRP-115 [21] multivariate linearized fit procedure.

7.4.10 Effect of Pressure Drop Along Leaking Crack (48)

This single case investigates the effect of the base assumption made in the matrix that the full operating pressure applies to leaking through-wall cracks as well as to surface cracks. In reality, for a leaking crack there must be a pressure drop along the crack path, resulting in a reduced average crack face pressure. The reduced crack face pressure tends to increase crack stability and reduce the crack growth rate, but it also tends to decrease the leak rate. For this case, PICEP was used to calculate the pressure drop on the crack face, and the average pressure (1330 psig) was applied in the crack growth and critical crack size calculations. The effect on the calculated leak rate was determined through the normal procedure of applying the crack opening area from the crack growth model in PICEP.

7.4.11 Effect of Relaxation of Normal Operating Thermal Load (49-51)

These cases investigated the effect of relaxation of the normal operating thermal loads assumed in the crack growth and crack stability calculations. For these cases, it is assumed that these stresses are 100% relaxed at the point that the crack becomes through wall. Besides decreasing the crack growth rate and increasing crack stability, the effect of removing these stresses is also a decrease in the leak rate through the reduction in the crack opening area. In Section 5, it was conservatively assumed to include the normal operating thermal constraint loads in the calculations although detailed evaluations tend to indicate that such secondary stresses are expected to significantly or completely relax prior to rupture. Cases 49-51 examine the effect of this assumption.

7.4.12 Effect of Nozzle-to-Safe-End Crack Growth Model vs. Standard Cylindrical Crack Growth Model (52-53)

These three cases (Case 52c, 52d, and 53b) are included to investigate the effect of the detailed nozzle-to-safe-end geometry versus the simplified cylindrical geometry. The methodology of the detailed nozzle-to-safe-end geometry as opposed to the simplified cylindrical model used for the other cases is described in Section 4.1.1. Cases 52c and 53b were included to investigate whether the simplified cylindrical geometry results in any significant differences in analysis results versus the detailed nozzle-to-safe-end geometry when the same WRS profile is simulated in both models using the thermal strain method. Case 52c is based on the Type 1a safety and relief nozzle configuration of Case 1c, with the same piping loads applied. Case 53b is based on the Type 8 surge nozzle configuration of Case 17b, with the same piping loads applied. Finally, Case 52d is included to investigate the effect of basing the WRS input to the crack growth model on direct interpolation of the results of the FEA WRS simulation (per the methodology described in Section 3). For Case 52d, the stainless steel weld to the stainless steel piping was not simulated as part of the FEA WRS simulation preceding the crack growth calculation. Therefore, the direct FEA WRS simulation for Case 52d produces an axial stress profile that is comparable to that for Case 1b, which also does not reflect the benefit of the stainless steel weld.

7.4.13 Supplementary Cases Specific to Effect of Multiple Flaws on Limiting Surge Nozzles (S1-S9)

The supplemental cases S1-S9 were added to further investigate the potential effect of multiple flaws in the subject surge nozzles. Cases S1a, S1b, and S8b examine the effect of assuming a 360° initial flaw on Cases 17a, 17b, and 19b, respectively, rather than a 21:1 initial partial-arc flaw. Case S2b is a further sensitivity study on Case S1b in which the effective moment load (dead weight and normal operating thermal load) is reduced to that corresponding to the surge nozzle for Plant C. The moment load for Cases 17a and 17b bounds the surge nozzles for Plants B and G.

Case S3b was designed to apply the Wolf Creek surge nozzle findings to develop additional multiple flaw assumption cases. Table 7-3 shows detailed summary statistics for the three circumferential indications that were reported in the Wolf Creek surge nozzle. The two largest indications may be enveloped by a flaw having an aspect ratio of 20:1, just less than the standard

21:1 assumption applied in the matrix. The third indication (Indication #1) was located away from the two largest indications, but had an area that is less than 0.2% of the wall cross section. In Case S3b, a flaw having the length and depth reported for this indication is grown with the piping bending moment assumed to line up with the flaw center. After 1.3 years of growth this flaw is predicted to have grown to the profile marked by closed squares shown at the top of Figure 7-14 (with depth of 56% and total length of 67°). The 1.3 years was chosen because it is the elapsed time at which the Case 17b flaw is calculated to reach 7 days of leakage (all above 1.0 gpm).

Cases S4b through S7b are crack stability cases in which a pair of flaws (one on each halfmodel) are superimposed on the weld cross section for Case 17b at its growth step corresponding to the point after which 7 days of leakage (all above 1.0 gpm) has occurred. For Cases S4b, S5b, and S6b the pair of flaws that is superimposed is the Case S3b profile after 1.3 years of growth. As shown in Figure 7-14, in Case S4b the pair of additional flaws are inserted on the Case 17b cross section near the bottom of the cross section, with each additional flaw just touching. In Case S6b the pair of additional flaws are assumed to be just in contact with both ends of the Case 17b profile. In Case S5b an intermediate position to these other cases is assumed. In this manner, the sensitivity of the stability results to the assumed location of the pair of additional flaws is checked. This approach to applying the Wolf Creek experience is conservative in that the number of flaws outside the 21:1 envelope is doubled versus the Wolf Creek experience and each of these two flaws is grown based on the moment direction aligning with the flaw center, increasing the size of the grown flaw. Additionally, Case S7b was considered in which a hypothetical pair of flaws, each 95% through-wall and 50° in circumferential extent, was added to the Case 17b cross section.

It is noted that the approach of Cases S4b through S7b of addressing multiple flaws through independent growth of the individual flaws presumes that any crack interaction effects do not have a significant effect on the results. Based on experience, this is in fact a reasonable assumption. Analysis work investigating the flaw interaction effects on the stress intensity factor typically show only mild increases in stress intensity factor versus the single-flaw case. For example, for the simplified case of two identical coplanar through-wall cracks in an infinite plate, the stress intensity factor at the adjoining crack tips is only increased by about 10% when the separation distance is half the total length of each individual crack [38].

Finally, Case S9b was designed as another case to further investigate the concern for multiple flaws in the subject surge nozzles. This case is also closely related to Case 17b, but assumes a pair of initial 26% through-wall 21:1 aspect ratio flaws placed at the top and bottom of the weld cross section, rather than a single such flaw placed at the top of the cross section centered at the location of maximum axial bending stress. Because the two flaws when grown in separate crack growth models remain a considerable distance apart for the relevant growth period (see Figures 7-15 and 7-16), it is clear that crack interaction effects are insignificant for this case. Thus, it is appropriate to model growth using separate meshes and then combine the two crack profiles onto a single weld cross section for the purpose of the crack stability calculation. Unlike for Cases S4b through S7b, this process was repeated for multiple times yielding a crack stability curve as a function of time. In addition, because of the lack of crack interaction in this case, the leak rate time dependence of the leaking (i.e., upper) flaw in Case S9b can be taken as identical to that for Case 17b.

7.5 Matrix Results

All 109 cases in the main sensitivity matrix (Cases 1-53) showed either stable crack arrest (60 cases) or crack leakage and crack stability results satisfying the evaluation criteria (49 cases). In most cases, the results showed large evaluation margins in leakage time and in crack stability. In addition, a supplemental set of 10 cases (Cases S1-S9) was investigated to further explore the potential effect of multiple flaws on the limiting surge nozzle cases. With the exception of Cases S1b and S2b, which are not credible cases as discussed below in Section 7.5.13, the supplemental sensitivity cases also satisfied the evaluation criteria. Figure 7-17 shows nine example crack meshes covering the variety of crack types.

Tables 7-4, 7-5, and 7-6 present detailed results for the 69 cases that were investigated using the newly developed FEACrack software tools. An additional 50 cases were confirmed to show stable crack arrest using a simplified axisymmetric crack growth model in which the bending moment was conservatively applied as a linear stress profile based on the highest bending stress circumferential position. The axisymmetric model is based on the axisymmetric stress intensity factor solution published by Anderson et al. in WRC Bulletin 471 [39]. Table 7-4 shows the key results for the surface crack at the point it becomes through wall. Table 7-5 shows similar key results but also the calculated leak rate for the through-wall growth step that resulted in just above a 1.0 gpm leak (or the initial through-wall leak rate if greater than 1.0 gpm). Table 7-6 shows corresponding crack stability and leak rate results for the through-wall growth step that resulted in a load stability margin factor just above 1.2. Finally, Table 7-7 is a summary of the key sensitivity results for three main output parameters: time interval from 1 gpm leak rate until stability margin factor reaches 1.2, stability margin factor reaches 1.2.

For those cases that showed through-wall crack development, Figures 7-18 through 7-21 show in column chart form the main analysis results from Tables 7-4, 7-5, and 7-6. Figures 7-18 and 7-19 cover the first half of the main matrix, while Figures 7-20 and 7-21 cover the second half. Figures 7-18 and 7-20 show the key time and leak rate outputs, specifically the time between the leak rate reaching 1.0 gpm and the crack stability margin factor decreasing to 1.2, and the leak rates corresponding to the beginning and end of this interval. (In some cases, the initial throughwall leak rate is greater than 1.0 gpm.) The time intervals shown in these two figures may be directly compared to the 7-day interval of the evaluation criteria. It is observed that all the time intervals in these two plots exceed 7 days. Additional key results are illustrated in Figures 7-19 and 7-21, which show the calculated load margin factor at the time that the leak rate reaches 1.0 gpm (or initial leakage if greater than 1.0 gpm). The minimum load margin factor for the cases covered in these two figures is 1.38. Lastly, Figures 7-22 through 7-41 show complete leak rate and crack stability margin trends versus time for 20 selected cases, including 16 of the most limiting cases (those cases in which the load margin factor was calculated to be 1.75 or lower when the leak rate was calculated to be 1 gpm). These plots directly illustrate the margin levels that exist versus the evaluation criteria illustrated in Figure 7-1. The results of the individual subsets of cases are discussed below.

7.5.1 Geometry and Load Base Cases (1-20)

All these cases show at least 35 days from the 1.0 gpm leak rate until the load margin factor of 1.2 is reached. The most limiting base cases are 6c (safety/relief), 12c (spray), and 17b (surge). For Case 17b the initial through-wall leak rate is calculated to be 2.6 gpm, with the leak rate increasing to 69 gpm when the stability factor reaches 1.2. These cases also show that the effect of increased piping moment load (Pb) is to decrease somewhat the available margin. This behavior shows that the beneficial actions of an increased moment in pushing the crack through-wall at a more concentrated location on the circumference plus increased leak rate for a given through-wall crack extent are outweighed by the detriment of decreased crack stability.

7.5.2 ID Repair Base Cases (21-26)

These repair cases show relatively high evaluation margins compared to the axisymmetric WRS cases. This behavior is due to the tendency of the high tensile WRS in the repair zone to quickly push the crack through wall at that location. Note that for Cases 21a, 22a, 23a, 24a, and 26a the crack growth progression was terminated with load margin factors much greater than 1.2 because of difficulty in meshing these more extreme crack profiles. However, the existing results clearly illustrate large levels of evaluation margin in these cases.

7.5.3 Further Bending Moment Cases (27-30)

The results of these cases for the limiting surge nozzle configuration confirm that Case 17b reflecting the maximum effective moment value is in fact the limiting surge nozzle case. The competing effects of the moment on crack stability, leak rate, and crack shape development result in the maximum moment case being most limiting.*

Note that like Case 17b, Cases 27b and 28b assume an initial 21:1 aspect ratio flaw. The 21:1 aspect ratio corresponds to the highest aspect ratio reported for any of the Wolf Creek pressurizer nozzle indications (in the relief nozzle) and also bounds the 20:1 aspect ratio enveloping the two largest indications reported in the Wolf Creek surge nozzle (see Table 7-3). The assumption of a 21:1 initial flaw accounts for the possibility of multiple significant and growing flaws because the typical aspect ratio for a single flaw is usually in the range of 2:1 to 6:1 based on plant experience. Moreover, these cases tend to show a relatively short time (1.2, 1.3, and 3.4 years, respectively) between the initial flaw depth and through-wall penetration. Within this relatively short time period, it is highly unlikely that a large portion of the 360° length (i.e., 37 inches) of the inside circumference would initiate flaws. Section 7.5.13 below discusses the results of the supplemental cases to further investigate the effect of multiple flaws on the limiting surge nozzle cases.

^{*} The effect of decreased moment in increasing the time interval from a 1 gpm leak rate until the stability margin factor of 1.2 is reached is observed through comparison of Case 27b versus base Case 17b (38 versus 35 days). Case 28b shows a decrease in the time interval result because in this case the calculated through-wall crack was converted to a complex crack having a 10% through-wall depth on the uncracked portion of the ID. As discussed in Section 7.1, the conversion to a complex flaw geometry was conservatively made because of the difficulty in meshing the through-wall crack geometry for this case. In addition, Case 29b shows a reduced time interval result because in its case an initial 360° surface flaw was assumed rather than an initial partial-arc flaw as in Cases 17b, 27b, and 28b.

7.5.4 Cases to Investigate Potential Uncertainty in As-Built Dimensions (31-32)

These cases show that a change of $\pm 10\%$ in the wall thickness (assuming same ID) acts to increase or decrease the time margin by about one third given Case 1 as a baseline. Reducing the wall thickness reduces the time margin. Again the effect on critical crack size of a reduced wall cross section outweighs the benefit of a smaller distance for growth through-wall to leakage. These results show that the analysis results are modestly sensitive to the exact weld diameter and thickness.

7.5.5 Axial Membrane Load Sensitivity Cases (33-34)

Consistent with the previous results, these cases show that an increase in the membrane stress loading results in a slight decrease in the time margin. These cases confirm that the membrane stress variations within each geometry configuration are not significant. Even given this conclusion, it is noted that the most limiting cases in the matrix (Case 6c, 12c, and 17b) do bound the highest Pm+Pb combined stress loads for the subject welds covered in each case.

7.5.6 Effect of Length Over Which Thermal Strain Simulating WRS is Applied (35)

Case 35c shows the time interval result for Case 6c is reduced from 41 to 32 days when the length over which the thermal strain applied to simulate WRS is reduced in half. This behavior is due to a slight increase in the cracked area fraction at the point of through-wall penetration for Case 35c (0.447 vs. 0.435). This case shows that the modeling results are reasonably insensitive to this modeling length assumption. Furthermore, there does not appear to be any evidence of a significant WRS relaxation effect on the crack growth progression. Such effects are apparent in other cases in which there is a clear change in global component stiffness with the presence of a large flaw.

7.5.7 Simulation of Elastic-Plastic Redistribution of Stress at ID (36)

Case 36c shows only small differences in results versus those for its base case (Case 6c). For example, the main time interval result for Case 6c is increased by one day from 41 to 42 days. Very similar behavior in leak rate and stability margin factor development is observed in Figure 7-22 (Case 6c) and Figure 7-31 (Case 36c). These results indicate that the assumption of elastic combination of the high welding residual stresses assumed at the weld ID with the piping axial membrane and bending stresses does not introduce significant modeling uncertainties.

7.5.8 Effect of Initial Crack Shape and Depth (37-41)

As expected based on Phase I calculation results, these cases confirm that the results in terms of time between detectable leakage and rupture are insensitive to initial partial-arc crack shape factor for a given initial crack length and depth (Cases 37 through 39). Cases 40 and 41 show furthermore that the results are relatively insensitive to the initial crack depth given a fixed initial aspect ratio. Therefore, it was appropriate that these factors (initial shape factor and depth) were investigated in a limited manner in the sensitivity matrix.

7.5.9 Effect of Stress Intensity Factor Dependence of Crack Growth Rate Equation (42-47)

These six cases showed that the limiting base cases are only modestly sensitive to the Kdependence exponent assumed. The limiting surge nozzle case (17b) was shown to be most sensitive of the three limiting cases, with the time interval result reduced from 35 to 22 days when the K-exponent is increased from 1.6 to 2.2 (Case 47b). Even given this K-dependence sensitivity, there is sufficient margin in this result to accommodate an unlikely combination of detrimental factors, for example this K-dependence sensitivity plus the sensitivity to as-built weld thickness of $\pm 10\%$ assumed in Cases 31c and 32c. Likewise, there is sufficient margin in the Case 47b results to accommodate the possibility of an increased crack growth rate power-law constant versus the 75th percentile value assumed (see MRP-115 [21] and Section 7.4.9). Use of the 95th percentile MRP-115 "weld factor" rather than the 75th percentile "weld factor" corresponds to a factor of 1.77 on the crack growth rate magnitude, which would reduce the 22 days calculated for Case 47b to about 13 days. It is highly unlikely that the stress intensity factor dependence and power-law constant effect would combine in this manner.

7.5.10 Effect of Pressure Drop Along Leaking Crack (48)

This sensitivity case showed a very small benefit of considering the decrease in pressure across the leaking crack face for the limiting surge nozzle case (17b). The time interval result increased from 35 to 39 days. This small difference justifies excluding the modeling complication of reduced crack face pressure for leaking cracks in the base matrix.

7.5.11 Effect of Relaxation of Normal Operating Thermal Load (49-51)

Two of these three sensitivity cases (49c and 50b) show a greatly increased time between a leak rate of 1.0 gpm and the load margin factor of 1.2 being reached, while the third (51b) shows stable crack arrest as does its base case (19b). The time interval result increased from 41 to 145 days for Case 6c, and from 35 to 293 days from Case 17b. These cases clearly show a large benefit if the piping thermal constraint loads are significantly relaxed once the crack grows through-wall. Furthermore, based on the results for low piping moment cases, stable crack arrest could be expected to occur in many cases if the piping thermal constraint loads are significantly relaxed before the crack reaches through-wall penetration. The degree to which such relaxation might occur would depend on the amount of nozzle rotation produced by the piping system, with greater rotation as the critical crack size is approached.

7.5.12 Effect of Nozzle-to-Safe-End Crack Growth Model vs. Standard Cylindrical Crack Growth Model (52-53)

The results for these cases indicate that there is no significant nonconservatism introduced by use of the simplified cylindrical geometry versus the more detailed nozzle-to-safe-end geometry. Case 52c (safety/relief nozzle) yielded a time interval result (time from 1 gpm until stability margin factor reaches 1.2) of 94 days compared to 109 days for Case 1c. Case 53b (surge nozzle) produced a time interval result of 49 days versus 35 days for Case 17b. As described in Section 7.4.12, Cases 52c and 53b were based on WRS simulation using the thermal strain

Sensitivity Case Matrix

method with the same temperature profile as the corresponding base case. On the other hand, Case 52d was based on direct interpolation of the results of a WRS FEA simulation. As was the case for Case 1b, Case 52d produced crack-tip closure and stable crack arrest.

7.5.13 Supplementary Cases Specific to Effect of Multiple Flaws on Limiting Surge Nozzles (S1-S9)

The supplemental sensitivity cases assuming an initial 360° flaw do not satisfy the evaluation criteria for the case of surge nozzles having a fill-in weld (used to seat the thermal sleeve) and a relatively high moment load and given the WRS assumption that does not take credit for the benefit of the stainless steel weld (Cases S1b and S2b).[†] However, these 360° initial flaw cases are not appropriate for making conclusions regarding these surge nozzles, which show relatively fast growth through wall, because of the unlikelihood of initiation over the 37-inch inside circumference during a narrow time band. (For Case 17b, 1.22 years was calculated for growth from the initial 26% through-wall flaw to through-wall penetration.) On the other hand, for the surge nozzles that have a fill-in weld but not a relatively high moment load (addressed by Cases 18, 26, 29, and 30), the calculated time for through-wall growth is considerably longer than 1.22 years, and a 360° 10% through-wall initial flaw geometry was assumed for these cases.

As described above in Section 7.4.13, the results of Case S3b were used as an input to stability Cases S4b, S5b, and S6b. In this manner, the three indications found in the Wolf Creek surge nozzle weld were conservatively applied to further investigate the potential effect of multiple flaws for the limiting surge nozzle case. After 7 days of detectable leakage per Case 17b (initial leak rate of 2.6 gpm), Cases S4b, S5b, and S6b show a load margin factor of 1.43, 1.48, and 1.29, respectively. The lowest of the three margin factors (1.29) is for Case S6b, in which the pair of additional flaws is assumed to just touch the leaking crack profile from Case 17b. The highest of the three load margin factors (1.48) is for Case S5b, which is the case in which the additional pair of flaws is closest to the fully plastic NSC neutral axis. Finally, as an additional hypothetical case, Case S7b shows a corresponding load margin factor of 1.44 even given the pair of 95% through-wall additional flaws on the weld cross section of Case 17b after 7 days of detectable leakage.

Also as described above in Section 7.4.13, Case S9b was designed to further investigate the effect of multiple flaws on the subject surge nozzles. Case S9b assumes a pair of initial 26% through-wall 21:1 aspect ratio flaws placed at the top and bottom of the weld cross section, rather than a single such flaw placed at the top of the cross section centered at the location of maximum axial bending stress (Case 17b). As discussed in Section 7.4.13, the leak rate and stability margin trends can be based on separate growth of the two assumed initial flaws, with combination of the flaws in a single weld cross section for the purpose of the crack stability calculation. The resulting crack growth progression for Case S9b is shown in Figure 7-15 in terms of Cartesian coordinates, and in Figure 7-16 in terms of polar coordinates. Because of the lack of crack interaction, the time from the initial flaws to through-wall penetration of the upper flaw is unaffected versus the 1.22 years of Case 17b. Likewise, the leak rate trend with time

[†] For Case S2b the time interval result is 4 days. Although less than 7 days, the initial leak rate for this case is 4.9 gpm, increasing to 6.0 gpm after 3 days. These relatively high leak rates are expected to be readily detectable even considering a leak rate margin factor of 4 to account for uncertainty in the leak rate calculation. Therefore, despite the time interval result being 4 days in this case, the results may still be acceptable.

shown in Figure 7-40 is unaffected versus Case 17b. However, the stability margin factor trend in Figure 7-40 is lowered between 0.10 and 0.12 by the presence of the second flaw. The effect is to reduce the time interval from the initial leak rate of 2.6 gpm until reaching a load margin factor of 1.2 from 35 to 29 days. In summary, Case S9b shows a modest effect on crack stability if two initial flaws covering 46% (167°) of the ID circumference are assumed as opposed to a single initial flaw covering half this circumferential extent and centered at the location of maximum axial bending stress.

On the basis of the supplemental set of cases, it is concluded that the concern for multiple flaws in the limiting surge nozzles is adequately addressed by cases that satisfy the evaluation criteria with additional margin.

7.6 Conclusions

7.6.1 Main Sensitivity Matrix

All 109 cases in the main sensitivity matrix showed either stable crack arrest (60 cases) or crack leakage and crack stability results satisfying the evaluation criteria (49 cases). In most cases, the results showed large evaluation margins in leakage time and in crack stability.

In the base matrix, an initial partial-arc flaw having a length-to-depth aspect ratio of 21:1 was assumed for the surge nozzle cases having a relatively large piping thermal constraint bending moment. (As discussed above in Section 7.5.13, a 360° initial flaw is not a credible assumption for the surge nozzle cases having a relatively large piping thermal constraint bending moment because of the unlikelihood of initiation over the 37-inch inside circumference during a narrow time band. For Case 17b, 1.22 years was calculated for growth from the initial 26% throughwall flaw to through-wall penetration.) The 21:1 aspect ratio corresponds to the highest aspect ratio reported for any of the Wolf Creek pressurizer nozzle indications (in the relief nozzle) and also bounds the 20:1 aspect ratio enveloping the two largest indications reported in the Wolf Creek surge nozzle. The assumption of a 21:1 initial flaw accounts for the possibility of significant growing multiple flaws because the typical aspect ratio for a single flaw is usually in the range of 2:1 to 6:1 based on plant experience. Moreover, the surge nozzle cases that tend to show the least margin between detectable leakage and rupture show a relatively short time (e.g., 1.2 years) between the initial flaw depth and through-wall penetration. Within this relatively short time period, it is highly unlikely that a large portion of the 360° length (i.e., 37 inches) of the inside circumference would initiate flaws.

7.6.2 Supplemental Sensitivity Matrix

In order to further investigate the potential effect of multiple flaws in the subject surge nozzles, several supplemental cases were added. The supplemental sensitivity cases assuming an initial 360° flaw do not satisfy the evaluation criteria for the case of surge nozzles having a fill-in weld (used to seat the thermal sleeve) and a relatively high moment load and given the WRS assumption that does not take credit for the benefit of the stainless steel weld. However, these 360° initial flaw cases are not appropriate for making conclusions regarding these surge nozzles, which show relatively fast growth through wall, because of the unlikelihood of initiation over the

Sensitivity Case Matrix

37-inch inside circumference during a narrow time band. On the other hand, as described in Section 7.4.13, conservative application of the three indications found in the Wolf Creek surge nozzle weld for surge nozzles with a fill-in weld and relatively high moment load gives results meeting the evaluation criteria. In addition, considering a case with two long initial partial-arc flaws covering 46% of the ID circumference as opposed to a single initial flaw covering half this circumferential extent (and centered at the location of maximum axial bending stress) has only a modest effect on crack stability for these limiting surge nozzles. On this basis, it is concluded that the concern for multiple flaws in the limiting surge nozzles is adequately addressed by cases that satisfy the evaluation criteria with additional margin.

7.6.3 Tendency of Circumferential Surface Cracks to Show Stable Arrest

An additional key finding concerns the significant number of crack growth sensitivity cases that showed stable crack arrest prior to through-wall penetration. This type of behavior is consistent with the relatively narrow band of relative depths reported for the four largest Wolf Creek indications (23%, 25%, 26%, and 31% through-wall). As emphasized in the MRP white paper [1], it is statistically unlikely that these four indications would be found in this narrow depth band if they were in fact growing rapidly in the depth direction at the time they were detected. The basic reason that circumferential cracks may tend to arrest prior to through-wall penetration is that to the extent the through-wall welding residual stress profile is axisymmetric, it must be self-balanced at a particular circumferential position, meaning that a significant portion of the wall thickness must have compressive axial welding residual stresses. On the other hand, for axial flaws that are driven largely by tensile hoop welding residual stresses, these hoop welding residual stresses are generally balanced by the compressive residual stresses in the base metal material upstream and downstream from the dissimilar metal weld. Hence, the hoop welding residual stress in the weld material is more likely to remain tensile and drive an axial flaw through-wall than is the case for axial residual stress and circumferential flaws. This expectation is consistent with general PWR plant experience that has shown part-depth and leaking axial PWSCC in Alloy 82/182 piping butt welds, but only indications of part-depth circumferential flaws in such weldments.

7.6.4 Nozzles with Liner Directly Covering Dissimilar Metal Weld

In this evaluation, the liners installed in lieu of weld cladding for safety/relief nozzle Type 2a/2b and spray nozzle Type 5 are conservatively not credited with precluding PWSCC-susceptibility in the underlying DM weld. The design function of these liners is, like weld cladding, to isolate the nozzle low alloy steel material from the RCS coolant. The deterministic crack growth calculations for these nozzles presuppose that RCS coolant has access to the DM weld surface under the liner, for example via through-wall cracking of the nickel-alloy fillet weld at the end of the liner, and that the DM weld material subsequently initiates PWSCC.

7.6.5 Potential Effect of Multiple Through-Wall Flaw Segments on Leak Rate

It is noted that another type of multiple flaw concern than the one discussed in Section 7.5.13 is the potential effect of multiple through-wall flaw segments to reduce the leak rate in comparison to a single through-wall flaw. However, this concern is addressed as follows:

- First, it should be recognized that the effect of the tight intergranular SCC type morphology is generally addressed by the leak rate prediction methodology.
- Second, the effect of multiple through-wall flaw segments to reduce the leak rate is mitigated by the increased resistance to rupture provided by the ligaments between the flaw segments. Significant axial offsets between crack segments may be likely in this situation because of the relatively long axial region of susceptible material, and such axial offsets would be expected to increase the resistance to rupture substantially.
- Third, substantial margin in the calculated leak rate above the detection threshold exists for • all the cases in the main sensitivity matrix. Applying a leak rate margin factor of 10, which has historically been applied in regulatory LBB assessments [35], rather than 4 on the 0.25 gpm detectability limit results in all 13 of the most limiting cases in the main sensitivity matrix satisfying the evaluation criteria with one exception (Case 44c). The 13 most limiting cases are defined here as those cases for which the load margin factor is 1.75 or less at the time the leak rate is calculated to be 1 gpm. Full leak rate and load margin factor curves versus time were developed for these 13 cases (see Figures 7-22 through 7-38). A leak rate margin factor of about 9 does satisfy the evaluation criteria for Case 44c. All other cases in the main matrix very likely satisfy the evaluation criteria with a leak rate margin factor of 10 based on the compiled leak rate and stability data, although this has been verified explicitly for only four of the other cases (12c, 23b, 25a, and 43c). Moreover, the most limiting surge nozzle case (Case 17b) is predicted to have an initial through-wall leak rate of 2.6 gpm, with the leak rate increasing to 69 gpm when the load margin factor decreases to 1.2, indicating robustness with respect to the value of the assumed leak rate margin factor for the surge nozzle cases.

It is concluded that the sensitivity matrix demonstrates sufficient margin to address modeling uncertainties such as those associated with the potential for multiple through-wall crack segments.

7.6.6 Overall Conclusion

The sensitivity matrix robustly addresses the range of nozzle design and fabrication factors, as well as the key modeling uncertainties. Later cases in the sensitivity matrix were defined to further investigate cases showing limiting results. Furthermore, the margins in the matrix results demonstrate that even cases representing an unlikely combination of detrimental factors are likely to result in sufficient time for leak detection prior to rupture. Hence, it is concluded that all 51 subject welds are adequately covered by crack growth sensitivity cases that satisfy the evaluation criteria presented in Section 7.2.
Table 7-1Sensitivity Matrix Case Definitions

				1		Geomet	ry Case								Load C	Case			
							ſ			TW									[
									1	Z-factor									
	1									per						max		1	Pb
Case	Base	Sensitivity	Model	Nozzle	Geometry		Do	t	1	PVP	Pm	р	F _{dw+nt}	Faxial	Pm	F _{dw+n}	Pb	M	(thick)
#	Case	Purpose	Туре	Туре	Configuration	Plants	(in)	(in)	R/t	paper	Case	(ksi)	(kips)	(kips)	(ksi)	(kips)	Case	(in-kips)	(ksi)
⊢–							7 7 6	1 200	2 004			2.025	1.00	45.64	1 74	0.40		000.00	
⊢ <u>¦</u>	-	geometry/load	cylinder	S&R	Config 1a	AEH	7.750	1.290	2.004	1.17	typical	2.235	1.28	45.64	1.74	2.42	high	209.28	5.71
<u></u>		geometry/load	cylinder	S&R		AEH	7.750	1.290	2.004	1.17	турісаі	2.235	1.28	45.64	1.74	2.42	intermed	194.09	5.30
	-	geometry/load	cylinder	S&R	Config Ta	AEH	7.750	1.290	2.004	1.17	турісаі	2.235	-1.28	45.64	1.74	2.42	IOW	178.90	4.88
4	· ·	geometry/load	cylinder	S&R	Config 1b	F	8.000	1.405	1.847	1.17	typical	2.235	7.90	55.19	1.90	15.37	high	237.40	5.74
5		geometry/load	cylinder	S&R	Config 1b	F	8.000	1.405	1.847	1.17	typical	2.235	7.90	55.19	1.90	15.37	low	201.91	4.88
<u> </u>	-	geometry/load	cylinder	S&R	Config 2a/2b	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	high	252.14	7.63
<u> </u>	-	geometry/load	cylinder	S&R	Config 2a/2b	BCG	1.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	łów	158.04	4.78
8		geometry/load	cylinder	S&R	Config 3	DI	8.000	1.405	1.847	1.17	typical	2.235	0.66	47.94	1.65	1.74	high	277.18	6.70
9	· ·	geometry/load	cylinder	S&R	Config 3	DI	8.000	1.405	1.847	1.17	typical	2.235	0.66	47.94	1.65	1./4	łow	201.91	4.88
10		geometry/load	cylinder	spray	Config 4	AE	5.810	0.900	2.228	1.16	typical	2.235	+1.27	26.96	1.94	-0.35	high	12.78	4.89
		geometry/load	cylinder	spray	Config 4	AE	5.810	0.900	2.228	1.16	typical	2.235	-1.2/	26.96	1.94	-0.35	low	66.98	4.50
12		geometry/load	cylinder	spray	Config 5	BCG	5.810	0.780	2.724	1.16	typical	2.235	-0.77	30.94	2.51	0.47	high	65.33	4.75
13	-	geometry/load	cylinder	spray	Config 5	BCG	5.810	0.780	2.124	1.15	typical	2.235	-0.77	30.94	2.51	0.47	low	55.75	4.13
14		geometry/load	cylinder	spray	Config 6	F	8.000	1.150	2.478	1.17	typical	2.235	-0.84	56.19	2.27	-0.84	high	27.91	0.75
15	<u> </u>	geometry/load	cylinder	spray	Config /		5.190	1.045	1.483	1.15	typical	2.235	0.62	17.49	1.29	0.81	nign	35.65	4.65
10		geometry/load	cylinder	spray	Config 7	DI	5.190	1.045	1.483	1.15	typical	2.235	0.62	17.49	1.29	0.81	low	49.47	4.13
	-	geometry/ioad	cylinder	surge	Config 8	AEHBCG	15.000	1.580	3./47	1.19	typical	2.235	1.62	247.70	3.72	8.04	high	2/50.77	13.57
18	-	geometry/load	cylinder	surge	Config 8	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	low	989.57	4.88
19	-	geometry/load	cylinder	surge	Config 9	DI	13.060	1.470	3.442	1.19	high	2.235	4.97	184.75	3.45	4.97	high	2034.30	14.55
20		geometry/load	cylinder	surge	Config 9	DI	13.060	1.470	3.442	1.19	high	2.235	4.97	184.75	3.45	4.97	low	929.97	6.65
21	1	ID repair	cylinder	S&R	Config 1a	AEH	7.750	1.290	2.004	1.1/	typical	2.235	-1.28	45.64	1.74	2.42	high	209.28	5.71
22	3	ID repair	cylinder	S&R	Config 1a	AÉH	7.750	1.290	2.004	1.17	typical	2.235	-1.28	45.64	1.74	2.42	low	178.90	4.88
23	6	ID repair	cylinder	S&R	Config 2a/2b	BCG	7.750	1.065	2.638	1.1/	typical	2.235	-3.01	52.44	2.34	4.98	high	252.14	7.63
24	17	ID repair	cylinder	S&R	Config 2a/2b	BCG	1.750	1.065	2.638	1.1/	typical	2.235	-3.01	52.44	2.34	4.98	low	158.04	4.78
25	1/	ID repair	cylinder	surge	Config 8	AEHBCG	15.000	1.580	3.141	1.19	typical	2.235	1.62	247.70	3.72	8.04	high	2750.77	13.57
20	18	IU repair	cylinder	surge	Conrig 8	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	low	989.57	4.88
21	17	Po sensitivity	cylinder	bound	bounding	AEHBCG	15.000	1.500	3.141	1.19	typical	2.235	1.02	247.70	3.12	8.04	sens i	2035.33	10.00
20	10	Po sensitivity	cylinder	bound	bounding	AEHBCO	15.000	1.500	2 747	1.19	typical	2.235	1.02	247.70	3.12	9.04	sens 2	1410.02	7.00
30	18	PD sensitivity	cylinder	bound	bounding	AEHBCG	15.000	1.500	3.747	1 10	typical	2.235	1.02	247.70	3.72	8.04	sens a	1419.02 817.40	1.00
31	1	as built uncertainty	cylinder	SEP	as-built 1	ALHOUG	8 008	1 419	1 822	1 17	typical	2 2 2 3 5	-1.02	45.64	1 55	2 / 2	bounding	200.28	5.02
32	<u> </u>	as-built uncertainty	cylinder	SER	as-built 2	AEH	7 492	1 161	2 227	1 17	typical	2 2 35	-1.20	45.64	1.00	2 42	bounding	209.20	6.56
33	4	Pm sensitivity	cylinder	S&R	bounding S&R	F	8.000	1.405	1.847	1.17	low	2.235	0.44	47.73	1.64	15.37	bounding	237.40	5.74
34	4	Pm sensitivity	cylinder	S&R	bounding S&R	F	8.000	1.405	1.847	1.17	high	2.235	15.37	62.65	2.15	15.37	bounding	237.40	5.74
35	6	shortened 0.5" "weld"	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
36	6	plastic redistribution	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
37	6	initial crack shape	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
38	6	initial crack shape	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
39	6	initial crack shape	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
40	6	initial crack depth	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
41	6	initial crack depth	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
42	6	CGR K-exponent	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
43	6	CGR K-exponent	cylinder	S&R	bounding S&R	BCG	7.750	1.065	2.638	1.17	typical	2.235	-3.01	52.44	2.34	4.98	bounding	252.14	7.63
44	12	CGR K-exponent	cylinder	spray	bounding spray	BCG	5.810	0.780	2.724	1.16	typical	2.235	-0.77	30.94	2.51	0.47	bounding	65.33	4.75
45	12	CGR K-exponent	cylinder	spray	bounding spray	BCG	5.810	0.780	2.724	1.16	typical	2.235	-0.77	30.94	2.51	0.47	bounding	65.33	4.75
46	17	CGR K-exponent	cylinder	surge	bounding surge	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	bounding	2750.77	13.57
47	17	CGR K-exponent	cylinder	surge	bounding surge	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	bounding	2750.77	13.57
48	17	reduced press. on CF	cylinder	bound	bounding	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	bounding	2750.77	13.57
49	6	no thermal load for TW	cylinder	bound	bounding	BCG	7.750	1.065	2.638	1.17	typical	2.235	-0.33	55.11	2.46	0.17	bounding	31.10	0.94
50	1/	no thermal load for TW	cylinder	bound	bounding	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	0.76	246.84	3./1	5.76	bounding	160.18	0.79
51	19	no thermal load for 1 W	cylinder	bound	bounding	DI	13.060	1.470	3.442	1.19	high	2.235	0.00	1/9.78	3.30	0.00	bounding	126.20	0.90
1 <u>52</u>		detailed geometry	nozzie	S&R	example S&R	ALH	1.806	1.318	1.901	1.1/	typical	2.235	-1.28	45.64	1.70	2.42	bounding	209.28	5.55
C1		offect of multiple flours	nozzie	surge	example surge	AEHBOG	15.000	1.000	2741	1.19	typical	2.235	1.02	241.10	3.12	0.04	bounding	2150.11	13.5/
3	17	affect of multiple flaws	cylinder	surge	Config 8	AEHBOO	15.000	1.300	3.141	1 10	typical	2 225	1.02	247.70	3.12	8.04	nıgn hich	1702.92	13.57
52	17	effect of multiple flave	cylinder	surge	Config 8	AFHROO	15 000	1 580	3.747	1 10	typical	2.235	1.02	247.70	3.72	8.04	high	2750 77	13.40
S4	17	effect of multiple flave	cylinder	surna	Config 8	AFHRCC	15 000	1 580	3 747	1 10	typical	2 225	1.62	247 70	372	8.04	hinh	2750 77	13.57
55	17	effect of multiple flaws	cylinder	surge	Config 8	AFHRCC	15 000	1 580	3 747	1 19	typical	2 235	1.02	247 70	372	8.04	high	2750 77	13.57
56	17	effect of multiple flaws	cylinder	surne	Config 8	AEHBCG	15.000	1.580	3.747	1,19	typical	2.235	1.62	247.70	3.72	8.04	high	2750 77	13.57
\$7	17	effect of multiple flaws	cylinder	surge	Config 8	AEHBCG	15.000	1.580	3.747	1,19	typical	2.235	1.62	247.70	3.72	8.04	hian	2750.77	13.57
S8	19	effect of multiple flaws	cylinder	surge	Config 9	DI	13.060	1.470	3.442	1.19	high	2.235	4.97	184.75	3.45	4.97	high	2034.30	14.55
S9	17	effect of multiple flaws	cylinder	surge	Config 8	AEHBCG	15.000	1.580	3.747	1.19	typical	2.235	1.62	247.70	3.72	8.04	high	2750.77	13.57

Table 7-1 (continued) Sensitivity Matrix Case Definitions

.

	[]		WRS	Case (see Note 1)		CGR	Equation '		Initial Flav	N
	1 1	[]		· · · · ·	· · · · · · · · · · · · · · · · · · ·	T	<u>г</u> ,		i ·	
	(7	(I	l – – – – – – – – – – – – – – – – – – –	i I	í '	(1_ /	()	i l	L I
	1 /	Weld	1	1	More Conservative	K- !	C75th,650*F		í	1 1
Case	Base	Repair ¹	Nominal WRS Case	Conservative WRS Case	WRS Case	Exp.	(in/h; /	1 1	Shape	Depth
#	Case	Case?	("a" case)	("b" case)	("c" case)	n l	psi-in ^{0.5})	2rla	Factor	(%tw)
┝┯┙	ليستيكم	╘╴╴╴╴╴				<u> </u>				
ليل	<u>↓ · · </u>	Axisymm	1a: Type 1 S&R with SS weld	*1b: Type 1 S&R without SS weld	1c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
2	<u> </u>	Axisymm	2a: Type 1 S&R with SS weld	*2b: Type 1 S&R without SS weld	2c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
3	<u> </u>	Axisymm	*3a: Type 1 S&R with SS weld	*3b: Type 1 S&R without SS weld	3c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
4	<u>[</u> !	Axisymm	4a: Type 1 S&R with SS weld	*4b: Type 1 S&R without SS weld	4c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
5	$\Box \cdot \prime$	Axisymm	5a: Type 1 S&R with SS weld	*5b: Type 1 S&R without SS weld	5c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
6	- T	Axisymm	6a: Type 1 S&R with SS weld	*6b: Type 1 S&R without SS weld	6c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
7	L . !	Axisymm	7a: Type 1 S&R with SS weld	*7b: Type 1 S&R without SS weld	7c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
8	<u> </u>	Axisymm	*Ba: Type 1 S&R with SS weld	*8b' Type 1 S&R without SS weld	8c: Mod ASME 3/30 Fit	1.6	8.515E-12	360	uniform	10%
9	<u> </u>	Axisymm	•9a: Type 1 S&R with SS weld	*9h: Type 1 S&R without SS weld	9c Mod ASME 3/30 Fit	1.6	8 515E-12	360	uniform	10%
	<u>⊢ -</u> /	Avisymm	102: Type 1 S&P with SS weld	*10h: Type 1 S&P without SS weld	10e: Mod ASME 3/30 Fit	1.0	9.515E-12	3600	uniform	10%
	<u> </u>	Avieymm	*11a: Tupo 1 S&D with SS wold	"11b: Type 1 Self without SS wold	11a Mod ASME 2/20 Eit	16	0.5152-12	12600	uniform	10%
	<u>↓ · · · ·</u>	Axisymm	+12- Tupo 1 Se D with SS wold	11D: Type 1 S&K Without SS Weiu	TIC: WOU ASWE 3/30 Fit		8.515E-12	1300		10%
12	<u>↓</u> -'	Axisymm	12a: Type I S&R With SS weid	12b: Type T S&R without SS weiu	12C: MOD ASIVE 3/30 FIL	1.0	8.515E-12	360	unirorm	10%
13	<u> - '</u>	Axisymn	*13a: Type 1 S&R with SS weld	*13b: Type 1 S&R without SS weig	13c: Mod ASME 3/30 Fit	1.0	8.515E-12	360		10%
14	<u>↓ - '</u>	Axisymm	14a: Type 1 S&R with SS weld	*14b: Type 1 S&R without SS weld	14c: Mod ASME 3/30 Fit	1.6	8.515E-12	360-1	uniform	10%
15	L - '	Axisymm	15a: Type 1 S&R with SS weld	15b: Type 1 S&R without SS weld	15c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°/	uniform	10%
16	<u> - '</u>	Axisymm	*16a: Type 1 S&R with SS weld	*16b: Type 1 S&R without SS weld	16c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
17	- '	Axisymm	17a: Type 8 surge with SS weld	17b: Type 8 surge without SS weld		1.6	8.515E-12	21	natural	26%
18	- 1	Axisymm	18a: Type 8 surge with SS weld	18b: Type 8 surge without SS weld		1.6	8.515E-12	360°	uniform	10%
19		Axisymm	19a Type 9 surge	19b: Type 8 surge with SS weld	·/	1.6	8.515E-12	21	natural	26%
20	<u>⊢</u> /	Avisymm	*20a* Type 9 surge	20h: Type 8 surge with SS weld	<u> </u>	16	8 515E-12	360	uniform	10%
20	+	D Dopair	21a: SED 20° ID rapair / wo SS weld	200: Type o surge with 35 weit	<u> </u>	16	0.0100-12	1300	uniform	10%
21	+	ID Repair	21a: Sork 20 1D repair / wo 55 weiu	· · · · · · · · · · · · · · · · · · ·		1.0	8.5150-12	1300		1070
22		10 Repair	22a: S&R 20" ID repair / wo SS werd		<u> </u>	1.0	8.515E-12	360	uniform	10%
23	10	ID Repair	23a: S&R 20" ID repair / wo SS weid	23b: S&R 20° ID repair / mod ASME	23c: 23a with 3 repairs	1.6	8.515E-12	360-1	uniform	10%
24	7	ID Repair	24a: S&R 20° ID repair / wo SS weld	ľ <u></u> /		1.6	8.515E-12	360°	uniform	10%
25	17	ID Repair	25a: surge ID repair / with SS weld	25b: surge ID repair / w/o SS weld	·	1.6	8.515E-12	21	natural	26%
26	18	ID Repair	26a: surge ID repair / with SS weld	[]		1.6	8.515E-12	360°	uniform	10%
27	17	Axisymm		27b: Type 8 surge without SS weld		1.6	8.515E-12	21	natural	26%
28	17	Axisymm		28b: Type 8 surge without SS weld	· · · · · · · · · · · · · · · · · · ·	1.6	8.515E-12	21	natural	26%
29	18	Axisymm		29h: Type 8 surge without SS weld		1.6	8.515E-12	360°	uniform	10%
30	18	Axisymm		30b. Type 8 surge without SS weld	<u></u>	16	8 515F-12	360	uniform	10%
31	+		*31a: Type 1 S&P with SS weld	131b: Type 1 S&P without SS weld	210 Mod ASME 3/30 Fit	16	8 515E-12	3600	uniform	10%
32	┝╌┷	Avicumm	122a. Tupo 1 S&D with SS wold	Alob. Type 1 Sark Without SS were	31C: WOU ASWIE 3/30 Fit	1.0	0.515E-12	300	uniform	10%
32	<u>⊢</u> ,'	Axisymm	328: Type I S&K With SS weid	32D: Type T S&R Without SS weid	32C: MOD ASINE 3/30 FR		8.515E-12	300		1070
33	4	Axisymn	33a: Type I S&R With SS weid	33b: Type 1 S&R without SS weig	33C: MOD ASME 3/30 FIL	1.0 1	8.515E-12	360	uniform	10%
34	4	Axisymm	*34a: Type 1 S&R with SS weld	'34b: Type 1 S&R without SS weld	34c: Mod ASME 3/30 Fit	1.6	8.515E-12	360.)	uniform	10%
35	6	Axisymm		L'	35c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
36	6	Axisymm	<u> </u>		36c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°/	uniform	10%
37	6	Axisymm			37c: Mod ASME 3/30 Fit	1.6	8.515E-12	21	natural	26%
38	6	Axisymm		[· · · · · · · · · · · · · · · · · · ·	38c: Mod ASME 3/30 Fit	1.6	8.515E-12	21	semi-ellipse	26%
39	6	Axisymm	[······	· · · · · · · · · · · · · · · · · · ·	39c: Mod ASME 3/30 Fit	1.6	8.515E-12	21	constant	26%
40	6	Axisymm		<u></u>	40c: Mod ASME 3/30 Fit	1.6	8.515E-12	21	natural	15%
41	6	Axisymm		<u> </u>	41c: Mod ASME 3/30 Fit	16	8 515E-12	1-21	natural	40%
12		Avisymm	122 Type 1 S&P with SS weld	*42b: Type 1 SP B without SS weld	470, Mod ASME 3/30 Fit	10	4 213E-00	2600	uniform	10%
42		Avisymm	#2d. type i Sork with SS weid	42D: Type 1 Sork Without SS werd	42C: WOU ASWE 3/30 Fit	1.0	4.313E-05	300	uniform	10%
43	12	Axisymm	438: Type 1 Sork Will 55 Weiu	43D: Type 1 S&R without 55 weid	43C: MOD ASIVE 3/30 FIL	144	1.530E-14	300		1070
44	<u> </u>	Axisymin	44a: Type I S&K With SS weid	144b: Type 1 S&R without SS weid	44C: MOD ASME 3/30 FIL		4.313E-09	360		10%
45		Axisymn	45a: Type 1 S&R with SS weld	*45b: Type 1 S&R without SS weid	45c: Mod ASME 3/30 Fit	22	1.530E-14	360	uniform	10%
46	17	Axisymm		46b: Type 8 surge without SS weld		1.0	4.313E-09	21	natural	26%
47	17 '	Axisymm	· · · · · · · · · · · · · · · · · · ·	47b: Type 8 surge without SS weld		2.2	1.530E-14	21	natural	26%
48	17	Axisymm	L	48b: Type 8 surge without SS weld		1.6	8.515E-12	21_/	natural	26%
49	6	Axisymm		,	49c: Mod ASME 3/30 Fit	1.6	8.515E-12	360°	uniform	10%
50	17	Axisymm	,	50b: Type 8 surge without SS weld		1.6	8.515E-12	21	natural	26%
51	19	Axisymm		51b. Type 8 surge with SS weld		1.6	8 515E-12	21	natural	26%
52	1 1	Axisymm	·······	52d: Type 1 S&R w/o SS weld (Interpolated)	52c Mod ASME 3/30 Fit	1.6	8 515F-12	360°	uniform	10%
53	17	Avisymm		520. Type 9 surge without SS weld	JZC. HIGH HOHIE GROOT A	16	0 615E.12	1 21	natural	26%
<u> </u>	+++-	Avisymm	Star Tupo 9 surges with SS wold	53D: Type o surge without 55 weid	<u></u>	1.0	0.313E+12	12500	uniform	100/
51	<u>⊢</u> ;;/	Axisymin	Sta: Type o surge with 55 weith	SID: Type 8 surge without 55 weid	<u>{</u>	무운	8.515E-12	300		1070
22	<u> <u> </u></u>	Axisymin	<u>↓</u>	S2b: Type 8 surge without S5 weig			8.515E-12	360	uniform	10%
53	1/	Axisymm	· · · · · · · · · · · · · · · · · · ·	S3b: Type 8 surge without SS weld	L	1.6	8.515E-12	5.6	naturai	10%
<u>S4</u>	17	Axisymm		S4b: Type 8 surge without SS weld	<u> </u>	1.6	8.515E-12	Com	oine 17b +	S3b #1
S5	17	Axisymm		S5b: Type 8 surge without SS weld		1.6	8.515E-12	Com	bine 17b +	S3b #2
S6	17	Axisymm	[S6b: Type 8 surge without SS weld		1.6	8.515E-12	Com'	bine 17b +	S3b #3
S7	17	Axisymm	· · · · · · · · · · · · · · · · · · ·	S7b: Type 8 surge without SS weld		1.6	8.515E-12	Com	bine 17b +	95%tw
S8	19	Axisymm		S8b: Type 8 surge with SS weld	<u></u>	1.6	8.515E-12	360°	uniform	T 10%
59	17	Axisymm		S9b: Type 8 surge without SS weld	······ ;	1.6	8.515E-12	2 Ca	se 17b 21;	1 flaws

Notes

(1) Asterisk before case number indicates stable crack arrest verified using axisymmetric crack growth solution for uniform depth 360° crack.

.

					Lo	ads		
			P	m	F	b	P _b /(P	$_{m}+P_{b})$
Trme	Desim	# of	(k	si)	(k	si)		-
Туре	Design	nozzles	Min	Max	Min	Max	Min	Max
	la	12	3.17	3.45	0.07	5.71	0.02	0.64
Safety	1b	4	3.20	3.71	0.78	5.74	0.20	0.63
and Relief	2a	8	3.93	4.29	1.04	7.63	0.21	0.64
Nozzles	2b	4	3.57	3.90	2.35	4.78	0.38	0.57
	3	7	3.16	3.24	0.00	6.70	0.00	0.67
	4	2	3.45	3.58	1.38	4.89	0.28	0.59
Spray	5	3	4.00	4.20	1.12	4.75	0.21	0.54
Nozzles	6	1	3.84	3.84	0.75	0.75	0.16	0.16
	7	2	2.76	3.05	1.16	4.80	0.30	0.61
Surge	8	6	5.24	5.43	4.04	13.58	0.43	0.72
Nozzles	9	2	4.92	5.06	6.65	14.55	0.57	0.74

Table 7-2Geometry and Load Combination for 51 Subject Welds

Note:

Pm in this table is based on ASME pressure stress pD/4t, plus dead weight and normal thermal axial loads divided by metal cross sectional area.

Table 7-3

Summary Statistics for Wolf Creek Pressurizer Surge Nozzle DM Weld Indications Reported in October 2006

			ี []	2				ΰ	<u>.</u>	Circ	,:		Individual	_	Flaw Area		PUDIVIDU	
	Max.	Depth	Pos	ition	Len	ngth	anoth	Pos	ition	Exte	nt		Flaw Lengt	hs	(Note 1)		Flaw Area	S
			Start	Stop	uo	uo	to-Depth					Total ID	Total % of	Ind#1% of		Total	Total % of	Ind#1% of
Assumed			on OD	on OD	QO	₽	Aspect	Start	Stop		_	Lengths	Envelope	Envelope		Areas	Envelope	Envelope
Flaw	(%tw)	(in)	(in)	(in)	(in)	(in)	Ratio	(%Circ)	(%Circ)	(%Circ)	(deg)	(ii)	Length	Length	(in ²) (%wa	() (%wall)	Area	Area
Indication #1	10%	0.145	43.0	44.0	1.0	0.81	5.6	91.5%	93.6%	2.1%	1.7	r			0.12 0.195	. 9		
Indication #2	25%	0.363	28.75	31.5	2.75	2.22	6.1	61.2%	67.0%	5.9%	21.1				0.83 1.3%			
Indication #3	31%	0.450	20.5	25.5	5.0	4.03	9.0	43.6%	54.3%	10.6%	38.3				1.88 3.1%			
Envelope 2&3	31%	0.450	20.5	31.5	11.0	8.87	19.7	43.6%	67.0%	23.4%	84.3	6.25	70.5%		4.13 6.7%	4.4%	65.5%	
Envelope 1,2&3	31%	0.450	20.5	44.0	23.5	18.94	42.1	43.6%	93.6%	50.0%	180.0	7.05	37.2%	4.3%	8.83 14.49	6 4.6%	32.0%	1.3%

47.0	14.96	1.45	12.06	0.806	61.54
Weld OD Circumference (in)	OD (in)	Weld Thickness, t (in)	(II) (II)	ID/OD	Cross Sectional Area (in ²)

Notes: (1) Constant depth shape assumed for flaw area calculations.

Table 7-4 Sensitivity Matrix Case Surface Crack Results

			Geometry Ca	se		Surface	Crack Stabi	lity Results	(Press + D)	N + NT loa	ds and Z∙fa	ctor for Crit	ical Size)
	ase					Time	Fraction	Crack	Max tot	Max Pm	Stability	Support.	Support.
Case	Pc:	Nozzle	Geometry	Ri	t	to TW	Xsection	Face	Faxial	Based on	Margin	Pm	Pb (thick)
#	Su VI	Туре	Configuration	(in)	(in)	(yrs)	Cracked	F (kips)	(kips)	CF (ksi)	Factor	(ksi)	(ksi)
1	C	S&R	Config 1a	2.585	1.290	17.4	0.400	23.40	72.74	2.78	3.10	8.6	17.7
2	С	S&R	Config 1a	2.585	1.290	21.3	0.395	23.12	72.45	2.77	3.33	9.2	17.6
3	С	S&R	Config 1a	2.585	1.290	26.3	0.383	22.43	71.77	2.74	3.67	10.1	17.9
4	С	S&R	Config 1b	2.595	1.405	18.0	0.400	26.04	88.68	3.05	2.95	9.0	16.9
5	С	S&R	Config 1b	2.595	1.405	25.7	0.381	24.79	87.44	3.00	3.51	10.6	17.2
6	С	S&R	Config 2a/2b	2.810	1.065	3.4	0.435	21.74	82.16	3.67	2.04	7.5	15.6
7	C	S&R	Config 2a/2b	2.810	1.065	10.5	0.440	22.01	82.43	3.69	2.63	9.7	12.6
8	С	S&R	Config 3	2.595	1.405	13.4	0.399	25.94	74.96	2.58	2.87	7.4	19.2
9	C	S&R	Config 3	2.595	1.405	32.2	0.364	23.69	72.71	2.50	4.12	10.3	20.1
10	с	spray	Contig 4	2.005	0.900	21.2	0.389	12.06	39.94	2.88	3.57	10.3	17.4
11	C	spray	Config 4	2.005	0.900	25.3	0.378	11.71	39.59	2.85	3.95	11.3	17.8
12	c	spray	Config 5	2.125	0.780	10.5	0.435	11.76	44.18	3.58	2.70	9.9	13.1
13	C	spray	Config 5	2.125	1 150	13.0	0.427	11.70	43.94	3.50	3.05	10.9	12.0
14	C C	spray	Config 7	1 550	1.150				Arr	rost			
15		spidy	Config 7	1.550	1.045				Arr	ost			
10		surge	Config 8	5 920	1.043								
17	h	surge	Config 8	5 920	1.500	12	0.240	35.80	289.91	4 35	1 73	75	23.4
18	a	surne	Config 8	5.920	1.580	1.6	0.270	55.00	Δrr	est	1.15	1	
18	h	surge	Config 8	5.920	1,580	11.5	0,499	74.22	328.34	4,93	2.05	10.1	10.0
19	b	surae	Config 9	5.060	1.470		·		Arr	est			
20	b	surae	Config 9	5.060	1.470	-			Arr	est			
21	a	S&R	Config 1a	2.585	1.290	0.6	0.212	12.41	61.75	2.36	5.08	12.0	29.0
22	a	S&R	Config 1a	2.585	1.290	0.6	0.213	12.44	61.78	2.36	5.58	13.2	27.2
23	а	S&R	Config 2a/2b	2.810	1.065	0.4	0.208	10.40	70.82	3.17	3.79	12.0	28.9
23	b	S&R	Config 2a/2b	2.810	1.065	0.4	0.275	13.74	74.16	3.32	3.37	11.2	25.7
23	С	S&R	Config 2a/2b	2.810	1.065	0.5	0.298	14.91	75.33	3.37	3.55	12.0	27.1
24	а	S&R	Config 2a/2b	2.810	1.065	0.5	0.210	10.49	70.91	3.17	6.09	19.3	29.1
25	а	surge	Config 8	5.920	1.580	0.8	0.173	25.73	279.84	4.20	2.13	9.0	28.9
25	b	surge	Config 8	5.920	1.580	0.5	0.183	27.21	281.33	4.22	2.07	8.7	28.0
26	a	surge	Config 8	5.920	1.580	2.2	0.359	53.51	307.62	4.62	2.88	13.3	14.1
27	Ь	surge	bounding	5.920	1.580	1.3	0.243	36.20	290.32	4.36	1.76	7.7	22.9
28	Ь	surge	bounding	5.920	1.580	2.0	0.271	40.31	294.42	4.42	1.92	8.5	19.2
29	D	surge	bounding	5.920	1.580	1.1	0.527	78.39	332.50	4.99	1.47	1.3	10.3
30	D	surge	bounding	5.920	1.580	25.2	0.260	24.22	AII	250	2.07	10.0	20.0
31	C C	S&R	as-puilt 2	2.585	1.419	35.2	0.369	24.22	73.55	2.50	2.597	7.0	20.0
32		S&D	bounding S&P	2.505	1.101	19.8	0.417	25.22	87.87	3.07	2.30	9.4	17.8
34	C C	S&R	bounding S&R	2 595	1 405	14.6	0.300	26.50	89.15	3.02	2.86	88	16.4
35	C C	SER	bounding S&R	2 810	1.405	29	0.407	22 33	82 75	3 70	1.00	72	14.8
36	c	S&R	bounding S&R	2 810	1.005	3.6	0.434	21.69	82.11	3.67	2 05	7.5	15.6
37	c	S&R	bounding S&R	2.810	1.065	3.4	0.332	16.59	77.01	3.44	2.32	8.0	17.7
38	c	S&R	bounding S&R	2.810	1.065	3.4	0.331	16.56	76.98	3.44	2.32	8.0	17.7
39	с	S&R	bounding S&R	2.810	1.065	3.4	0.340	16.99	77.41	3.46	2.29	7.9	17.4
40	С	S&R	bounding S&R	2.810	1.065	3.9	0.308	15.38	75.80	3.39	2.44	8.3	18.6
_ 41	С	S&R	bounding S&R	2.810	1.065	2.6	0.357	17.83	78.25	3.50	2.22	7.8	17.0
42	С	S&R	bounding S&R	2.810	1.065	1.8	0.476	23.79	84.21	3.77	1.68	6.3	12.8
43	C	S&R	bounding S&R	2.810	1.065	7.6	0.408	20.41	80.83	3.61	2.27	8.2	17.3
44	С	spray	bounding spray	2.125	0.780	2.9	0.470	12.94	45.11	3.66	2.34	8.6	11.1
45	С	spray	bounding spray	2.125	0.780	48.1	0.417	11.50	43.67	3.54	2.97	10.5	14.1
46	b	surge	bounding surge	5.920	1.580	1.1	0.236	35.14	289.26	4.34	1.74	7.5	23.6
47	b	surge	bounding surge	5.920	1.580	1.5	0.247	36.77	290.88	4.37	1.71	7.5	23.2
48	Þ	surge	bounding	5.920	1.580	1.2	0.240	35.80	289.91	4.35	1.73	1.5	23.4
49	C	S&R	bounding	2.810	1.065	3.4	0.435	21.74	//.35	3.46	3.96	13.7	3.1
50		surge	bounding	5.920	1.580	1.2	0.240	35.80	287.63	4.3Z	4.37	1 18.9	3.5
51		surge	Dounding	3.060	1.4/0	11.0	0.422	25.24	Arr	251	2 00	00	10.0
52	с - Л	Ser	example S&R	2.303	1 210	11.0	0.422	25.34	/4.00	2.78	2.00	1 0.0	0.0
52	L L	SULLOP	example Ser	5 020	1.510	11	0 244	36.33	290 45	631	1 70	7 4	22.1
\$1	2	Surge	Config 8	5 920	1 580	1.1	0.244	L 30.33	<u>Σ30.45</u> Δri	est	1.70	1.4	<u> </u>
51	h	surne	Config 8	5.920	1.580	1.2	0.489	72.76	326.88	4,91	1.08	5.3	14.6
S2	b	surae	Config 8	5.920	1.580	3.4	0.518	77.12	331.23	4.97	1.37	6.8	11.5
S3	b	surae	Confia 8	5.920	1.580	2.2	0.179	26.63	280.74	4.21	2.10	8.8	28.4
S4	b	surge	Config 8	5.920	1.580			· · · · · ·	N	/A			
S5	b	surge	Config 8	5.920	1.580				N	/A			
S6	b	surge	Config 8	5.920	1.580				N	/A ·			
<u>S7</u>	b	surge	Config 8	5.920	1.580				N	/A			
S8	b	surge	Config 9	5.060	1.470				Arr	est			
S9	b	surge	Config 8	15.920	1.580				N	/A			

Table 7-5 Sensitivity Matrix Case Through-Wall Crack Results at 1 gpm or Initial Leak Rate if Higher

		Crack								
	Fraction	Face	Max tot	Max Pm	Support.	Support.	Stability	Time	Time	Leak Rate
Case and	Xsection	Force	Faxial	Based on	Pm	Pb (thick)	Margin	since TW	since TW	(apm @
Step	Cracked	(kips)	(kips)	CF (ksi)	(ksi)	(ksi)	Factor	(hrs)	(days)	70°F)
010513	0.466	27.27	76.61	2 93	6.55	12.78	2.24	2726	114	1.04
02cS14	0.100	27.48	76.82	2.00	6.79	12.70	2 31	3416	14	1.04
03cS15	0.472	27.59	76.02	2.00	7.04	11.70	2.31	4358	192	1.03
04cS12	0.472	30.06	92.71	2.34	6.05	12.52	2.40	4550	102	1.07
050514	0.402	30.00	02.05	2 10	7.50	11.52	2.10	2307	107	1.00
060513	0.400	23 53	92.95	2.19	6.27	12.05	2.35	4320	100	1.00
076521	0.471	23.55	84.05	3.75	7.64	12.95	1.70	152	31	1.04
090512	0.451	24.55	79.01	3.60	5.70	9.02	2.01	1062	70	1.02
000512	0.439	29.00	70.91	2.71	5.79	14.32	2.14	2208	94	1.09
100520	0.470	30.30	/9.50	2.73	6.84	10.12	2.50	5489	229	1.08
1100320	0.497	15.42	43.30	3.12	6.40	10.13	2.07	4690	195	1.01
120517	0.506	13.69	43.57	3.14	6.54	9.38	2.08	6251	260	1.04
120517	0.507	13.90	40.13	3.74	0.95	8.82	1.86	2639	110	1.03
140500	0.512	14.10	46.28	3.75	1.29	8.03	1.94	3120	130	1.03
140511					Afre	est				
15cSna					Arre	est				
16cSna					Arre	est		-		
1/aSna					Arre	est				
1/0500	0.243	36.18	290.30	4.36	1.44	23.17	1.71	0	0	2.55
18aSna	0.500	77 ***			Arre	est				
180500	0.523	//.93	332.04	4.98	8.94	8.75	1.79	0	0	2.71
19bSna					Arre	est				
20bSna		· · ·			Arre	est				
21aS16	0.255	14.95	64.28	2.46	10.86	25.26	4.42	1762	73	1.02
22aS17	0.260	15.23	64.57	2.47	11.78	23.31	4.78	1894	79	1.06
23aS13	0.248	12.38	72.80	3.26	10.92	25.59	3.36	1194	50	1.01
23bS02	0.311	15.55	75.98	3.40	10.13	22.75	2.98	194	8	1.06
23cS16	0.369	18.44	78.87	3.53	10.53	22.76	2.99	1799	75	1.00
24aS15	0.255	12.75	73.17	3.27	13.86	20.25	4.24	1607	67	1.03
25aS00	0.175	25.99	280.10	4.20	8.92	28.78	2.12	0	0	5.28
25bS00	0.185	27.47	281.58	4.23	8.68	27.88	2.05	0	0	6.03
_26aS00	0.364	54.17	308.29	4.63	13.12	13.84	2.83	0	0	1.18
27bS00	0.246	36.58	290.69	4.36	7.61	22.68	1.74	0	0	2.50
28bS00	0.355	52.84	306.96	4.61	7.71	16.74	1.67	0	0	2.43
29bS00	0.537	79.95	334.07	5.02	6.91	9.65	1.38	0	0	4.05
30bSna					Arre	est				
31cS16	0.471	30.90	80.23	2.73	6.73	12.37	2.46	5656	236	1.06
32cS11	0.471	24.32	73.66	3.19	6.26	12.86	1.96	1847	77	1.02
33cS13	0.460	29.94	92.59	3.18	6.98	12.60	2.20	3374	141	1.00
34cS12	0.468	30.45	93.09	3.20	6.77	12.16	2.12	2346	98	1.06
35cS06	0.480	23.98	84.40	3.77	6.13	12.38	1.62	617	26	1.10
36cS08	0.471	23.56	83.98	3.75	6.35	12.89	1.69	857	36	1.05
37cS19	0.419	20.96	81.38	3.64	6.67	13.98	1.83	1024	43	1.01
38cS19	0.420	21.02	81.44	3.64	6.67	13.98	1.83	1035	43	1.01
39cS19	0.424	21.22	81.64	3.65	6.62	13.82	1.81	993	41	1.03
40cS22	0.410	20.47	80.89	3.62	6.82	14.39	1.89	1151	48	1.01
41cS18	0.434	21.68	82.10	3.67	6.51	13.53	1.77	957	40	1.03
42cS00	0.487	24.36	84.79	3.79	5.96	12.00	1.57	0	0	1.07
43cS09	0.452	22.58	83.00	3.71	6.82	14.01	1.84	1035	43	1.00
44cS09	0.528	14.55	46.72	3.79	6.41	8.04	1.69	1228	51	1.01
45cS19	0.501	13.81	45.98	3.73	7.14	9.10	1.91	3284	137	1.06
46bS00	0.240	35.69	289.80	4.35	7.45	23.25	1.71	0	0	4.63
47bS00	0.248	36.95	291.07	4.37	7.42	23.03	1.70	0	0	1.38
48bS00	0.243	21.53	275.65	4.14	7.18	23.54	1.73	0	0	2.42
49cS30	0.502	25.10	80.71	3.61	10.30	2.68	2.85	4004	167	1.01
50bS00	0.243	36.19	288.03	4.32	18.70	3.42	4.33	0	0	1.07
51bSna					Arre	est		·		· · · ·
52cS10	0.470	28.22	77.55	2.89	6.51	12.52	2.26	1658	69	1.00
52dSna					Алте	est				
53bS00	0.246	36.68	290.80	4.37	7.36	22.88	1.69	0	0	2,39
S1aSna					Arre	est		1		4.00
S1bS00	0.496	73.89	328.00	4,92	5.08	14.01	1.03	0	0	7.39
S2bS00	0.529	78.83	332.95	5.00	6.38	10.72	1.28	0	õ	4 87
S3bS00	0,188	28.04	282.15	4,24	8.61	27.58	2.03	n i	0	2 43
S4bSna*	0.400	59.53	313 64	4.71	6.75	19.44	1 43	167	7	2.55
S5bSna*	0.400	59.53	313.64	4,71	6.95	20.02	1 48	167	7	2.55
S6bSna*	0.400	59.53	313.64	4 71	6 10	17 57	1 20	167	7	2.00
S7bSna*	0.453	67.50	321 61	4.83	6 95	19.52	1 44	167	, 7	2.55
S8hSna					Δ				,	2.00
59h500	0 322	47 95	302.06	4 5 2	7 24	21 65	1.60	0	0	255
- 399300	U.JLL	-1.JJ	JU2.00	4.00	1.24	CO.12	1.00	U	U	2.33

*Stability results after 7 days of detectable leakage for these multiple flaw cases only (S4b through S7b)

Table 7-6			•		
Sensitivity	/ Matrix Case	Through-Wall	Crack Results	at Load Mar	gin Factor of 1.2

r · · · · · · · · · · · · · · · · · · ·		Crack		Max Pm			1		Time	Time	Time	leak
	Fraction	Face	Max tot	Based	Sunnort	Support	Stability	Time	since	since 1	since 1	Rate
Case and	Xsection	Force	Faxial	on CF	Pm	Pb (thick)	Marnin	since TW	TW	anm	anm	(apm @
Sten	Cracked	(kins)	(kins)	(ksi)	(ksi)	(ksi)	Factor	(hrs)	(days)	(hrs)	(davs)	70°F)
01.626	Ordered	22.21	0255	2.15	2.00	6.00	1 21	E 250	(00)3)	1622	100	5.01
010336	0.506	33.21	02.33	3.15	3.80	6.89	1.21	5350	223	2023	109	5.81
020537	0.574	33.01	82.95	3.17	3.85	0.43	1.21	7267	201	2839	118	5.89
030538	0.580	33,93	83.26	3.18	3.88	5.95	1.22	1357	307	2998	125	0.22
040534	0.558	30.29	98.94	3.40	4.19	7.07	1.23	5252	219	2085	112	5.22
050537	0.574	37.36	100.01	3.44	4.15	5.90	1.21	/615	317	3288	137	5.81
060541	0.529	26.45	86.87	3.88	4.70	9.23	1.21	1741	/3	989	41	4.04
076562	0.573	28.64	89.06	3.98	4.79	5.75	1.20	3389	141	1706	/1	5.44
086534	0.553	36.00	85.03	2.92	3.58	8.21	1.23	4643	193	2375	99	5.58
096541	0.586	38.10	87.13	2.99	3.63	5.93	1.21	8942	3/3	3453	144	6.56
10cS38	0.582	18.05	45.92	3.31	3.98	5.89	1.20	6450	269	1/60	73	3.80
11cS39	0.587	18.21	46.09	3.32	4.09	5.54	1.23	7996	333	1/45	/3	3.70
12cS33	0.575	15.83	48.00	3.89	4.66	5.69	1.20	3801	158	1163	48	3.54
13cS34	0.582	16.04	48.21	3.91	4.83	5.10	1.23	4414	184	1295	54	3.49
14cSna						Arre	est					
15cSna						Arre	est					
16cSna						Arre	est					
17aSna						Arre	est		-	-		
17bS73	0.331	49.30	303.42	4.55	5.45	16.24	1.20	829	35	829	35	69.28
18aSna			F			Arre	est					
18bS21	0.591	88.03	342.15	5.14	6.15	5.84	1.20	1022	43	1022	43	15.79
19bS32						Arre	est					
20bSna						Arre	est					
21aS20	0.270	15.78	65.12	2.49	10.47	24.04	4.21	2272	95	509	>>21	1.28
22aS20	0.271	15.84	65.18	2.49	11.46	22.47	4.60	2295	96	400	>>17	1.25
23aS21	0.278	13.91	74.34	3.32	10.05	23.06	3.02	2085	87	891	>>37	1.67
23bS33	0.517	25.84	86.26	3.86	4.64	9.18	1.20	4354	181	4160	173	6.44
23c\$20	0.387	19.34	79.76	3.57	10.08	21.57	2.83	2296	96	497	>>21	1.27
24aS19	0.270	13.48	73.90	3.30	13.31	19.26	4.03	2115	88	508	>>21	1.31
25aS75	0.330	49.10	303.22	4.55	5.49	16.36	1.21	1868	78	1868	78	98.51
25bS79	0.329	49.04	303.15	4.55	5.49	16.37	1.21	1642	68	1642	68	91.86
26aS09	0.383	57.09	311.21	4.67	12.24	12.79	2.62	958	40	958	>>40	5.40
27bS68	0.337	50.12	304.24	4.57	5.50	15.64	1.20	919	38	919	38	70.43
28bS30	0.424	63.08	317.20	4.76	5.71	12.00	1.20	655	27	655	27	28.75
29bS08	0.560	83.38	337.50	5.07	6.07	8.38	1.20	267	11	267	11	8.49
30bSna						Arre	est					
31cS40	0.588	38.59	87.92	2.99	3.58	6.00	1.20	9163	382	3507	146	6.43
32cS31	0.552	28.50	77.84	3.37	4.07	7.91	1.21	3616	151	1769	74	4.80
33cS35	0.560	36.46	99.10	3.40	4.11	6.94	1.21	6338	264	2964	123	5.27
34cS34	0.561	36.51	99.16	3.41	4.11	6.93	1.21	4709	196	2363	98	5.52
35cS18	0.528	26.38	86.80	3.88	4.76	9.35	1.23	1393	58	776	32	3.67
36cS24	0.529	26.43	86.86	3.88	4.70	9.24	1.21	1870	78	1013	42	3.99
37cS57	0.503	25.16	85.58	3.83	4.58	9.14	1.20	2193	91	1170	49	4.97
38cS56	0.504	25.21	85.63	3.83	4.58	9.12	1.20	2210	92	1175	49	4.98
39cS55	0.504	25.22	85.64	3.83	4.60	9.16	1.20	2117	88	1124	47	4.87
40cS63	0.501	25.05	85.47	3.82	4.59	9.16	1.20	2424	101	1273	53	5.18
41cS52	0.508	25.39	85.81	3.84	4.60	9.14	1.20	2009	84	1052	44	4.70
42cS15	0.534	26.71	87.13	3.90	4.66	9.12	1.20	927	39	927	39	2.97
43cS30	0.525	26.26	86.68	3.88	4.68	9.21	1.21	2171	90	1135	47	4.84
44cS18	0.581	16.01	48.18	3.91	4.80	5.84	1.23	2125	89	898	37	2.64
45cS37	0.573	15.78	47.95	3.89	4.69	5.73	1.21	4397	183	1113	46	3.86
46bS44	0.330	49.07	303.18	4.55	5.48	16.33	1.20	1755	73	1755	73	73.58
47bS85	0.331	49.25	303.37	4.55	5.48	16.32	1.20	534	22	534	22	63.34
48bS76	0.335	29.71	283.82	4.26	5.12	16.32	1.20	941	39	941	39	70.05
49cS86	0.628	31.37	86.98	3.89	4.67	1.13	1.20	7474	311	3470	145	8.57
50bS150	0.492	73.20	325.04	4.88	6.14	0.99	1.26	7034	293	7034	293	191.43
51bSna						Arre	est					
52cS35	0.567	34.07	83.40	3.10	3.84	6.87	1.24	3916	163	2257	94	6.61
52dSna						Ап	est					
53bS103	0.331	49.29	303.41	4.55	5.46	16.26	1.20	1164	49	1164	49	42.35
S1aSna						Arre	est					
S1bSna		Not Applica	ble @	W Load	actor = 1.	08 (1.03 at	first leaka	ige) / 2 day	s from TW	to load fa	ctor of 1.0	
S2bS01	0.537	79.90	334.01	5.01	6.14	10.28	1.22	82	3 (Note 1)	82	3 (Note 1)	6.00
S3bS93	0.330	49.16	303.27	4.55	5.47	16.30	1.20	1772	74	1772	74	87.49
S4bSna												
S5bSna						Not Apr	licable					
S6bSna						HOL APP	meable					
S7bSna											_	
S8bSna						Arre	est					
CObCas	0.415	61.74	215 06	1 71	5 17	14.91	1 00	020	35 (Noto 2)	020	25 (Mate 2)	60.00

Note 1: Case S2b showed 4 days from initial leakage (at 4.9 gpm) until load margin factor of 1.20 based on interpolation. Note 2: Case S9b showed 29 days from initial leakage (at 2.6 gpm) until load margin factor of 1.20 based on interpolation.

i

					Result Cr	omnarison		
9567 9			Time Interval a Stability Ma 1.2 I	from 1 gpm to argin Factor of davsl	Stability Mar 1 gpm (or at i if hic	gin Factor at nitial leak rate	Calculated (at 70°F) a Margin Factu	Leak Rate It a Stability or of 1.2 foom
Gualitative Sensitivity [Description	Quantitative Sensitivity Description	from	to	from	to	from	to
1c Case 1c with intermediate I	pending moment	Pb from 5.71 ksi to 5.30 ksi	109	118	2.24	2.31	5.81	5.89
1c Case 1c with low bend	ing moment	Pb from 5.71 ksi to 4.88 ksi	109	125	2.24	2.40	5.81	6.22
tc Case 4c with low bend	ing moment	Pb from 5.74 ksi to 4.88 ksi	112	137	2.18	2.35	5.22	5.81
3c Case 6c with low benc	ling moment	Pb from 7.63 ksi to 4.78 ksi	41	11	1.70	2.01	4.04	5.44
3c Case 8c with low benc	ling moment	Pb from 6.70 ksi to 4.88 ksi	66	144	2.14	2.50	5.58	6.56
0c Case 10c with low ben	ding moment	Pb from 4.89 ksi to 4.50 ksi	73	73	2.07	2.08	3.81	3.70
2c Case 12c with low bene	ding moment	Pb from 4.75 ksi to 4.13 ksi	48	54	1.86	1.94	3.54	3.49
5c Case 15c with low ben	ding moment	Pb from 4.65 ksi to 4.13 ksi	arrest	arrest	arrest	arrest	arrest	arrest
7a Case 17a with shifted weld	d residual stress	WRS from wi SS weld to wio SS weld	arrest	35	arrest	1.71	arrest	69.28
7a Case 17a with low ben	ding moment	Pb from 13.57 ksi to 4.88 ksi	arrest	arrest	arrest	arrest	arrest	arrest
7b Case 17b with low ber	iding moment	Pb from 13.57 ksi to 4.88 ksi	35	43	1.71	1.79	69.28	15.79
9b Case 19b with low ber	nding moment	Pb from 14.55 ksi to 6.65 ksi	arrest	arrest	arrest	arrest	arrest	arrest
Ic Case 1c with a 20° ID repair	(WRS w/o SS weld)	WRS from ASME 3/30 fit to 20° ID repair w/o SS weld	109	>>21	2.24	4.42	5.81	1.28 (note 1)
Ic Case 3c with a 20° ID repair	(WRS w/o SS weld)	WRS from ASME 3/30 fit to 20° ID repair w/o SS weld	125	>>17	2.40	4.78	6.22	1.25 (note 1)
Case 6c with a 20° ID repair	(WRS w/o SS wetd)	WRS from ASME 3/30 fit to 20° ID repair w/o SS weld	41	>>37	1.70	3.36	4.04	1.67 (note 1)
Case 6c with a 20 (modified ASM))° ID repair E WRS)	WRS from ASME 3/30 fit to 20° ID repair modified ASME	41	173	1.70	2.98	4.04	6.44
Case 6c with a 20° ID repair and multiple r	(WRS w/o SS weld) epairs	WRS from ASME 3/30 fit to 20° ID repair w/o SS weld: Number of Repairs from 1 to 3	41	>>21	1.70	2.99	4.04	1.22 (note 1)
c Case 7c with a 20° ID repair	(WRS w/o SS weld)	WRS from ASME 3/30 fit to 20° ID repair w/o SS weld	11	>>21	2.01	4.24	5.44	1.31 (note 1)
7a Case 17a with an ID repair	(WRS w/ SS weld)	WRS from w/ SS weld to ID repair w/ SS weld	arrest	78	arrest	2.12	arrest	98.51
7b Case 17b with an ID repair	(WRS w/o SS weld)	WRS from w/o SS weld to ID repair w/o SS weld	35	68	1.71	2.05	69.28	91.86
8a Case 18a with an ID repair	(WRS w/ SS weld)	WRS from w/ SS weld to ID repair w/ SS weld	arrest	>>40	arrest	2.83	arrest	5.40 (note 1)
7b Case 17b with intermediate	bending moment	Pb from 13.57 ksi to 13.00 ksi	35	38	1.71	1.74	69.28	70.43
7b Case 17b with low ben	ding moment	Pb from 13.57 ksi to 10.00 ksi	35	27	1.71	1.67	69.28	28.75
3b Case 18b with high ber	iding moment	Pb from 4.88 ksi to 7.00 ksi	43	11	1.79	1.38	15.79	8.49
3b Case 18b with low ben	ding moment	Pb from 4.88 ksi to 4.03 ksi	43	arrest	1.79	arrest	15.79	arrest
c Case 1c with 10% gre	ater thickness	Thickness from 1.29 in to 1.419 in	109	146	2.24	2.46	5.81	6.43
c Case 1c with 10% les	sser thickness	Thickness from 1.29 in to 1.161 in	109	74	2.24	1.96	5.81	4.80
c Case 4c with low axial me	embrane stiffness	Pm from 1.90 ksi to 1.64 ksi	112	123	2.18	2.20	5.22	5.27
c Case 4c with high axial m	embrane stiffness	Pm from 1.90 ksi to 2.15 ksi	112	98	2.18	2.12	5.22	5.52
ic Case 6c with shortene	d weld length	Weld Length from 1 in to 0.5 in	41	32	1.70	1.62	4.04	3.67
not specific for a Stability Mardi	In Factor of 1.2; case	has Stability Margin Factor >> 1.2 when time > 40 days						

Table 7-7 **Sensitivity Summary**

Margin Factor of 1.2 [gpm] not applicable pplicable applicable applicable Catculated Leak Rate (at 70°F) at a Stability 191.43 pplicable 87.49 69.28 73.58 70.05 arrest arrest arrest 3.99 4.98 5.18 4.70 4.84 3.86 63.34 arrest 42.35 6.00 4.97 2.97 2.64 8.57 4.87 6.61 ğ ğ ğ ŋð 69.28 69.28 69.28 69.28 69.28 69.28 69.28 69.28 69.28 arrest 69.28 69.28 69.28 arrest 69.28 arrest arrest from 4.04 4.04 4.04 4.04 4.04 4.04 4.04 3.54 3.54 4.04 4.04 5.81 Stability Margin Factor at 1 gpm (or at initial leak rate 1.48 (note 2) 1.29 (note 2) 1.44 (note 2) 1.43 (note 1.69 1.70 1.73 arrest 1.83 1.89 1.77 1.84 1.69 1.71 2.85 4.33 arrest 2.26 arrest 1.69 1.03 1.28 arrest 1.60 Comparison \$ 1.83 1.81 1.57 <u>1.9</u> 2.03 if higher) 1.65 (note 2) 1.65 (note 2) 1.65 (note 2) 1.65 (note 2) Result arrest arrest 1.70 nom 1.70 1.70 1.70 1.70 1.70 1.70 1.70 1.86 1.86 1.71 1.71 1.71 1.70 1.71 arrest 2.24 arrest 1.71 1.71 1.71 1.71 1.7 Time Interval from 1 gpm to a Stability Margin Factor of not applicable not applicable applicable applicable applicable arrest arresf arresf arrest 5 42 49 49 47 53 44 39 47 46 73 22 39 145 293 49 74 not not Ъ 29 37 94 4 1.2 [days] from arrest arrest arrest arrest 4 109 4 4 4 £ 4 £ 4 48 48 35 35 35 4 35 35 35 35 35 35 35 35 35 35 Number of Initial Flaws from single 21:1 partial-arc crack at top of weld to 21:1 partial-arc cracks at top and bottom of weld (Fig. 7-15) arc nitial Surface Flaw from 21:1, 26% TW, natural shape partial-arc nitial Surface Flaw from 21:1, 26% TW, natural shape partial-arc Initial Surface Flaw from 21:1, 26% TW, natural shape partial-arc Initial Surface Flaw from 21:1, 26% TW, natural shape partial-arc after 7 days of leakage w additional limiting partial-arc crack at 95% TW (Fig. 7-14) Geometry from cylinder to detailed nozzle-to-safe end; WRS from thermal simulation to direct FEA interpolation after 7 days of leakage w/ additional 21:1 partial arc crack at after 7 days of leakage w/ additional 21:1 partial-arc crack at after 7 days of leakage w/ additional 21:1 partial arc crack at Pm from 2.34 ksi to 2.46 ksi; Pb from 7.63 ksi to 0.94 ksi Pm from 3.72 ksi to 3.71 ksi; Pb from 13.57 ksi to 0.79 ksi Prn from 3.45 ksi to 3.36 ksi; Pb from 14.55 ksi to 0.90 ksi Initial Surface Flaw from 21:1, 26% TW, natural shape partial-to Uniform, 10% TW 360* to Uniform, 10% TW 360°; Pb from 13.57 ksi to 8.40 ksi Geometry from cylinder to detailed nozzle-to-safe end Geometry from cylinder to detailed nozzle-to-safe end Initial Surface Flaw from Uniform, 10% TW 360° to initial Surface Flaw from Uniform, 10% TW 360° to initial Surface Flaw from Uniform, 10% TW 360° to 9 2 WRS from ASME 3/30 fit to plastic redistribution Crack Front Pressure from 2235 psi to 1330 psi 21:1. 26% TW. constant depth partial-arc Initial Surface Flaw from Uniform. 10% TW 360" 21:1. 15% TW. natural shape partial-arc Initial Surface Flaw from Uniform. 10% TW 360" 21:1. 40% TW. natural shape partial-arc to 5.6:1, 10% TW, natural shape partial-arc 21:1, 26% TW, natural shape partial arc 21:1, 26% TW, semi-ellipse partial-arc Quantitative Sensitivity Description CGR Exponent from 1.6 to 1.0 CGR Exponent from 1.6 to 2.2 CGR Exponent from 1.6 to 1.0 CGR Exponent from 1.6 to 1.0 CGR Exponent from 1.6 to 2.2 CGR Exponent from 1.6 to 2.2 to Uniform, 10% TW 360* to Uniform, 10% TW 360* position 1 (Fig. 7-14) position 2 (Fig. 7-14) position 3 (Fig. 7-14) Case 17b with additional crack flaw at position 2 Case 17b with additional crack flaw at position 3 Case 17b with additional crack flaw at bottom of Case 6c with constant depth initial surface flaw Case 17b with 360° initial surface flaw and low Case 17b with short crack length initial surface Case 6c with natural shape initial surface flaw Case 17b without thermal loads for TW crack Case 19b without thermal loads for TW crack Case 17b with additional crack flaw at position Case 6c with semi-ellipse initial surface flaw Case 17b with reduced crack front pressure Case 6c without thermal loads for TW crack geometry and direct FEA WRS interpolation Case 17b with high crack growth exponent redistribution Case 12c with low crack growth exponent Case 12c with high crack growth exponent Case 17b with low crack growth exponent Case 1c with detailed nozzle-to-safe end Case 1b with detailed nozzle-to-safe end Case 17b with detailed nozzle-to-safe end Case 6c with high crack growth exponent Case 6c with low crack growth exponent Case 6c with shallow initial surface flaw Case 17b with 360° initial surface flaw Case 17b with additional limiting crack Case 19b with 360° initial surface flaw Case 6c with deep initial surface flaw Case 17a with 360° initial surface flaw Qualitative Sensitivity Description Vote 2: Stability Margin Factor after 7 days of leakage plastic (bending moment (modified WRS) geometry geometry flaw weld with Case 6c modeled 17b 17b 17b 17b 17b 17b 17b gc g <u>6</u> ပ္ပ 12c 12c 17b gc 19b 4 17b 17a 17b 17b 17b 17b 19b aseC ase 90 90 g g ę ARS Subcase υ U υ U U o o o U υ a ٩ م υ م م U σ م æ م ٩ م ٩ ۵ p ٩ ٩ ۵ Case 36 37 38 39 4 4 42 43 44 45 46 47 48 49 50 51 52 52 53 S S SS S3 S4 S5 S6 S7 S8 S9

Table 7-7 (cont'd) Sensitivity Summary







Figure 7-2 WRS Fit for Type 1 Safety and Relief Nozzle Including Effect of Stainless Steel Weld (with normal operating temperature applied)



Figure 7-3

WRS Cubic Fit for Type 1 Safety and Relief Nozzle Excluding Effect of Stainless Steel Weld (with normal operating temperature applied)



Figure 7-4

WRS Quartic Fit for Type 1 Safety and Relief Nozzle Excluding Effect of Stainless Steel Weld with σ_0 set to 54 ksi (with normal operating temperature applied)





WRS Fits for Safety and Relief Nozzle with 3D ID Repair Excluding Effect of Stainless Steel Weld with σ_0 set to 27.5 ksi and 74.8 ksi (with normal operating temperature applied)



Figure 7-6

WRS Fit for Type 8 Surge Nozzle Including Effect of Stainless Steel Weld (with normal operating temperature applied)



Figure 7-7

WRS Fit for Type 8 Surge Nozzle Excluding Effect of Stainless Steel Weld with σ_0 set to 54.0 ksi (with normal operating temperature applied)



Figure 7-8

WRS Fit for Type 8 Surge Nozzle Excluding Effect of Stainless Steel Weld (Applied in Case 17b) Compared to DEI and EMC² WRS FEA Results Including Effect of Stainless Steel Weld



Figure 7-9

WRS Fit for Type 9 Surge Nozzle Excluding Effect of Stainless Steel Weld with σ_0 set to -15.2 ksi (with normal operating temperature applied)



Figure 7-10

MRP-115 Deterministic Crack Growth Rate Equation for Alloy 82 and 182 (best-fit K-exponent of 1.6) and Newly Developed Curves for Alloy 182 with 5^{th} and 95^{th} Percentile K-Exponents (n = 1.0 and 2.2, respectively)



Figure 7-11 Weld Factor Fit Used to Develop Power-Law Constant for Best-Fit K-Exponent (1.59)



Figure 7-12 Weld Factor Fit Used to Develop Power-Law Constant for 5th Percentile K-Exponent (1.0)













Case S9b Growth Progression Based on Individual Growth of Initial 21:1 Aspect Ratio 26% through-wall Flaws Placed at Top and Bottom of Weld Cross Section



Figure 7-16 Case S9b Growth Progression Shown in Polar Coordinates



Figure 7-17 Example Crack Meshes for a Variety of Sensitivity Cases and Crack Types







7-42



Figure 7-19 Key Load Margin Factor Results for Geometry and Load Base Cases Including ID Repair



Time (days) or Leak Rate (gpm at 70°F)

Figure 7-20

Key Time and Leak Rate Results for Other Main Cases



Figure 7-21 Key Load Margin Factor Results for Other Main Cases



Figure 7-22 Leak Rate and Load Margin Factor as a Function of Time—Case 6c



Figure 7-23 Leak Rate and Load Margin Factor as a Function of Time—Case 12c



Figure 7-24 Leak Rate and Load Margin Factor as a Function of Time—Case 17b



Figure 7-25 Leak Rate and Load Margin Factor as a Function of Time—Case 23b



Figure 7-26 Leak Rate and Load Margin Factor as a Function of Time—Case 25a



Figure 7-27 Leak Rate and Load Margin Factor as a Function of Time—Case 27b



Figure 7-28 Leak Rate and Load Margin Factor as a Function of Time—Case 28b



Figure 7-29 Leak Rate and Load Margin Factor as a Function of Time—Case 29b



Figure 7-30 Leak Rate and Load Margin Factor as a Function of Time—Case 35c



Figure 7-31 Leak Rate and Load Margin Factor as a Function of Time—Case 36c



Figure 7-32 Leak Rate and Load Margin Factor as a Function of Time—Case 42c



Figure 7-33 Leak Rate and Load Margin Factor as a Function of Time—Case 43c



Figure 7-34 Leak Rate and Load Margin Factor as a Function of Time—Case 44c



Figure 7-35 Leak Rate and Load Margin Factor as a Function of Time—Case 46b



Figure 7-36 Leak Rate and Load Margin Factor as a Function of Time—Case 47b



Figure 7-37 Leak Rate and Load Margin Factor as a Function of Time—Case 48b

Sensitivity Case Matrix



Figure 7-38 Leak Rate and Load Margin Factor as a Function of Time—Case 53b



Figure 7-39 Leak Rate and Load Margin Factor as a Function of Time—Case S1b



Figure 7-40 Leak Rate and Load Margin Factor as a Function of Time—Case S2b



Figure 7-41 Leak Rate and Load Margin Factor as a Function of Time—Case S9b

8 SUMMARY AND CONCLUSIONS

A summary of the findings of this study, including main conclusions, are as follows:

- ELIMINATION OF OVERLY CONSERVATIVE ASSUMPTION OF SEMI-ELLIPTICAL CRACK SHAPE. A calculation methodology has been developed through extensions to the FEACrack software to model the shape progression of a circumferential PWSCC flaw based on the stress intensity factor calculated at each point on the crack front. This refinement in crack growth modeling eliminates the need to assume that the crack shape remains a semi-ellipse grown on the basis of the stress intensity factor at the deepest and surface points. This study demonstrates that this classical assumption of a semi-elliptical crack shape results in a large overestimation of the crack area and thus underestimation of the crack stability at the point in time at which the crack penetrates to the outside surface.
- COLLECTION OF PLANT-SPECIFIC INPUTS. Extensive weld-specific design and fabrication inputs were collected for the group of 51 subject dissimilar metal welds. Detailed geometry and piping load inputs were collected for each subject weld to ensure that all welds are appropriately addressed by the crack growth sensitivity matrix developed as part of this study. Weld-specific fabrication and weld repair data were also collected as a key input to the welding residual stress simulations addressing the subject population. The frequency of ID weld repairs in the subject population was found to be significantly less than that for the Wolf Creek pressurizer nozzle dissimilar metal welds.
- WELDING RESIDUAL STRESS SIMULATIONS. A matrix of welding residual stress (WRS) simulations were performed on the basis of the detailed design, fabrication, and weld repair information collected. Axisymmetric and non-axisymmetric weld repair WRS profiles were developed for input to the crack growth simulations under various assumptions in recognition of the uncertainty in calculation of WRS values. In addition, the WRS methodology applied in this report was benchmarked versus stress measurements and the simulations of other organizations for a piping butt weld mockup.
- CRITICAL CRACK SIZE METHODOLOGY. A critical crack size methodology was developed specific to the subject nozzle-to-safe-end geometry and materials. This methodology, which was implemented as a post-processing calculation to the crack profiles simulated in the crack growth calculations, is based on the net section collapse (NSC) equations for an arbitrary circumferential crack profile in a thin-walled pipe. Although new calculations and past experimental experience indicate that secondary piping thermal constraint loads will significantly or completely relax prior to rupture, normal thermal piping loads were included in the crack stability calculations. In addition, a Z-factor approach reducing the NSC failure load was implemented in consideration of the possibility of an EPFM failure mechanism. Available experimental failure data for complex cracks in materials similar to Alloy 82/182 show that the implemented critical crack size methodology likely results in conservative predictions of rupture.

Summary and Conclusions

- LEAK RATE METHODOLOGY. EPRI's PICEP software was applied to calculate the leak rate development for the simulated through-wall and complex crack profiles. The crack opening area at the weld OD calculated in the crack growth finite-element simulations was applied directly in these PICEP leak rate calculations. NRC's SQUIRT software was also applied in scoping leak rate calculations, and was found to predict slightly higher leak rates (that would be identified sooner) than PICEP.
- DEVELOPMENT OF EVALUATION CRITERIA. Based on the detailed input of the EPRI expert panel, a set of criteria were developed to evaluate the results of the crack growth, crack stability, and leak rate calculations for each sensitivity case investigated. These criteria provide guidance for applying the matrix results, and were developed in consideration of the many modeling uncertainties addressed in the detailed calculations performed. The evaluation criteria provide safety margins based on explicit consideration of leak rate detection sensitivity, plant response time, and uncertainty in the crack stability calculations.
- CRACK GROWTH SENSITIVITY MATRIX DEVELOPMENT. An extensive sensitivity matrix of 119 cases was developed to robustly address the weld-specific geometry and load input parameters for the set of 51 subject welds, plus key modeling uncertainties such as those associated with WRS, initial crack shape and depth, the K-dependence of the crack growth rate equation, and the effect of multiple flaws. The later cases in the sensitivity matrix were defined to further investigate cases showing limiting results.
- CRACK GROWTH SENSITIVITY MATRIX RESULTS. All 109 cases in the main sensitivity matrix showed either stable crack arrest (60 cases) or crack leakage and crack stability results satisfying the evaluation criteria (49 cases). In most cases, the results showed large evaluation margins in leakage time and in crack stability. The margins in the matrix results demonstrate that even cases representing an unlikely combination of detrimental factors are likely to result in sufficient time for leak detection prior to rupture. The complementary probabilistic evaluations presented in Appendix E further support the adequacy of the deterministic sensitivity cases investigated.

Ten supplemental cases were added to further investigate the potential effect of multiple flaws in the subject surge nozzles. Conservative application of the three indications found in the Wolf Creek surge nozzle weld for surge nozzles with a fill-in weld and relatively high moment load gives results meeting the evaluation criteria with additional margin. In addition, considering a case with two long initial partial-arc flaws covering 46% of the ID circumference as opposed to a single initial flaw covering half this circumferential extent (and centered at the location of maximum axial bending stress) has only a modest effect on crack stability for these limiting surge nozzles. On this basis, it is concluded that the concern for multiple flaws in the limiting surge nozzles is adequately addressed by those supplemental cases that satisfy the evaluation criteria with additional margin.

In summary, all 51 subject welds are adequately covered by crack growth sensitivity cases that satisfy the evaluation criteria presented in Section 7.2.

• TENDENCY OF CIRCUMFERENTIAL SURFACE CRACKS TO SHOW ARREST. An additional key finding concerns the significant number of crack growth sensitivity cases that showed stable crack arrest prior to through-wall penetration. This type of behavior is consistent with the relatively narrow band of relative depths reported for the four largest Wolf Creek indications (23%, 25%, 26%, and 31% through-wall). It is statistically unlikely that these four
indications would be found in this narrow depth band if they were in fact growing rapidly in the depth direction at the time they were detected. The basic reason that circumferential cracks may tend to arrest prior to through-wall penetration is that to the extent the throughwall welding residual stress profile is axisymmetric, it must be self-balanced at a particular circumferential position, meaning that a significant portion of the wall thickness must have compressive axial welding residual stresses.

• LARGE BENEFIT GIVEN RELAXATION OF SECONDARY LOADS UPON THROUGH-WALL PENETRATION. Two sensitivity cases showed a greatly increased time between a leak rate of 1.0 gpm and the load margin factor of 1.2 being reached when it is assumed that the piping thermal constraint loads are relieved upon through-wall penetration. These cases confirm the expectation of a large benefit if the piping thermal constraint loads are significantly relaxed once the crack grows through-wall. Detailed evaluations tend to support this kind of behavior, but such relaxation was conservatively not credited in the base assumptions of the critical crack size methodology developed for this study. Rather, 100% of the normal operating thermal piping loads (excluding surge line thermal stratification effects) were included in the critical crack size calculations.

In summary, this study demonstrates the viability of leak detection to preclude the potential for rupture for the pressurizer nozzle dissimilar metal (DM) welds in the group of subject PWRs.

9 REFERENCES

- 1. "Implications of Wolf Creek Pressurizer Butt Weld Indications Relative to Safety Assessment and Inspection Requirements," MRP 2007-003 Attachment 1, January 2007.
- 2. US NRC, "NRC Wolf Creek Flaw Evaluation," presented at November 30, 2006, public meeting between US NRC and MRP, North Bethesda, Maryland.
- 3. US NRC, "Safety Concerns Regarding Potential Pressurizer Weld Cracking," presented at December 20, 2006, public meeting between US NRC and MRP, Rockville, Maryland.
- 4. "Review and Refinement of NRC Crack Growth Calculation for Relief Nozzle," Section 5 in Implications of Wolf Creek Pressurizer Butt Weld Indications Relative to Safety Assessment and Inspection Requirements, MRP 2007-003 Attachment 1, January 2007.
- 5. "Westinghouse Data: Repair History, Nozzle Dimensions, Nozzle Loads," Westinghouse Electric Co., NSD-EPRI-07-28, April 27, 2007.
- 6. "Transmittal of PWROG Information under PA-MSC-0233 to EPRI to Support the Industry Finite Element Analysis (FEA) for the Pressurizer Nozzles, LTR-PCAM-07-38, Rev 1, April 2007," PWR Owners Group, OG-07-185, April 27, 2007.
- 7. "Westinghouse and Combustion Engineering Pressurizer Nozzle Fabrication Detail," Westinghouse Electric Co., NSD-EPRI-07-41, July 27, 2007.
- 8. "Transmittal of Final PWROG Information under PA-MSC-0233 to EPRI to Support the Industry Finite Element Analysis (FEA) for the Pressurizer Nozzles, LTR-PCAM-07-67, July 20, 2007," PWR Owners Group, OG-07-343, July 26, 2007.
- 9. Modeling and Meshing Guide, ANSYS 10.0 Documentation, ANSYS, Inc.
- 10. *Inconel Alloy 600*, Special Metals Corporation Publication No. SMC 027, September 2002.
- 11. ASME Boiler and Pressure Vessel Code, Section II, Part D, Properties, 1992 Edition.
- 12. M. H. Duc, "Specification de Calcul de Maquettes d'adaptateurs." EdF Specification MS-92-090-A-GPE: A667M.

References

- 13. L. Karlsson, M. Jonsson, L-E. Lindgren, M. Näsström, and L. Troive, "Residual Stresses and Deformations in a Welded Thin-Walled Pipe," *ASME Pressure Vessels & Piping Conference*, Honolulu, Hawaii, USA, July 1989.
- E. F. Rybicki and R. B. Stonesifer, "Computation of Residual Stresses due to Multipass Welds in Piping Systems," Journal of Pressure Vessel Technology, Volume 101, May 1979, pp. 149-154.
- 15. BWR Vessel and Internals Project: Evaluation of Crack Growth in BWR Stainless Steel RPV Internals (BWRVIP-14), EPRI No. TR-105873, Appendix H. Palo Alto, CA: Electric Power Research Institute, March 1996.
- 16. "Welding Handbook," Volume One, Seventh Edition, p. 94, American Welding Society, 1981.
- 17. P. Dong, J. Zhang, and P. J. Bouchard, "Effects of Repair Weld Length on Residual Stress Distribution," *Journal of Pressure Vessel Technology*, vol. 124, February 2002.
- T. McGaughy and L. Boyles, "Significance of Changes in Residual Stresses and Fracture Toughness due to SMAW Repair of Girth Welds in Line Pipe," *Pipeline Technology Conference*, Oostende, Belgium, vol. 2., pp. 16.29-16.36, 1990.
- 19. Assessment of Dissimilar Metal Weld Integrity: Final Report of the NESC-III Project, EUR 22510 EN, European Commission Joint Research Centre, 2006.
- 20. *NESC-III Project, TG6 2nd (Detailed) Computational Round Robin,* NESCDOC TG6 (04) 01, Rev. 2, February 26, 2004.
- 21. Materials Reliability Program (MRP) Crack Growth Rates for Evaluating Primary Water Stress Corrosion Cracking (PWSCC) of Alloy 82, 182, and 132 Welds (MRP-115), EPRI, Palo Alto, CA: 2004. 1006696.
- 22. Materials Handbook for Nuclear Plant Pressure Boundary Applications, EPRI, Palo Alto, CA: 2002. 1002792.
- 23. P. Riccardella, Private Communication to G. White, May 25, 2007.
- 24. S. Rahman, G. Wilkowski, "Net-Section-Collapse Analysis of Circumferentially Cracked Cylinders—Part I: Arbitrary-Shaped Cracks and Generalized Equations," *Engineering Fracture Mechanics*, Vol. 61, pp. 191-211, 1998.
- 25. G. Wilkowski, H. Xu, D.-J. Shim, and D. Rudland, "Determination of the Elastic-Plastic Fracture Mechanics Z-factor for Alloy 82/182 Weld Metal Flaws for Use in the ASME Section XI Appendix C Flaw Evaluation Procedures," PVP2007-26733, *Proceedings of ASME-PVP 2007: 2007 ASME Pressure Vessels and Piping Division Conference*, San Antonio, TX, 2007.

- 26. G. Wilkowski, H. Xu, P. Krishnaswamy, N. Chokshi, S. Shaukat, A. Hiser, G. Degrassi, J. Johnson, and R. Olson, "Seismic Considerations for the Transition Break Size," PVP2006-ICPVT11-93994, Proceedings of ASME-PVP 2006 Pressure Vessels and Piping Division Conference, 2006, Vancouver, BC, Canada.
- D. S. Kupperman, S. H. Sheen, W. J. Shack, D. R. Diercks, P. Krishnaswamy, D. Rudland, and G. M. Wilkowski, "Barrier Integrity Research Program: Final Report," NUREG/CR-6861, December 2004.
- 28. ANSC for Determining Net Section Collapse of Arbitrarily Thinned Cylinder, Software User Manual, Structural Integrity Associates, San Jose, CA: 1994.
- 29. An Assessment of Circumferentially Complex-Cracked Pipe Subjected to Bending, Battelle, Columbus, OH, 1986. NUREG/CR-4687.
- 30. Fracture Analysis of Welded Type 304 Stainless Steel Pipe: J-R Curve Characterization and Limit Load Analysis, David W. Taylor Naval Ship Research and Development Center, Bethesda, MD, 1986. NUREG/CR-4538-V1.
- 31. Instability Predictions for Circumferentially Cracked Type-304 Stainless Steel Pipes Under Dynamic Loading, EPRI, Palo Alto, CA: 1982. NP-2347 Volumes 1 and 2.
- 32. *PICEP: Pipe Crack Evaluation Program (Revision 1),* EPRI, Palo Alto, CA: 1987. NP-3596-SR.
- 33. D. Rudland, R. Wolterman, G. Wilkowski, R. Tregoning, "Impact of PWSCC and Current Leak Detection on Leak-Before-Break," *Vessel Head Penetration Inspection, Cracking, and Repairs Conference*, Gaithersburg, MD, 2003.
- 34. SQUIRT Computer Code: Windows Version 1.1 User's Manual, Battelle, Columbus, OH, 2003. NRC-04-91-063.
- 35. US NRC, Standard Review Plan, 3.6.3 Leak-Before-Break Evaluation Procedures, NUREG-0800, Revision 1, March 2007.
- 36. T. Sullivan and A. Csontos, "NRC Questions and Comments on the Industry Advanced FEA Draft Report," July 12, 2007.
- 37. B. Brust and P. Scott, "Battelle Memorial Lab Results: EU Report WRS Round Robin Study Modeling," presented at MRP-NRC meeting of July 12, 2007.
- T. L. Anderson, *Fracture Mechanics*, Third Edition, CRC Press, Taylor & Francis Group, New York, 2005, pp. 86-87.
- 39. T. L. Anderson, et al., "Development of Stress Intensity Factor Solutions for Surface and Embedded Cracks In API 579," Welding Research Council Bulletin 471, May 2002.

References

- 40. R. Bandy and D. van Rooyan, "Quantitative Examination of Stress Corrosion Cracking of Alloy 600 in High Temperature Water – Work in 1983," *Proceedings: 1983 EPRI Workshop on Primary-Side Stress Corrosion Cracking of PWR Steam Generator Tubing*, EPRI, Palo Alto, CA: 1987. NP-5498.
- 41. Analysis of Stress Corrosion Cracks in Alloy 182 Weld Metal After Exposure to PWR Primary Water (MRP-107), EPRI, Palo Alto, CA: 2004. 1009399.
- 42. US NRC, Technical Report on Material Selection and Processing Guidelines for BWR Coolant Pressure Boundary Piping, NUREG-0313, Rev. 2, 1988.
- 43. "Evaluations of Flaws in Austenitic Piping," *Transactions of ASME, J. of Pressure Vessel Technology*, v. 108, Aug. 1986, pp. 352-366.

A APPENDIX A: DISSIMILAR METAL BUTT WELD FABRICATION PROCESSES

Appendix A was prepared by

Westinghouse Electric Co. Nuclear Services 4350 Northern Pike Monroeville, PA 15146

Principal Investigator C. Martin

A.1 General Pressurizer Nozzle Fabrication Processes

This section outlines the general fabrication processes used in production of the dissimilar metal (DM) butt welds of the Combustion Engineering and Westinghouse designed pressurizer surge, spray, safety, and relief nozzles. This section only applies to the subject plants and was created by reviewing design and fabrication information. For the subject plants either a machining or back-welding process was used to ensure solid weld metal throughout the DM weld region. Table A-1 outlines the applicable fabrication process for the subject DM weld locations.

The following provides a brief overview of the three "DM welding processes" noted in Table A-1. A more detailed discussion of these processes is then provided in Section A.2. The fabrication overview will focus on the surge nozzle, but many details of the fabrication process apply equally to the safety/relief nozzles and to the spray nozzles.

1. MACHINED DM WELD LAND WITH ROLLED THERMAL SLEEVE (Figure A-1). Following initial DM weldout, the nozzle DM weld preparation (i.e. weld land) and the inside diameter (ID) of the safe-end were machined to final dimensions. During the machining process the DM weld lands and DM root pass weld were removed to ensured solid weld metal in the DM weld region. The thermal sleeve for the surge and spray nozzles were installed using a rolling process only (no welding).

Plant Identifier	Nozzle	DM Welding Process	Buttering Weld Land Thickness (inch)*	
	Surge		0.06	
A	Spray	Back-Weld	0.06	
	Safety/Relief	· ·	0.06	
	Surge		0.06	
В	Spray	Back-Weld	0.06	
	Safety/Relief		0.06	
	Surge		0.06	
С	Spray	Back-Weld	0.06	
•	Safety/Relief		0.06	
	Surge	Machinad	0.09	
D	Spray	(Bolled Thermal Sleeve)	0.09	
	Safety/Relief	(Holied Hierman Dieeve)	0.09	
	Surge	Machinad	0.10	
E	Spray	(Welded Thermal Sleeve)	0.10	
	Safety/Relief	(Weided Meimar Sieeve)	0.10	
	Surge		N/A	
F	Spray	Back-Weld	0.06	
	Safety/Relief		0.06	
	Surge		0.06	
G	Spray	Back-Weld	0.06	
	Safety/Relief		0.06	
	Surge	Machinad	0.10	
н	Spray	(Welded Thermal Sleeve)	0.10	
	Safety/Relief	(Weided Theimar Cleeve)	0.10	
	Surge	Machinad	0.09	
I	Spray	(Rolled Thermal Sleeve)	0.09	
	Safety/Relief	(Holled Merinal Sleeve)	0.09	
J	Surge		0.06	
	Spray	Back-Weld	0.06	
	Safety/Relief		0.06	

Table A-1Pressurizer Nozzle Fabrication

* See Figure A-5 for typical weld land configuration.



Figure A-1 Surge Nozzle – Machined DM Weld with Rolled Thermal Sleeve

2. BACK-WELD DM WELD LAND WITH WELDED THERMAL SLEEVE (Figure A-2). Following initial DM weldout, the ID DM weld preparation (i.e. weld land) was removed using a grinding process (nozzle ID, 360 degrees circumference). To ensure that the excavation reached the proper depth a dye penetrant examination was used to ensure the weld lands of the nozzle buttering and the safe-end were removed to sound metal. The resultant excavation was then back-welded using Alloy 182, which ensured solid weld metal throughout the DM weld region. Upon completion of the back-welding process an ID weld buildup (thermal sleeve fill-in weld) was applied, at the DM weld, in preparation for the installation of the thermal sleeve. Before the thermal sleeve was installed the weld buildup was machined and PT examined. Following a rolling process an Alloy 82/182 weld, for 45 degrees of the circumference, is used to attach the thermal sleeve to the safe end.



Figure A-2 Surge Nozzle – Back-Grooved DM Weld with Welded Thermal Sleeve

3. MACHINED DM WELD LAND WITH WELDED THERMAL SLEEVE (Figure A-3). Following initial DM weldout, the nozzle DM weld preparation (i.e. weld land) and the inside diameter (ID) of the safe-end were machined to final dimensions. During the machining process the DM weld lands were removed, which ensured solid weld metal within the DM weld region. During the machining process the ID of the nozzle is prepared for the installation of the thermal sleeve. Following a rolling process an Alloy 82/182 weld, for 45 degrees of the circumference, is used to attach the thermal sleeve to the safe-end.



Figure A-3 Surge Nozzle – Machined DM Weld with Welded Thermal Sleeve

A.2 Surge Nozzle Fabrication

The following provides a step-by-step review of the fabrication processes for a surge nozzle.

A.2.1 Machined DM Weld Land with Rolled Thermal Sleeve

This pressurizer nozzle fabrication process used an Alloy 82/182 weld to attach the safe-end to the nozzle. The DM weld lands and the root pass weld were removed using a machining process to ensure solid weld metal throughout the welded region. No attachment welding was used to install the thermal sleeve, instead a rolling process is used. This fabrication process applies to Plants D and I.

- 1. Nozzle Buttering and Cladding
 - a. Alloy 82/182 weld buildup (buttering) was applied to the low alloy steel nozzle using multiple weld layers.
 - b. The inside diameter of the nozzle bore was clad with weld-deposited stainless steel.
 - c. The nozzle buttering was machined to prepare for the safe-end to nozzle single Ugroove weld. Before PWHT the weld buttering underwent dye penetrant and radiography examination.
 - d. The pressurizer head assembly, including nozzle and buttering, underwent a post weld heat treatment (PWHT) process. Following PWHT the weld buttering underwent radiography examination.
- 2. Safe-End to Nozzle Weld
 - a. The safe-end was fit up to the nozzle, with the lands of the machined weld preparations for both the nozzle and safe end butted together. Note that at this point in the process, the ID of the nozzle to safe end region is smaller than the design requires, so the ID can be cleaned up later by machining.
 - b. Layered Alloy 82/182 weld passes were applied from inside diameter to outside diameter to complete DM weld. Radiography examination was then completed.

- 3. Machining
 - a. The nozzle buttering and safe-end weld lands and the root pass weld from the ID of the nozzle were removed using a machining process. During this machining process the inside diameter of the safe-end was machined to meet design requirements.
- 4. Thermal Sleeve
 - a. Thermal sleeve was rolled into place.



Thermal Sleeve

Figure A-4 Surge Nozzle – DM Weld with Rolled Thermal Sleeve

A.2.2 Back-Weld DM Weld Land with Welded Thermal Sleeve

This fabrication process used an Alloy 82/182 weld to attach the safe-end to the nozzle. The DM weld lands and a portion of the root pass weld were removed using a back-welding process (Step 3) to ensure solid weld metal throughout the welded region. This fabrication process applies to Plants A, B, C, F, G, and J

- 1. Nozzle Buttering and Cladding (Figure A-5)
 - a. Alloy 82/182 weld buildup (buttering) was applied to the low alloy steel nozzle using multiple weld layers.
 - b. The inside diameter of the nozzle bore was clad with weld-deposited stainless steel.
 - c. An Alloy 82/182 "tie-in" weld was used to connect the buttering and cladding.
 - d. The nozzle buttering was machined to prepare for the safe-end to nozzle single Ugroove weld (Table A-2). Before PWHT the weld buttering underwent dye penetrant and radiography examination.
 - e. The pressurizer head assembly, including nozzle and buttering, underwent a post weld heat treatment process. Following PWHT the weld buttering underwent radiography examination.



- 2. Safe-End to Nozzle Weld (Figure A-6)
 - a. The safe-end was fit up to the nozzle.
 - b. Layered Alloy 82/182 weld passes were applied from inside diameter to outside diameter. The DM weld then underwent radiography examination.



Figure A-6 Safe-End to Nozzle Weld

- 3. Back-Weld (Figure A-7)
 - a. The inside diameter of the safe-end to nozzle DM weld, at the DM weld lands, was then removed using a grinding process. Intermediate dye penetrant (PT) exams were used to ensure the weld lands of the nozzle buttering and safe-end were removed to sound metal (~0.06-0.10 inch).
 - b. After PT examination the excavation was filled using an Alloy 82/182 weld. PT examination was then completed on the ID of the DM weld.





- 4. Thermal Sleeve Welds (Figures A-8 and A-9)
 - a. An Alloy 82/182 weld buildup (fill-in weld) was then applied on the ID (360 degree circumference) using layering weld beads. The welded surface was then

machined to prepare for the installation of the thermal sleeve (Figure A-8, Table A-3). The weld buildup underwent PT exam prior to installation of the thermal sleeve.

b. The thermal sleeve is positioned on the thermal-sleeve fill-in weld and then rolled into place (Figure A-9). Following the rolling process an Alloy 82/182 weld, for 45 degrees of the circumference, is used to attach it to the safe end. Finally, the thermal sleeve attachment weld underwent PT exam.



Table A-3 Thermal Sleeve Fill-In Weld Approximate Dimensions				
Plant Identifier	"B" Approx. (inch)	"C" Approx. (inch)		
Α	2.1	0.3		
В	2.1	0.3		
С	2.1	0.3		
D	N/A (no weld buildup)			
Е	N/A (machined fit)			
F	N/A (mitigated)			
G	2.1	0.3		
Н	N/A (machined fit)			
1	N/A (no weld buildup)			
J	2.1	0.3		

Figure A-8 Thermal Sleeve Fill-In Weld





A.2.3 Machined DM Weld Land with Welded Thermal Sleeve

This fabrication process used an Alloy 82/182 weld to attach the safe-end to the nozzle. The DM weld lands and the DM root pass weld were removed using a machining process to ensure solid weld metal throughout the welded region. An attachment weld was used to install the thermal sleeve. This fabrication process applies to Plants E and H.

- 1. Nozzle Buttering and Cladding (Figure A-10)
 - a. Alloy 82/182 weld buildup was applied to the low alloy steel nozzle using multiple weld layers.
 - b. The inside diameter of the nozzle bore was clad with weld-deposited stainless steel.
 - c. The nozzle buttering was machined to prepare for the safe-end to nozzle single Ugroove weld.
 - d. The pressurizer head assembly, including nozzle and buttering, underwent a post weld heat treatment process. Following PWHT the weld buttering underwent radiography examination.



Figure A-10 Clad and Buttering

- 2. Safe-End to Nozzle Weld (Figure A-11)
 - a. The safe-end was fit up to the nozzle, with the lands of the machined weld preparations for both the nozzle and safe end butted together. Note that at this point in the process, the ID of the nozzle to safe end region is smaller than the design requires, so the ID can be cleaned up later by machining.
 - b. Layered Alloy 82/182 weld passes were applied from inside diameter to outside diameter to complete DM weld. Radiography examination was then completed.



Figure A-11 Safe-End to Nozzle DM Weld

- 3. Machining (Figure A-12)
 - a. The nozzle buttering and safe-end weld lands and root pass on the ID, were then machined. During this machining process the inside diameter of the nozzle was prepared for the installation of the thermal sleeve.



Figure A-12 Post DM Weld Machining

- 4. Thermal Sleeve Weld (Figure A-13)
 - a. The thermal sleeve is positioned and rolled into place. Following the rolling process an Alloy 82/182 weld, for 45 degrees of the circumference, is used to attach it to the safe end. Finally, the thermal sleeve attachment weld underwent PT exam.



Thermal Sleeve Attachment Weld

A.3 Spray Nozzle Fabrication

The fabrication processes identified in Table A-1 apply to the spray nozzles. The details of these fabrication processes for the spray nozzles are similar to those provided in Section A.1 and A.2 for the surge nozzles; the "Back-Weld" process is best represented by Figure A-6 and Figure A-7 and the "Machined" process is best represented by Figure A-11 and Figure A-12.

The major difference in fabrication, besides nozzle bore diameter, is that a liner may be used in the place of cladding. Table A-4 provides additional information pertaining to spray nozzle fabrication.

• Plants D, F, and I spray nozzle bore is clad.

• Plants A, B, C, E, G, H, and J spray nozzle bores had liners inserted. Liners were installed by first positioning it into the nozzle bore and then rolling the entire axial length tightly against the ID of the nozzle bore. Then the liner was welded in place using Alloy 82/182 on the safe end and stainless steel to the cladding. The final welds underwent PT examination.

A.4 Safety/Relief Nozzle Fabrication

For the subject plants, the safety and relief nozzles at a given plant were fabricated identically. The fabrication processes identified in Table A-1 apply to the safety and relief nozzles. The details of these fabrication processes for the safety and relief nozzles are similar to those provided in Section A.1 and A.2 for the surge nozzles; the "Back-Weld" process is best represented by Figure A-6 and Figure A-7 and the "Machined" process is best represented by Figure A-12.

The major difference in fabrication among the safety and relief nozzles at the different plants, besides nozzle bore diameter, is that a liner may be used in the place of cladding; these locations do not have a thermal sleeve. Table A-4 provides additional information pertaining to safety/relief nozzle fabrication. The nozzle liners were installed similar to that of the spray nozzle.

Plant Identifier	Surge Nozzle	Safety/Relief Nozzle				Sprov
		Α	В	С	Relief	Nozzle
A	С, Т	С	С	С	С	L, T
В	C, T	С	С	С	С	L, T
С	С, Т	. L	L	L	L	L, T
D	С, Т	С	С	С	С	СТ
E	С, Т	С	С	С	С	L, T
F	N/A	С	С	С	С	С, Т
G	С, Т	L	L	L	L	L, T
Н	С, Т	С	С	С	С	L, T
I	С, Т	С	С	N/A	С	С, Т
J	С, Т	С	С	С	С	L, T

Table A-4 Nozzle Detail

C = Stainless Steel Cladding

- L = Liner
- T = Thermal Sleeve

A.5 Design Sketches

Figures A-14 through A-38 are sketches of the nozzle designs covering each of the 51 subject welds. Figures A-14 through A-22 cover the 35 safety/relief nozzles, Figures A-23 through A-30 cover the 8 spray nozzles, and Figures A-31 through A-38 cover the 8 surge nozzles.

The figures provided in this appendix are not the final production manufacturing drawings. Manufacturing details were revealed later in the course of this project, and drawings showing the final manufactured state for each plant's nozzles are not as readily available as the design drawings. In some cases, the manufacturing process used for a given plant (per Table A-1) differs from the one suggested by the design drawing. For example, comparing Figure A-14 (safety/relief Plant A) to Figure A-18 (safety/relief Plant E), it would be concluded the plants A and E share the same manufacturing process. However, as noted in Table A-1, plants A and E do not share the same process.

The plants affected by this difference between design and manufacturing are plants E and H. The design drawings for these plants are consistent with a "Back-Weld" process, but they were manufactured using a "Machined" process. The figures for these plants are still relevant, however. The "Machined" process did not change the final outline dimensions of the safe end, weld, or nozzle relative to the design drawings. Therefore, for example, the thickness of the weld for these plants are the same as indicated in the design drawings. In order to avoid confusion, a note is provided on the figures for plants E and H, referring to this section for additional information.



Figure A-14 Plant A Safety and Relief Nozzle Sketch



Figure A-15 Plant B Safety and Relief Nozzle Sketch





Figure A-16 Plant C Safety and Relief Nozzle Sketch

		_
01	NOZZLE	1
02	WELD EU	
03	SAFE END	1
Ď₄	WELD	
05	CLADDING	1
05	WELD	
07	WELD	
08	PIPE	
09	PIFE	





Figure A-17 Plant D Safety and Relief Nozzle Sketch

Note: The manufacturing process suggested by this drawing differs from the actual manufacturing process. The outline dimensions provided in this figure are not affected by the difference. See Section A.5 for additional details.



Figure A-18 Plant E Safety and Relief Nozzle Sketch





Figure A-19 Plant F Safety and Relief Nozzle Sketch



Figure A-20 Plant G Safety and Relief Nozzle Sketch

Note: The manufacturing process suggested by this drawing differs from the actual manufacturing process. The outline dimensions provided in this figure are not affected by the difference. See Section A.5 for additional details.



Figure A-21 Plant H Safety and Relief Nozzle Sketch







Figure A-22 Plant I Safety and Relief Nozzle Sketch



Figure A-23 Plant A Spray Nozzle Sketch



Figure A-24 Plant B Spray Nozzle Sketch



Figure A-25 Plant C Spray Nozzle Sketch

Appendix A: Dissimilar Metal Butt Weld Fabrication Processes





Figure A-26 Plant D Spray Nozzle Sketch

Note: The manufacturing process suggested by this drawing differs from the actual manufacturing process. The outline dimensions provided in this figure are not affected by the difference. See Section A.5 for additional details.



Figure A-27 Plant E Spray Nozzle Sketch



Figure A-28 Plant F Spray Nozzle Sketch



Figure A-29 Plant G Spray Nozzle Sketch
ITEM	NOTE	PART NAVE
Ģi		NOZZLE
02		WELD BU
03		SAFE_END
04		SLEEVE
05		WELD
96		CLADDING
07	١	WELD MATL
<u>ð8</u>	2	PIPE





Figure A-30 Plant I Spray Nozzle Sketch

١



Figure A-31 Plant A Surge Nozzle Sketch

Appendix A: Dissimilar Metal Butt Weld Fabrication Processes



Figure A-32 Plant B Surge Nozzle Sketch

ï





Figure A-33 Plant C Surge Nozzle Sketch



Figure A-34 Plant D Surge Nozzle Sketch

Note: The manufacturing process suggested by this drawing differs from the actual manufacturing process. The outline dimensions provided in this figure are not affected by the difference. See Section A.5 for additional details.



Figure A-35 Plant E Surge Nozzle Sketch

Appendix A: Dissimilar Metal Butt Weld Fabrication Processes



Figure A-36 Plant G Surge Nozzle Sketch



Figure A-37 Plant H Surge Nozzle Sketch

Appendix A: Dissimilar Metal Butt Weld Fabrication Processes



Figure A-38 Plant I Surge Nozzle Sketch

A-40

B APPENDIX B: EVALUATION OF THE EFFECTS OF SECONDARY STRESSES ON SURGE LINE CRITICAL FLAW SIZE CALCULATIONS

Appendix B was prepared by

Structural Integrity Associates, Inc. 6855 South Havana Street Suite 350 Centennial, CO 80112

Principal Investigators P. Riccardella P. Hirschberg

B.1 Introduction

In support of the critical flaw size analyses being performed in the main body of this report, analyses were performed to evaluate the effects of secondary (displacement controlled) loads on critical flaw size. The evaluation included a review of test data from the NRC-sponsored Degraded Piping Program [B-1,B-2]. Detailed test data from selected full scale pipe tests of relevant materials, pipe sizes and flaw types were reviewed to determine the amount of crack plane rotation that was tolerated in the tests prior to failure.

Piping models were also developed for the surge lines of two representative plants in the advanced FEA study (Plants C and I, Westinghouse and CE plant designs, respectively). The piping models were run under secondary operational loading conditions, including anchor movements, thermal expansion and worst case thermal stratification loads for these surge lines. The surge nozzle secondary stresses from these runs were observed to be at the high end of stresses for all nozzles in the study. Then, the models were re-run, after releasing all rotational degrees of freedom at the nodes representing the surge nozzles in the models. The resulting rotations at those nodes were determined, and compared to the rotational tolerance of flawed piping determined from the pipe test data. This comparison evaluates the maximum capacity of the secondary loads to produce rotation at a cracked surge nozzle, relative to the rotational tolerance of a nozzle weld containing a large complex crack.

Also, since the pipe tests did not include any tests of the nozzle weldment material (Alloy-182), a comparison of material toughness properties (J-R curves) of the pipe test materials to Alloy-182 was also performed.

B.2 Full Scale Pipe Fracture Experiments

B.2.1 Test Data

Approximately 60 full scale pipe tests were conducted in the NRC-sponsored Degraded Piping Program [B-1,B-2] of pipes containing three types of circumferential defects: through-wall cracks, surface cracks, and complex cracks (see Figure B-1). Pipe sizes ranged from 4" to 42" and loadings included 4-point bending, combined bending + internal pressure and pure axial load. The majority of pipes tested were in the 6" to 16" range which is directly relevant to the current evaluation.

Selected test data from the Degraded Piping Program [B-1,B-2] are presented in Figures B-2 and B-3. Figure B-2 presents plots of crack plane rotation versus applied stress in the pipe for a series of 6-inch diameter stainless steel pipe tests containing the various crack types illustrated in Figure B-1 (complex cracks of two different sizes, thru-wall and surface cracks). Crack sizes are indicated in the plot legend in terms of lost cross sectional area caused by the crack (CF%). Figure B-3 shows similar plots, comparing crack plane rotation versus applied stress plots for tests with complex cracks only. This plot contains data from two different pipe sizes (6-inch and 16-inch), as well as two different complex flaw sizes (CFs = \sim 57% and 77%). Once again, all tests were austenitic stainless steel pipe.

In some of the tests reported in Figures B-2 and B-3, an inclinometer was used in the test to measure crack plane opening angle directly. In others, inclinometer data were not available, so the crack plane opening angle was computed from measured crack mouth opening displacement using the following formula:

COA = ArcTan (CMOD/pipe Diameter)

where,

COA = Crack Plane Opening Angle (degrees) CMOD = Measured crack mouth opening displacement (at maximum opening location on crack)

This method of estimating crack opening angle was checked against inclinometer measurements for the pipe tests in which both types of measurements were available, and found to be reasonable, but on the low or conservative side (Table B-1, last column).

B.2.2 Permissible Rotations

Review of the plots in Figures B-2 and B-3 illustrate that in all cases, the pipe tests were able to sustain significant rotations, on the order of 2° or greater, prior to maximum load. Beyond that point, the load decreased, with additional rotation tolerated, until ultimate fracture of the pipe at rotations of 7° or greater. (The curve for test 4114-3 in Figure B-3 appears to end at a smaller rotation, ~3.5°, but this corresponded to failure of the displacement gage, not the end of the test.)

A summary of the various tests and the corresponding crack plane rotations at maximum load is given in Table B-1.

It is seen from this table that the only exception to the observation of rotations on the order of $\sim 2^{\circ}$ or greater, prior to maximum load, is the surface crack test, 4131-6, which had rotation of 1.67° at maximum load. This is not unexpected, as the surface crack geometry is not expected to be as compliant as the other crack geometries, and even this amount of rotation tolerance is not insignificant. Another observation regarding the surface crack test is that maximum load did not correspond to failure of the pipe, but rather to break-through of the surface crack to a through-wall crack, which, as illustrated by the plot for this test in Figure B-2, is still able to support significant loading and additional rotation as the test progressed beyond that point.

On the basis of these test results, it is concluded that all but the surface crack geometry can sustain crack plane rotations on the order of 2° or greater prior to failure of the pipe, considering relatively large flaws (CFs between 36% and 77%) and pipe sizes that are relevant to the current evaluation of pressurizer nozzles (6"and 16" nominal pipe diameters). For the surface flaw geometry, the rotational tolerance is slightly smaller, on the order of 1.67°. These observed crack plane rotations are conservatively assumed to be the permissible rotation for cracks of these sizes and configurations in austenitic piping materials. On the basis of the complete curves in Figures B-2 and B-3, crack plane rotations much greater than these values are expected to be tolerated, beyond maximum load, but prior to fracture. However, a more advanced analysis, considering relative compliance of the crack plane versus that of the piping system would be required to take advantage of this additional flaw tolerance, which is beyond the scope of the current study.

B.2.3 Material Toughness

Pipe materials used in the Degraded Piping Program full scale pipe tests included 304 stainless steel, A-600 and Carbon Steel base metals, but no weldments of direct relevance to the A-182 and A-82 dissimilar metal welds (DMWs) of interest in the current evaluation. Therefore the results of the base material pipe tests must be interpreted relative to pressurizer nozzle DMWs on the basis of relative material properties. Fortunately, the piping materials used in the tests were extensively characterized in terms of tensile properties and fracture toughness (J-R curves). Data also exists on the J-R properties of a large A-182 weldment and an A-82 weldment, which can be used for comparison to the test materials.

Figure B-4 presents a compilation of EPFM toughness data (J-R curves) from a number of sources [B-1 through B-5]. The pink dashed curves represent compact tension specimen J-R curves for a large A-182 weldment [B-3], and the sea green dashed curve is for an A-82 weldment [B-4]. These curves represent the weldment materials of interest in pressurizer DMWs. The solid curves are for austenitic base materials (stainless steel + A-600), including the specific materials used for the complex crack pipe tests (blue, red and orange curves). It is seen from these data that, except for the orange A-600 curve, the base materials are not significantly different than the A-82/182 weldments. In fact one of the complex crack pipe test materials (304SS A24C) falls right on top of the A-182 data for crack extension up to ~0.1" and the A-82 curve is much higher. Based on this toughness comparison, it is not expected that A-182 would behave significantly different than the base metals used in full scale pipe tests.

Also shown for comparison are J-R curves for two materials that would be considered "low toughness", a stainless steel submerged arc weld (SAW) and a carbon steel material from the pipe test program, indicated by the heavy brown and black curves in the figure. Note that these material J-R curves lie significantly below the previously discussed curves for austenitic base metal and A-82/182 weldments. These are indicative of how low the toughness of the A-82/182 weldments would have to be before one would be concerned about significantly reduced toughness in these weldments.

On the basis of these materials toughness comparisons, it is reasonably concluded that the rotational tolerances observed in the stainless steel pipe tests (Figures B-2 and B-3) are representative of what would be observed if similar tests were conducted with A-82/182 DMWs.

B.3 Surge Line Piping Analyses

B.3.1 Piping Models

To evaluate the potential pipe rotations that can result from the maximum secondary loads at typical surge nozzles, piping analytical models were created. Two models were developed: one for a CE plant and one for a Westinghouse plant. The details of the piping geometry, including routing, pipe support types and locations, fitting details, and operating conditions, were included. The geometry of the surge line is very similar between plants of a particular NSSS vendor, therefore these models are considered to be typical and representative.

The approach taken was to apply typical enveloping secondary loads to the piping, and determine the resulting stresses and moments at the pressurizer surge nozzle. Then, the rotational degrees of freedom at the nozzle were released, and the magnitude of rotation produced by these loads was determined.

The piping analysis was done using the program PIPESTRESS [B-6]. PIPESTRESS is a fully verified computer code that implements the requirements of the ASME Section III piping design Code.

Figures B-5 and B-6 show the piping models.

B.3.2 Loading Cases

The secondary loadings that are applied to the surge line are three types:

- Thermal expansion
- Anchor movements
- Thermal stratification

For the CE plant, thermal expansion was based on a maximum pipe temperature of 653°F, corresponding to the pressurizer steam space temperature, which is conservative. Thermal anchor movements were applied at the hot leg and at the pressurizer nozzle. These were obtained from the Design Specification. For thermal stratification, a maximum top to bottom

temperature gradient of 320°F was applied. This gradient was used in the CEOG generic stratification report.

For the Westinghouse plant, a similar approach was taken, except that thermal expansion was based on a temperature of 608°F, corresponding to the hot leg temperature, as is typical of Westinghouse analyses. The stratification gradient was 270°F, which is the maximum gradient in the Design Specification of the plant being analyzed.

B.3.3 Analysis Results

Table B-2 summarizes the results of the two analyses. The maximum secondary stress on the CE plant surge nozzle is 19.5 ksi, and in the Westinghouse plant is 24.9 ksi. When the rotational degrees of freedom are released at the nozzle, the rotation produced by the secondary loads is 1.81 degrees for the CE plant model, and 1.77 degrees for the Westinghouse plant model.

Thus, it is concluded that the rotation that would be produced by the maximum secondary loading on typical CE and Westinghouse surge lines does not exceed 2 degrees.

B.4 Conclusions

This evaluation was performed to determine the potential effects of secondary (displacementcontrolled) stresses in surge line piping of plants in the advanced FEA project.

Full scale pipe test data from the Degraded Piping Program show that pipes containing large complex cracks can sustain greater than $\sim 2^{\circ}$ rotation at the crack plane prior to maximum loads being achieved in the tests. The permissible rotational tolerance would be even greater if additional rotation, beyond maximum load in the tests but prior to fracture, were credited.

•The maximum rotation at the surge nozzle that could be produced by worst case secondary loads (anchor movement + thermal expansion + stratification) was demonstrated to be less than 2° for two representative surge lines in the advanced FEA project (one Westinghouse and one CE plant design). This was determined based on piping models of the two surge lines that included the applicable supports and system geometries.

Therefore, the secondary loads would be completely relieved prior to fracture of the nozzles, and critical flaw size calculations need only consider primary, load-controlled stresses.

B.5 References

- B-1. Summary of Technical Results and Their Significance to Leak-Before-Break and In-Service Flaw Acceptance Criteria, NUREG/CR-4082, Volume 8, March 1984 - January 1989.
- B-2. *Pipe Fracture Encyclopedia*, U.S. NRC, 1997 (A collection of NUREG Reports and Data Files from the DP2 and other programs distributed on CDs).

- B-3. G. Wilkowski, H. Xu, D.-J. Shim, and D. Rudland, "Determination of the Elastic-Plastic Fracture Mechanics Z-factor for Alloy 82/182 Weld Metal Flaws for Use in the ASME Section XI Appendix C Flaw Evaluation Procedures," PVP2007-26733, Proceedings of ASME-PVP 2007: 2007 ASME Pressure Vessels and Piping Division Conference, San Antonio, TX, 2007.
- B-4. W. J. Mills and C. M. Brown, "Fracture Toughness of Alloy 600 and EN82H Weld in Air and Water," B-T-3264, Bettis Atomic Power Laboratory.
- B-5. Toughness of Austenitic Stainless Steel Pipe Welds, EPRI, Palo Alto, CA: 1988. NP-4768.
- B-6. Program PIPESTRESS, Version 3.5.1+026, DST Systems, June 2004.

Test	Nominal Pipe Diam. (in.)	Crack Type	CF%	Crack Face Rotation at Max. Load (°)		
				from CMOD	Inclinometer	
4113-1	6	Complex	56.6%	3.13		
4113-2	6	Complex	76.7%	1.97		
4131-5	6	Thru-Wall	38.9%	9.26		
4131-6	6	Surface	36.9%	1.67		
4114-3	16	Complex	58.5%	2.32	3.54	
4114-4	16	Complex	58.5%	2.54	2.95	

Table B-1			
Summary of Crack	Plane Rotations at Maximu	Im Load in Pipe	Tests

Table B-2 Piping Analysis Results

	Summary of Results - Pressurizer Surge Nozzle Moment vs. Rotation								
	Fixed-Fixed Bending Moments			Fixed-Pinned Rotations (Deg.)			Notes		
	Mx, ft-kip	My	Mz	Stress, ksi	Rx, deg.	Ry	Rz	SRSS	
CE Plant	176.303	43.701	5.771	19.485	1.38	0.66	0.97	1.81	1, 2, 3
Westinghouse Plant	138.881	103.841	3.809	24.854	1.13	1.08	0.84	1.77	1, 2, 4
Notes:									
1. My is torsion direct	tion.								
2. Loads include thermal expnasion, anchor movement, and stratification									
3. Stratification delta T is 320 F.									
4. Stratification delta T is 270 F.									



(a) Simple Through-Wall Crack



(b) Internal Surface Crack



(c) Complex Crack

Figure B-1 Illustration of Circumferential Flaw Types Tested



Crack Rotation Comparison

Figure B-2

Plots of Crack Plane Rotation versus Applied Stress in Pipe Tests for Various Flaw Types - All Tests Austenitic Stainless Steel and 6-inch Nominal Pipe Size



Figure B-3

Plots of Crack Plane Rotation versus Applied Stress in Pipe Tests for Various Pipe Sizes – All Tests Austenitic Stainless Steel and Complex Crack Geometry





Comparison of J-R Curves for All0y-182 to Various Pipe Test Materials. Two "Low Toughness" Materials also Plotted for Comparison





Figure B-5 Model of CE Plant Surge Line





C APPENDIX C: SECONDARY STRESS STUDY—PIPE BENDING WITH A THROUGH-THICKNESS CRACK

Appendix C was prepared by

Quest Reliability, LLC 2465 Central Avenue Suite 110 Boulder, CO 80301

Principal Investigators T. Anderson G. Thorwald E. Scheibler

C.1 Introduction

Finite element analysis (FEA) of a pipe with a through-thickness crack was used to determine the effect on bending moment and crack driving force due to an imposed end rotation. The imposed end rotation bends the pipe and causes the through-thickness crack to open. An end rotation could be caused in a piping system by transverse pipe segments extending due to thermal expansion. The moment knock-down factors and crack driving force are computed for a range of crack lengths.

C.2 Analysis

The FEA pipe crack meshes were generated using the FEACrack software (Quest Reliability commercial software), and the analysis was run using ABAQUS (ABAQUS, Inc. software). Two pipe lengths were examined in the analysis. The total length, 2L, of the pipe models were: 60 in and 60 ft. The FEA models are quarter symmetric with a model length of L. The pipes have an inside radius, R_{in} of 6.0 in, and a thickness of 1.5 in. The initial bending stress in the pipe is 25 ksi (uncracked pipe).

The moment knock-down factor for a fixed rotation was computed for each crack length to evaluate the effect of the increasing crack length on the pipe bending moment. The moment knock-down factor is the ratio of the bending moment in the pipe with a crack, M, to the initial uncracked pipe bending moment, M_0 .

```
moment knock-down factor = M/M_{0}
```

The bending moment in the pipe is computed by summing the node reaction forces across the end of the pipe where the imposed rotation is applied.

The J-integral knock-down factor is the ratio of the crack driving force for a fixed rotation, J_{θ} , to the driving force for a fixed applied moment, J_{M} .

J-integral knock-down factor = J/J_{M}

The imposed rotation causes bending, but has a limited amount of elastic energy. As the crack length increases, the crack opening will cause the bending moment in the pipe and crack driving force to decrease.

The imposed rotation at the end of the pipe was applied in two ways. First, the imposed rotation and an axial constraint was applied to all the nodes at the end of the pipe. This method causes pipe bending, but also restricts any axial extension of the pipe. Second, the imposed rotation was applied using a single master node (multi-point constraint method), which allows the pipe to extend axially. The results for these two approaches are discussed in the sections below.

C.2.1 Material Data

For the elastic analysis cases, the Young's modulus of elasticity, E, is 30,000 ksi, and the Poisson ratio is 0.3.

For elastic-plastic analysis material type TP304 (pipe ID DP2-A8) was used. The yield strength is 26.1 ksi, the tensile strength is 66.5 ksi, the modulus E is 26,495 ksi, and the Poisson ratio is 0.3. The stress-strain curve is shown in Figure C-1. The curve was computed from Ramberg-Osgood parameters (a power-law equation); the first point was modified to give elastic behavior below 30 ksi.

C.2.2 Imposed Rotation and Restrained Axial Extension

For an imposed rotation applied to all the pipe end nodes, the axial extension is also constrained since all the nodes move a specified distance. That is axial displacement was imposed to nodes on the end of the model, such that displacement varied linearly through the pipe section and was zero at the neutral axis For long through-thickness cracks, partial crack closure was observed in the results. Figures C-2 to C-5 show a comparison of the bending of the cracked pipe due to an applied moment where the pipe can extend axially, versus the imposed rotation with restrain axial extension that can cause partial crack closure. By using this type of imposed rotation and axial restraint, and due to the crack closure, the pipe does not behave according to simple beam theory. However, there is a reduction in the moment knock-down factor for longer crack lengths. In Figures C-6 and C-7, the circled data points represent where the crack is closing. The moment knock-down factor reaches a minimum value since the region of crack closure is the same for the longer cracks. As Figure C-8 illustrates, the crack driving force (J-integral) reaches a peak value, but then decreases for longer cracks.

C.2.3 Imposed Rotation and Unrestrained Axial Extension

In the multi-point constraint (MPC) method, a single master node at the center of the pipe is grouped with the pipe end nodes, and the imposed rotation is applied to the master node. This method allows the axial extension of the pipe to remain unrestrained so that the pipe can extend while bending. Figures C-9 and C-10 show that since the pipe length is allowed to extend axially, the knock-down factors and crack driving force decrease to zero as the through-thickness crack length extends around the full pipe circumference. Comparing the crack driving force to an applied moment and applied rotation (Figures C-11 and C-12) shows that the bending moment applied unlimited strain to the pipe and the crack driving force is unbounded. The imposed rotation applies finite strain to the pipe and the crack driving force decreases after reaching a peak value. Figure C-13 shows that the J knock-down factor decreases with crack length.

C.3 Summary

The moment knock-down factor and crack driving force in a pipe with a through-thickness crack was examined by finite element analyses of quarter-symmetric pipe models; the pipe models have two lengths (short and long) and a range of crack lengths. An imposed rotation was applied at the end of the pipe to cause the pipe bending. Elastic and elastic-plastic analysis results were compared. The finite amount of strain imposed by the rotation shows that the moment knock-down factor and crack driving force relative to the load controlled case decrease significantly as the crack length increases.

The results of this calculation demonstrate that a circumferential crack in a cylinder responds differently to bending generated by a displacement-controlled source (rotation) versus one generated by a load-controlled source (moment). Even with bending applied to a 60-foot length of piping, the applied moment under displacement loading was found to reduce greatly as the crack length increased. Figures C-10 and C-13 show the key results, which demonstrate the general tendency for relief of secondary piping loads given sufficient crack plane rotation.



Figure C-1 Stress-Strain Curve for Elastic-Plastic Analysis



Figure C-2 Schematic of Pipe Bending due to an Applied Moment









Appendix C: Secondary Stress Study—Pipe Bending With a Through-Thickness Crack



Figure C-5 Elastic FEA Results, Imposed Moment





Figure C-6 Elastic Analysis, Moment Knock-Down Factors



L = 30 ft, Imposed Rotation

Figure C-7 Elastic and Elastic-Plastic Analysis Comparison, Moment Knock-Down Factors



Elastic-Plastic Analysis, L = 30 ft Initial Bending Stress = 30 ksi

Figure C-8 Elastic-Plastic Analysis Crack Driving Force



Imposed Rotation, Elastic Analysis

Figure C-9 Moment Knock-Down Factors, Elastic Analysis, MPC Imposed Rotation Only



Figure C-10 Moment Knock-Down Factors, Elastic-Plastic Analysis, MPC Imposed Rotation Only



Figure C-11 Elastic Crack Driving Force, MPC Imposed Rotation Only

Appendix C: Secondary Stress Study—Pipe Bending With a Through-Thickness Crack



Elastic-Plastic Crack Driving Force, MPC Imposed Rotation Only





Figure C-12

Elastic-Plastic Analysis L = 30 ft, σ_0 = 25 ksi

D APPENDIX D: SCATTER IN LEAK RATE PREDICTIONS

Appendix D was prepared by

Structural Integrity Associates, Inc. 6855 South Havana Street Suite 350 Centennial, CO 80112

Principal Investigator D. Harris

D.1 Evaluation

The purpose of this note is to summarize the results of a study performed regarding accuracy of leak rate predictions from cracks in pipes. This study was requested at the meeting on June 19 and 20 at Dominion Engineering offices in Reston, Virginia. A word document of Reference D-1 was provided in an e-mail from David Rudland of EMC^2 on June 22. IGSCC crack leak rate data from Table B.5 of this reference was employed. This provides about 82 data points of predicted leak rate versus measured leak rate. Table D-1 summarizes the data for which both measured and predicted values are available. This table is in gallons per minute (gpm), which have been converted from the kg/sec used in Reference D-1. Figure D-1 is a plot of this data.

Note that the scatter in the data is much larger at low leak rates, say below 0.1 gpm. This is consistent with the figure shown in the meeting at Dominion Engineering.

The leak rate data was sorted to include only measured leak rates above 0.1 gpm, since small leak rates are not of interest in this context. Values of the ratio of the measured to the predicted leak rates were calculated for the pruned data, which was then sorted in ascending order of this ratio. Table D-2 lists the 34 resulting points. The probability was evaluated from the formula $P=(I-\frac{1}{2})/N$. Figure D-2 presents a normal and lognormal plot of the data.

Figure D-2 shows that the data is not well fit by either a normal or lognormal distribution, and that the 95^{th} percentile is about 1.5. This means that there is a 95% probability that the actual (measured) leak rate will not exceed the calculated value by more than a factor of 1.5.

Another reading on the scatter in leak rate predictions can be obtained from results from Reference D-2, which provides the following relation for the standard deviation of the leak rate for a given mean:

Appendix D: Scatter in Leak Rate Predictions

$$\dot{Q}_{sd} = C_0 \dot{Q}_0 \left[\frac{\dot{Q}_m}{\dot{Q}_0} \right]^{C_1 - C_2 \ln(\dot{Q}_m / \dot{Q}_0)}$$

where,

$$\dot{Q}_0 = 1$$
 gpm=0.063093kg/s
 $C_0 = 0.4671199$
 $C_1 = 0.8675548$
 $C_2 = 0.0062139$.

Assuming the leak rate to be normally distributed with the mean and standard deviation as given above provides the result in Figure D-3. This figure shows that the 95^{th} percentile is predicted to be less than 2 times the mean for flow rates above about 0.1 gpm.

The above results indicate that the leak rate for IGSCC cracks can be predicted within a factor of 1.5-2.0 95% of the time. However, other sources of uncertainty exist, such as applicability of IGSCC data to estimation of scatter for PWSCC, as well as uncertainty in the inputs to the leak rate calculations for PWSCC cracks (items such as surface roughness and pathway loss coefficient).

D.2 References

- D-1. SQUIRT, Seepage Quantification of Upsets in Reactor Tubes, User's Manual, Windows version 1.1, March 24, 2003, Battelle, Columbus, Ohio.
- D-2. M. Bergman, B. Brickstad and F. Nilsson, "A Procedure for Estimation of Pipe Break Probabilities Due to IGSCC," *International Journal of Pressure Vessels & Piping*, Vol. 74, pp. 239-248.

Measured	Predicted		
0.016	0.094		
0.016	0.094		
0.017	0.121		
0.017	0.138		
0.017	0.138		
0.017	0.13		
0.001	0.003		
0.001	0.004		
0	0.001		
0	0.002		
0.002	0.002		
0.002	0.002		
0.002	0.002		
0.001	0.001		
0.002	0.001		
0.002	0.001		
0.482	0.403		
0.46	0.323		
0.769	0.501		
0.732	0.537		
0.716	0.618		
0.704	0.612		
0.582	0.488		
0.569	0.485		
0.398	0.314		
0.372	0.263		
0.477	0.425		
0.472	0.415		
0.628	0.556		
0.624	0.575		
0.715	0.667		
0.75	0.689		
0.609	0.613		
0.621	0.623		
0.609	0.521		
0.471	0.496		
0.415	0.311		
0.249	0.301		

Measured	Predicted
0.029	0.021
0.031	0.027
0.035	0.031
0.038	0.034
0.006	0.021
0.008	0.029
0.062	0.031
0.069	0.034
0.051	0.022
0.057	0.029
0.04	0.014
0.056	0.026
0.065	0.032
0.035	0.015
0.041	0.025
0.05	0.032
0.012	0.009
0.014	0.02
0.024	0.026
0.029	0.031
0.028	0.026
0.024	0.02
0.021	0.013
0.029	0.009
0.037	0.02
0.043	0.026
0.043	0.031
2.393	5.468
2.488	4.406
2.774	5.405
2.235	1.759
2.679	4.01
3.027	5.341
3.17	5.373
2.821	4.184
2.393	1.965
2.029	1.062
2.79	4.359
3.154	5.405

1

Table D-1 Listing of IGSCC Data from Table B.5 of Reference 1 (Leak Rates in gpm)

D-3

Appendix D: Scatter in Leak Rate Predictions

Table D-2

Ratio of Measured to Predicted Leak Rates for IGSCC Data from Table B.5 of Reference 1 with Measured Leak Rate Greater than 0.1 gpm

ratio	probability
0.438	0.0147
0.513	0.0441
0.565	0.0735
0.567	0.1029
0.584	0.1324
0.59	0.1618
0.64	0.1912
0.668	0.2206
0.674	0.25
0.826	0.2794
0.949	0.3088
0.992	0.3382
0.998	0.3676
1.071	0.3971
1.085	0.4265
1.087	0.4559
1.123	0.4853

ratio	probability
1.128	0.5147
1.137	0.5441
1.15	0.5735
1.159	0.6029
1.167	0.6324
1.173	0.6618
1.192	0.6912
1.197	0.7206
1.218	0.75
1.268	0.7794
1.27	0.8088
1.337	0.8382
1.363	0.8676
1.416	0.8971
1.422	0.9265
1.535	0.9559
1.91	0.9853



Figure D-1 Predicted Leak Rate versus Measured Leak Rate for IGSCC Data



Figure D-2 Normal and Lognormal Probability Plots of IGSCC Leak Rate Ratios for Measured Leak Rates above 0.1 gpm

Appendix D: Scatter in Leak Rate Predictions





E APPENDIX E: EVALUATION OF PRESSURIZER ALLOY 82/182 NOZZLE FAILURE PROBABILITY

Appendix E was prepared by

Structural Integrity Associates, Inc. 6855 South Havana Street Suite 350 Centennial, CO 80112

Principal Investigators P. Riccardella D. Dedhia D. Harris

E.1 Introduction

To complement the deterministic analyses described in the main body of this report, the MRP also performed a probabilistic evaluation of the Alloy 82/182 pressurizer butt welded nozzles, considering current inspection data, to assess the effect of various inspection options on the probability of a nozzle failure in the time interval until all nozzles are inspected or mitigated. There are three major elements to the probabilistic analysis approach:

- 1. FLAW DISTRIBUTION. As discussed in Section E.2 of this report, considering inspections performed through Spring of 2007, data exists for a total of 50 Alloy 82/182 nozzles that either have been inspected as part of the MRP-139 inspection program [E-1], or in which leaks, cracks or UT indications have been detected prior to the commencement of MRP-139 examinations in 2006. These data, summarized in Table E-1, and illustrated graphically in Figure E-2, are used to estimate probable flaw distributions that might exist in uninspected nozzles.
- 2. FRAGILITY CURVE. A second important aspect of the analysis, discussed in Section E.3, is the critical flaw size to cause a nozzle failure. For any given flaw size, characterized in terms of percentage of cross section lost to the crack (denoted in this report as the Criticality Factor, CF%), there is a probability that the flaw will cause a pipe rupture under operating loads and internal pressure. This probability of rupture versus flaw size is called a "fragility curve" which can be combined with a probable flaw distribution to estimate the cumulative probability of a nozzle failure in the time period up to the time of the recent inspections.
- 3. CRACK GROWTH. The flaw distribution discussed in 1 above represents a snapshot at the time of the inspections. In order to make meaningful comparisons of future
probabilities of rupture under various inspection scenarios, estimates of the probability of future flaw growth must be made. The deterministic results of Section 7 of the main body of this report are used, as discussed in Section E.4, to produce a series of flaw distributions similar to those discussed in 1 above, but which increase with time. These time-varying crack size distributions are used in conjunction with the fragility curve to produce estimates of the probability of rupture versus time into the future (at six month intervals).

The analysis process is illustrated in Figure E-1. A typical flaw distribution (Weibull) at the time of the recent inspections is illustrated by the curve on the left hand side of the graph. This curve is estimated to shift to the right due to crack growth during each six-month period between outage seasons, as illustrated by the series of parallel dashed curves in the figure. Finally, the fragility curve is illustrated by the red curve on the right hand side of the figure. Figure E-1b is a zoom-in view of the low probability region of the same graph.

The failure probability is actually simulated by a process of Monte Carlo sampling from a flaw distribution and the fragility curve, as discussed in detail in Section E.5. Each time a trial yields a flaw size from the flaw distribution that is greater than the critical flaw size from the fragility curve; it represents a predicted nozzle rupture. The number of predicted ruptures divided by the total number of trials performed represents the cumulative probability of rupture (per nozzle) up to the time of the flaw distribution. The Monte Carlo simulation process is performed for each time period for which a flaw distribution has been determined, and the incremental probabilities of failure (per nozzle, per time interval) are computed by subtracting the cumulative probabilities for adjacent time intervals. Finally, the incremental probabilities are multiplied by the number of nozzles, divided by the number of plants, and then combined by calendar year to produce the common units of probability per reactor-year for various inspection scenarios.

E.2 Flaw Distributions

The flaw size distribution is estimated from inspection data.

E.2.1 Inspection Data

A compilation of the inspection data used to develop the flaw distributions is provided in Table E-1. There are a total of 50 data points listed, in approximate chronological order, with a total of 7 axial indications (or leaks), and 7 circumferential indications. The early data (2005 and earlier) are legacy data that preceded MRP-139 inspections, and in some cases include non-pressurizer nozzles such as hot and cold leg drains, as well as international data. The 2006 and 2007 data are from inspections performed in response to MRP-139. The indication data were confirmed in each case with utility ISI personnel. The circumferential indications include the three Wolf Creek indications observed in Fall-2006.

The data were updated to reflect recent inspections performed in Spring 2007. These include a total of ten new data points, nine clean and one moderate-sized circumferential indication. These new data did not indicate any new trends that weren't apparent from the prior data.

Figure E-2 presents a locus plot of the data in which crack length as a percentage of circumference is plotted along the abscissa, and crack depth as a percentage of thickness on the ordinate. Axial indications plot along the vertical axis (l/circumference = 0) in this plot, with leaking flaws plotted at a/t = 100%. Circumferential indications plot at non-zero values of ℓ /circumference, at the appropriate a/t. Clean inspections are plotted randomly in a 10% box near the origin, to give some indication of inspection uncertainty.

Also shown on this plot are loci of critical flaw sizes from the fragility curve discussion in Section E.3. 50^{th} and 99.9^{th} percentile plots are shown. It is seen from this figure that all of the flaw indications detected are far below the sizes needed to cause a rupture. However, this analysis must address the small but finite probability that larger flaws may exist in uninspected nozzles, plus the potential for crack growth during future operating time until all the nozzles are inspected (or mitigated).

There exist a total of about 280 Alloy 82/182 pressurizer nozzles in 50 PWRs affected by this concern. Under the industry inspection program in accordance with MRP-139 (and approved deviations) 83 nozzles were inspected or mitigated, by the end of 2006, at the time that the Wolf Creek indications were observed. An additional 74 were performed in Spring 2007, and 70 are scheduled for Fall 2007. (Note that many of the nozzles were preemptively mitigated (via weld overlays) without inspection prior to the overlay, and the post-overlay inspections cover a limited volume, explaining why the numbers of inspections in Table E-1 are much less than these totals.) The issue being addressed in this report concerns a total of 51 nozzles in 9 plants for which inspections or mitigation are not currently planned until Spring 2008 under the industry program.

E.2.2 Statistical Fits to the Data

The "Criticality Factor" (CF = percentage of cross section lost to the assumed crack) was computed for each of the nozzles in Table E-1 (last column), by multiplying the reported indication circumferential lengths times their depths, and dividing the product by the approximate cross sectional area of the nozzle at the flaw location. CF corresponds, approximately, to the percentage of circumferential cross sectional area that is lost due to the observed indications, assuming that they are cracks with a depth equal to their maximum reported depth over the entire length of the indication. (Section E.3 contains test data and associated discussion that confirm the appropriateness of CF as a parameter to characterize nozzle failure.) A cumulative distribution of criticality factors was then developed, by sorting the data from smallest to largest CF and assigning each data point a rank of i/N (where i = the inverse rank of each data point and N = the total number of data points, 50). The individual data points are listed in Table E-2, which also shows the estimated cumulative probability (i/N) of an indication exceeding each CF value. Note that Table E-2 only lists the eight nozzles that had circumferential indications. The other 42 nozzles had a CF of zero (clean or axial indications only) and were not included in curve fitting the distribution, although N was assigned as the total number of data points (50).

Weibull, Log-Normal and Exponential fits to the data of Table E-2 are shown on a log-log scale in Figure E-3. The fits to the data were made by fitting a straight line to the data after transforming it to scales that would result in a straight line if the random variable had that distribution (equivalent to plotting it on probability paper appropriate for each distribution type).

The resulting distributions and the data are shown in Figure E-3. Table E-3 summarizes the parameters of the fits.

From Figure E-3 it is seen that the Weibull and Log-Normal distributions are excellent fits within the range of the actual data (up to ~12% CF). The exponential distribution fit is not as good, but still reasonable. Figure E-3 also shows the distributions extrapolated out to large flaw sizes, from which it is seen that there are substantial differences between the distributions at large sizes, even though they all agree well in the range of the data. For this reason, the probabilistic analysis will not be used to estimate absolute failure probabilities, but rather to compare relative probabilities for various inspection scenarios, under a common set of assumptions. Results of Monte Carlo simulations for the three distribution types are presented in Section E.5.

E.3 Critical Flaw Size Distribution

There are two sources of statistical variability in the critical flaw size calculations. One is the variability in the applied loads for the different plants and nozzle types, and the second relates to uncertainty in ability to predict critical flaw size (CF%) when the applied loading is known. These two sources of variability are addressed separately and then combined statistically to produce a single fragility curve as discussed in the following subsections.

E.3.1 Applied Load Distribution

Applied loads for the 51 PWR pressurizer nozzles scheduled for Spring 2008 inspections, plus the Wolf Creek pressurizer nozzles, have been compiled as part of the advanced FEA project. Figure E-4 presents a summary of this compilation, in terms of ASME Code membrane and bending stress levels (Pm and Pb) computed using standard Code formulas and nozzle dimensions for each plant. The loads include pressure and dead weight primary loading plus sustained thermal expansion (Pe) loads for some nozzles, which are secondary or displacement controlled. Analyses were performed in the advanced FEA project, as documented in Appendices B and C, which demonstrate that secondary loads do not need to be included in critical flaw size computations for the surge nozzles, thus justifying the exclusion of both thermal expansion and stratification loads on those nozzle types. However, such analyses were not performed for the other nozzle types (spray, safety and relief) so sustained thermal expansion loads are included in the critical flaw size computations for these nozzle types

Safe shutdown earthquake (SSE) loads are also included in Figure E-4, as indicated by the dashed lines in the plot. For the probabilistic evaluation, the load data were analyzed separately, with and without SSE loads, permitting seismic loads to be considered with a reduced probability of occurrence (typically 0.001 per year or less) relative to normal operating loads.

The data in Figure E-4 were sorted by increasing stress level, and were found to be well fit by Log-Normal statistical distributions, as illustrated in Figures E-5 and E-6 for Pm + Pb, with and without SSE loads, respectively. The fitting accuracy and parameters of the Log-normal fits are included on the figures.

E.3.2 Compilation of Full Scale Pipe Tests

The statistical fits of Figures E-5 and E-6 can be sampled to provide estimates of the distribution of applied loading on the pressurizer nozzles in the study. However, even if the applied loading were known with complete accuracy, uncertainty exists in our ability to predict the critical flaw size, in terms of CF%. To help characterize this uncertainty, a review was performed of test data from the NRC-sponsored Degraded Piping Program conducted at Battelle Columbus Laboratories [E-2, E-3]. Approximately 60 full scale pipe tests were conducted in this program, of pipes containing three types of circumferential defects: through-wall cracks, surface cracks, and complex cracks (see Figure E-7). Pipe sizes ranged from 4" to 42" and loadings included 4point bending, combined bending + internal pressure and pure axial load. The majority of the pipes tested were in the 6" to 16" range which is directly relevant to the pressurizer nozzles being evaluated. Pipe materials in the tests included 304 stainless steel, Alloy 600 and Carbon Steel, but no pipes containing A-82 or 182 weldments were tested. Therefore the results of the predominantly base material pipe tests must be translated to DMWs on the basis of relative material properties for use in this evaluation. Fortunately, the piping materials used in the program were extensively characterized in terms of tensile properties and fracture toughness (J-R curves). Recent data also exists on the J-R properties of a large A-182 weldment, which can be used for comparison to the test materials.

Figure E-8 is a plot of test data from 31 of the pipe tests, performed on Austenitic materials only (304SS plus A-600). The data are plotted in terms of maximum loading achieved in the pipe tests (i.e. failure load) vs. % of pipe cross section cracked (CF %). The maximum load is plotted in terms of applied stress at the cracked cross section normalized by the ASME Section III design allowable stress for the appropriate test material (304 SS or A-600) and temperature, (Pm + Pb) / Sm.

The large majority of the tests in Figure E-8 were conducted under bending loading (Pb) only, and those tests yielded a very consistent trend. However, in order to include pipes tested under combined membrane plus bending (Pm + Pb), and since the applied nozzle loadings in Section E.3.1 include both membrane and bending loads, a correction factor was developed based on net section collapse analyses plus data from similar pipes tested under varying amounts of membrane and bending stress. Specifically, tests were conducted for some flaw geometries (surface flaws and WOL tests) under combined pressure plus bending loads. These were complemented by net section collapse analyses of the other flaw types (thru-wall and complex flaw geometries) to calculate the effective increase in total loading as a function of the relative fraction of Pm versus Pb in the test/analysis. The following correction factor for membrane stress was obtained:

$(Pm + Pb)/Sm_{adjusted} = [(Pm + Pb)/Sm] \times [0.9817 + 0.4311 \times Pm/(Pm + Pb)]$

which varies from ~1 for pure bending loading (Pm/(Pm + Pb) = 0) to ~1.4 for pure membrane loading (Pm/(Pm + Pb) = 1). Figure E-15 presents a plot of this correction factor, and the associated test and analysis data, which demonstrates an excellent correlation with the data.

Plotting the test results in this manner yields a monotonic trend with relatively little scatter, indicating that CF% is a reasonable parameter for characterization of the effect of cracking on

pipe failure load, for the pipe and crack geometries tested, which are directly relevant to the subject nozzles. A power law fit of the data is shown on Figure E-8, which exhibits very good correlation and relatively little scatter for test data of this type. The equation and correlation coefficient of the fit are as follows:

$$(Pm + Pb)/Sm = 0.4061 (CF)^{-1.4613}$$

 $R^2 = 0.8988$

E.3.3 Development of Fragility Curve

In order to develop a statistical distribution for this curve, residuals were calculated based on the difference between the actual CF for each data point and that predicted by the power law fit (CF - CF_{predicted}). The residuals were then sorted from lowest to highest, and were found to be reasonably represented by a normal distribution, as illustrated in Figure E-9. CF% was selected as the dependent variable in this correlation, since applied loading is the independent variable in the analysis (i.e. applied loads determined from the plant loading distributions are used to determine critical CF% from Figures E-8 and E-9).

Consistent with the advanced FEA project, the applied loads are first multiplied by a Z-factor [E-4] before entering Figures E-8 and E-9 which accounts for potentially lower toughness of Alloy-182 weldments relative to the austenitic base materials tested in the pipe tests. J-Resistance testing of a typical Alloy-182 weldment showed little or no reduction in toughness relative to the pipe test materials [E-4]. Sm for stainless steel base metal at pressurizer operating temperature was used to normalize the plant loads.

The final step in developing the fragility curve was to perform Monte Carlo sampling from the load distribution of Figure E-5, and then independently sample the critical flaw size distribution of Figures E-8 and E-9 for critical CF % for each load. Consideration was given to occasionally sampling from the SSE distribution of Figure E-6 (e.g. once in every 1000 simulations), however, the two distributions are so close that this was judged to have an insignificant effect. 1000 samples were performed, resulting in the critical flaw size distribution shown in Figure E-10. Both the sampling results and a Log-Normal fit to the distribution are plotted. The Log-Normal fit was found to give a very accurate representation of the fragility curve distribution. Parameters of the Log-Normal fit are also listed in Figure E-10.

One anomaly exists in the fragility curve in Figure E-10 which requires explanation. The curve yields a probability of failure of less than one for CF = 100%, which is physically impossible. This effect results from sampling the tails of the two distributions, which occasionally yields unrealistically small applied loads or unrealistically high critical flaw sizes (For example, the right hand side of the power law curve in Figure E-8 doesn't go through zero.) However, this anomaly is corrected in the Monte Carlo analyses of Section E.5 by discarding and re-sampling any trials in which the critical flaw size is predicted to be greater than 100%.

E.4 Crack Growth

E.4.1 Summary of Advanced FEA Results

The advanced FEA analyses addressed a total of 53 cases with variations of each resulting in over 100 individual crack growth analyses. Over half of the analyses demonstrated stable crack arrest prior to penetrating through-wall or reaching critical size. The remainder exhibited varying degrees of crack growth. The first 20 cases were denoted base cases, and include cases that envelope all geometries and loads for the 51 Spring 2008 pressurizer nozzles. The 20 base cases and their resulting crack growth rates, in terms of CF% per year are summarized in Table E-4. (Note that a total of 22 analyses are actually reported in the table since two cases were run with two sets of weld residual stresses each.) The crack growth rates naturally divide into two regimes: crack growth from initial assumed flaw size until through wall (TW) penetration, denoted "Rate1" in the table, and crack growth following TW penetration, denoted "Rate2". Rate2 can be seen to be on average about an order of magnitude greater than Rate1, indicating significant acceleration in crack growth once the assumed crack breaks through and becomes through wall.

Another observation from Table E-4 is that all but two base cases exhibit relatively small pre-TW crack growth rates (~1%/yr < Rate1 < 3.5%/yr) with the exception of Case 6 (9.85%/yr) and Case 17 (14.97%/yr). A similar trend is seen in the post-TW growth rates (Rate2), albeit at much higher rates. Thus for the geometries enveloped, the high crack growth rates predicted for cases 6 and 17 are relatively rare. The remainder of the cases (21 through 53) for the most part started with cases 6 and 17 and looked at the effect of various analysis parameters and assumptions on these bounding cases. For this reason, it was judged not appropriate to include these remaining cases in the statistical distribution of crack growth rates, since they would bias the distribution very much to the high side. Instead, only the base cases were used, but the spread in the distributions was combined with the experimental scatter in crack growth rates from MRP-115 [E-5], as described in the next section.

E.4.2 Adaptation to Probabilistic Analysis

The base case crack growth results identified in Section E.4.1 were used to define statistical distributions of crack growth rates for the probabilistic analysis. Figure E-11 presents the sorted data for pre- and post-penetration crack growth rates plotted versus cumulative probability. Bilinear fits to the data were developed for the two regions of each of the curves. These bilinear distributions properly characterize the dichotomy observed in the FEA results (i.e. about an 80% probability that the crack growth rate will be relatively small, and about a 20% probability of large crack growth rates as observed in Cases 6 and 17). The high portion of the crack growth distributions also extrapolate out to even higher crack growth rates than those predicted for Cases 6 and 17, thereby covering to some extent the remaining sensitivity cases that weren't included in the distribution.

The distributions in Figure E-11 do not include the scatter in the crack growth rate itself. All the base case computations used the 75^{th} percentile of the MRP-155 crack growth rate distribution that describes material crack growth rate scatter (Figure E-12).

The material crack growth rate scatter needs to be combined with the above analytical distributions to obtain the overall statistical description of the crack growth rate. This was accomplished by Monte Carlo simulation employing the following steps:

- 1. Sample from the bilinear distributions of Figure E-11.
- 2. Divide the sampled value by the ratio of the 75th to the 50th percentile of the MRP-115 distribution of Figure E-12(i.e. adjust to the median).
- 3. Sample from the MRP distribution (with a median of 1 and lognormal shape parameter of 0.6069) to determine a multiplier for the analytical crack growth rate.
- 4. Multiply the sample from Step 2 by the sample from Step 3.

This provides a set of samples from which a cumulative distribution can be derived. The cumulative distribution for pre-TW penetration is shown in Figure E-13 on lognormal scales (as data points) along with a lognormal distribution that was fit to the data. The line is seen to provide a good description to the Monte Carlo results. The constants describing the line are the parameters of the lognormal distribution of crack growth rate for pre-penetration.

A similar analysis was performed for the post-TW penetration data. Figure E-14 provides the corresponding results.

Note that, for purposes of this analysis, it was not considered necessary to include new crack initiations or multiple crack initiations during the evaluation periods. These are considered to be adequately addressed by starting with the empirical nozzle flaw distributions derived in Section E.2.

E.5 Monte Carlo Analysis

Monte Carlo simulation was used to generate results of the probability of a nozzle failure as a function of time.

E.5.1 Methodology

The following steps were used in each trial of the Monte Carlo simulation.

- 1. SAMPLE CRACK SIZE (CF%) from one of the flaw size distributions (Weibull, Log-Normal, Exponential) developed in Section E.2. Truncate the CF at 100% (if the sampled CF is greater than 100%, then discard it and sample again). Separate Monte Carlo analyses were conducted for each of the distribution types, and results are presented for each.
- 2. SAMPLE PRE-PENETRATION CRACK GROWTH RATE from a log-normal distribution using the same percentile as the sampled crack size (based on the observation that the larger cracks likely were associated with high crack growth rates, either due to material, high loads, or both). This crack growth rate was used for crack sizes up to CF = 40%, which corresponds to the mean crack size at through-wall penetration in Table E-4.

- 3. SAMPLE POST-PENETRATION CRACK GROWTH RATE from a lognormal distribution using an independent sample. This crack growth rate was used to grow cracks beyond CF=40%.
- 4. SAMPLE FRAGILITY CF. Truncate the Fragility CF at 100% (if the sampled Fragility CF is greater than 100%, then discard it and sample again).
- 5. GROW THE CRACKS in steps of 6 months at a time for up to 18 months. The prepenetration crack growth rate is used for cracks of size less than 40%. The postpenetration crack growth rate is used once the crack size exceeds 40%. (If the initial size of the sampled crack is greater than 40 %, it will always grow at the post-penetration rate.) Failure at a given time step (0, 6, 12, 18 months) is defined as the cracking CF exceeding the fragility CF.
- 6. CHECK FOR CRACK ARREST. Probability of arrest is an input, and only applies to sampled cracks of initial size that are smaller than 40% CF. If the sampled crack is less than 40%, a random sample is taken from the uniform distribution. If this sample is less than the probability of arrest, then that crack does not grow beyond 40% CF. This crack could still cause a failure if the sampled Fragility CF is less than the cracking CF. If the sampled crack size is greater than 40%, arrest is not assumed. Based on the results of the advanced FEA crack growth analyses, a probability of arrest = 0.57 was used in the Monte Carlo analyses.
- 7. THE PROBABILITY OF FAILURE is computed as the number of failures divided by the number of trials.

E.5.2 Cases Analyzed

Monte Carlo results were generated for all three distribution types (Weibull, exponential, lognormal) for times up to the present and for 6, 12, and 18 months into the future. Since the majority of the inspection data reported in Table E-1 were from 2006, and the Wolf Creek inspection findings were observed in Fall 2006, the inspection data were treated as a snapshot in time at end of the Fall 2006 outage season, and that date was assumed to be the present, or time = 0 in the time-based probability of failure results.

E.5.3 Results

The results of the Monte Carlo simulations are presented in Table E-5. 10^7 trials were used in each case. The cumulative probabilities are directly from the Monte Carlo simulation and are given for each of the three distribution-types. The incremental probabilities are the differences in the cumulative probabilities for each six-month time span. These correspond to the probability of a nozzle rupture (per nozzle) during each six-month time interval.

The number of nozzles column corresponds to the number of remaining, PWSCC-susceptible pressurizer nozzles that will not have been inspected or mitigated at the end of each outage season, assuming that the industry inspection plans are implemented. The next column reflects the number of plants containing those uninspected/unmitigated nozzles. The probability of a nozzle failure in the time increment is given by the expression $P_{noz}=1-(1-p_1)^N$, where p_1 is the incremental failure probability for a single nozzle and N is the number of nozzles. The per plant

probability of a nozzle failure is then obtained by dividing by the number of plants in which those nozzles exist.

It may be observed from Table E-5 that the incremental probabilities of nozzle failure are remaining about constant for each of the six month intervals, especially for the analyses performed with the Weibull and lognormal flaw distributions (which from Figure E-2 were the better fits of the data). The analyses with the exponential distribution show some increase in incremental probability of failure versus time, but those start at much lower present values (time = 0), since the exponential fit produced less conservative extrapolations of probabilities of larger flaw sizes. Since the numbers of susceptible nozzles and plants are being removed from the population at a steady rate, the industry inspection plan results in an essentially constant probability of a nozzle failure per time interval, until the time when all nozzles will have been inspected or mitigated, at the end of the Spring 2008 outage season.

E.6 Conclusions

The following observations are offered based on the results of the probabilistic evaluation presented in Table E-5:

- Pressurizer nozzle failure probabilities (per plant, per six months) for the Spring-08 Plants are approximately the same as what has existed in PWRs due to PWSCC susceptible pressurizer nozzles during the Fall and Spring of 2007 (on the order of 4×10^{-3} per plant, per six months). During 2007, this failure probability existed for the entire year, resulting in an estimated failure probability (per plant per year) of ~8 x 10⁻³. For 2008, this probability will exist for less than six months; so on a per reactor-year basis, the failure probability will actually be a factor of two smaller in 2008.
- The absolute failure probabilities resulting from this study are greater than generally accepted LOCA frequencies. However, as stated in Section E.2, the results of the probabilistic evaluation are not intended to yield absolute probabilities for comparison to fixed licensing limits, but rather, are intended to provide estimates of the relative effects of various inspection programs, such as accelerating the Spring 2008 exams versus not accelerating them. Furthermore, these results assume no leakage or plant response to leakage. For comparison to accepted LOCA probabilities, they need to be factored by the probability of non-Leak-Before-Break (or failure to react to leakage), which is expected to be very small, given the increased attention to the PWSCC concern in these particular plants and nozzles, and the associated confirmatory action commitments by the utilities relative to leakage monitoring and immediate plant actions if leakage is detected..
- Based on the advanced FEA analyses performed in the body of this report, plus the above referenced confirmatory action commitments, it is extremely unlikely that leaks from these nozzle locations would go undetected for a sufficient duration and of sufficient magnitude that a break could occur before operator action to shut the plant down. A total of 108 crack growth analysis cases were performed in the main sensitivity matrix and all 108 cases showed either stable crack arrest or crack leakage and stability results that satisfied agreed-upon evaluation criteria. In most cases, the results showed large margins relative to those criteria. Many of the cases were conservative sensitivity studies that utilized limiting base

case results as their starting point, and thus the 108 case matrix (plus several supplemental cases that were added) represent a conservatively biased sample of the actual nozzle population. On this basis, a reasonable estimate of the probability of a leak going undetected to the point of pipe rupture in one of the subject nozzles is estimated to be on the order of 1/500 (assuming that an unbiased matrix of the actual nozzle population would add an additional 400 arrests or acceptable cases). Applying this probability to the probability of nozzle rupture, assuming no LBB, for the Spring 2008 plants of 1.6 x 10^{-3} to 4 x 10^{-3} (Table E-4) results in a combined probability of pipe rupture of 3.2 x 10^{-6} to 8 x 10^{-6} per reactor-year for the nine Spring 2008 plants.

On the basis of these evaluation results, it is concluded that there is no significant benefit, in terms of reduced nozzle failure probability, to accelerating the originally scheduled Spring 2008 inspections. The probability of nozzle failure, assuming no leak before break, is predicted to be less for the Spring 2008 plants than it was, on a per-plant-year basis, for the plants that inspected/mitigated in Spring or Fall of 2007. The results of this study are complementary to the advanced FEA program discussed in the body of the report, in that they provide an indication of what to expect for the very small number of cases in which leak-before-break cannot be demonstrated.

E.7 References

- E-1. Materials Reliability Program: Primary System Piping Butt Weld Inspection and Evaluation Guidelines (MRP-139), EPRI, Palo Alto, CA: 2005. 1010087.
- E-2. Summary of Technical Results and Their Significance to Leak-Before-Break and In-Service Flaw Acceptance Criteria, NUREG/CR-4082, Volume 8, March 1984 - January 1989.
- E-3. *Pipe Fracture Encyclopedia*, U.S. NRC, 1997 (A collection of NUREG Reports and Data Files from the DP2 and other programs distributed on CDs).
- E-4. G. Wilkowski, H. Xu, D.-J. Shim, and D. Rudland, "Determination of the Elastic-Plastic Fracture Mechanics Z-factor for Alloy 82/182 Weld Metal Flaws for Use in the ASME Section XI Appendix C Flaw Evaluation Procedures," PVP2007-26733, Proceedings of ASME-PVP 2007: 2007 ASME Pressure Vessels and Piping Division Conference, San Antonio, TX, 2007.
- E-5. Materials Reliability Program (MRP) Crack Growth Rates for Evaluating Primary Water Stress Corrosion Cracking (PWSCC) of Alloy 82, 182, and 132 Welds (MRP-115), EPRI, Palo Alto, CA: 2004. 1006696.

Plant	Inspection Date	Nozzle	OD (in)	Thick (t, in)	Type of Indication	Indication Depth (a, in)	Indication Length (I, in)	a/t	l/circ	Criticality Factor
Tihange 2	2002	Surge	14	1.4	Axial	0.600	0.000	43%	0%	0.00%
TMI	2003	Surge	12	1.3	Axial	0.585	0.000	45%	0%	0.00%
Tsuruga	2003	Relief	6	1	Axial	1.000	0.000	100%	0%	0.00%
Tsuruga	2003	Safety	6	1	Axial	0.900	0.000	90%	0%	0.00%
Calvert 2	2005	CL Drain	2	0.56	Circ	0.056	0.628	10%	10%	1.00%
Calvert 2	2005	HL Drain	2	0.56	Axial	0.392	0.000	70%	0%	0.00%
DC Cook	2005	Safety	8	1.4	Axial	1.232	0.000	88%	0%	0.00%
Farley 2	2005	Safety	8	1.1	Clean	0.000	0.000	0%	0%	0.00%
Farley 2	2005	Spray	6	0.83	Clean	0.000	0.000	0%	0%	0.00%
Calvert 1	2006	HL Drain	2.875	0.54	Circ	0.100	0.450	19%	5%	0.92%
Calvert 1	2006	Relief	6.0675	1.3	Axial	0.100	0.000	8%	0%	0.00%
Calvert 1	2006	Surge	12.75	1.6	Circ	0.400	2.400	25%	6%	1.50%
Davis Besse	2006	CL Drain	2	0.56	Axial	0.056	0.000	7%	0%	0.00%
D-B	2006	Relief	4.5	0.8125	Clean	0.000	0.000	0%	0%	0.00%
D-B	2006	Safety	4.5	0.8125	Clean	0.000	0.000	0%	0%	0.00%
D-B	2006	Safety	4.5	0.8125	Clean	0.000	0.000	0%	0%	0.00%
D-B	2006	Spray	5.125	0.625	Clean	0.000	0.000	0%	0%	0.00%
D-B	2006	Surge	11.5	1.125	Clean	0.000	0.000	0%	0%	0.00%
Prairie Is.	2006	Surge	15	1.5	Clean	0.000	0.000	0%	0%	0.00%
SONGS 2	2006	Safety	8	1.4	Axial	0.420	0.000	30%	0%	0.00%
SONGS 2	2006	Safety	8	1.4	Axial	0.420	0.000	30%	0%	0.00%
SONGS 2	2006	Safety	8	1.4	Clean	0.000	0.000	0%	0%	0.00%
SONGS 2	2006	Spray	5.5	0.75	Clean	0.000	0.000	0%	0%	0.00%
SONGS 3	2006	Relief	8	1.1875	Clean	0.000	0.000	0%	0%	0.00%
SONGS 3	2006	Safety	8	1.1875	Clean	0.000	0.000	0%	0%	0.00%
SONGS 3	2006	Safety	8	1.1875	Clean	0.000	0.000	0%	0%	0.00%
SONGS 3	2006	Spray	5.5	0.75	Clean	0.000	0.000	0%	0%	0.00%
SONGS 3	2006	Surge	13	1.437	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Relief	7.75	1.29	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Safety	7.75	1.29	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Safety	7.75	1.29	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Safety	7.75	1.29	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Spray	6	0.9	Clean	0.000	0.000	0%	0%	0.00%
Watts Bar	2006	Surge	15	1.5	Clean	0.000	0.000	0%	0%	0.00%
Wolf Creek	2006	Relief	7.96	1.32	Circ	0.340	11.500	25.8%	46%	11.85%
Wolf Creek	2006	Safety	7.96	1.32	Circ	0.297	2.500	22.5%	10%	2.25%
Wolf Creek	2006	Safety	7.96	1.32	Clean	0.000	0.000	0%	0%	0.00%
Wolf Creek	2006	Safety	7.96	1.32	Clean	0.000	0.000	0%	0%	0.00%
Wolf Creek	2006	Spray	6	0.9	Clean	0.000	0.000	0%	0%	0.00%
Wolf Creek	2006	Surge	15	1.45	Circ	0.465	8.750	32.1%	19%	5.95%
Farley 2	2007	Safety	8	1.1	Clean	0.000	0.000	0%	0%	0.00%
Farley 2	2007	Safety	8	1.1	Clean	0.000	0.000	0%	0%	0.00%
Farley 2	2007	Safety	8	1.1	Clean	0.000	0.000	0%	0%	0.00%
Farley 2	2007	Safety	8	1.1	Clean	0.000	0.000	0%	0%	0.00%

Table E-1 Plant Data used in Flaw Distribution

Plant	Inspection	Nozzle	OD	Thick	Type of	Indication Depth	Indication Length	a/t	l/circ	Criticality
	Date		(in)	(t, in)	Indication	(a, in)	(I, in)			Factor
Farley 2	2007	Spray	6	0.83	Clean	0.000	0.000	0%	0%	0.00%
Farley 2	2007	Surge	15	1.52	Circ	0.500	3.000	33%	6%	2.12%
Calvert 2	2007	Safety	8	1.1875	Clean	0.117	1.886	0%	0%	0.00%
Calvert 2	2007	Safety	8	1.1875	Clean	0.052	1.681	0%	0%	0.00%
Calvert 2	2007	Spray	5.5	0.75	Clean	0.066	1.475	0%	0%	0.00%
Calvert 2	2007	Surge	13	1.437	Clean	0.030	3.107	0%	0%	0.00%

Table E-1Plant Data used in Flaw Distribution (cont'd)

 Table E-2

 Circumferential Indications from Table E-1 Including Estimates of Cumulative Probability

CF	Rank, i	F, i/N*	1-F
0.92%	7	0.14	0.86
1.00%	6	0.12	0.88
1.50%	5	0.1	0.9
2.09%	4	0.08	0.92
2.25%	3	0.06	0.94
5.95%	2	0.04	0.96
11.85%	1	0.02	0.98

* N = 51

	CF% Initial	CF% @ TW	Time to TW (yrs)	Rate1C F%/yr	CF% @ 1GPM	Time (days)	Time to1 GPM (yrs)	CF% @ LF =1.2	Time (yrs)	Comb Time (yrs)	Rate2 CF%/yr
	10.00%	40.00%	17.4	1.72%	46.60%	114	0.312	56.80%	0.299	0.611	27.50%
	10.00%	39.50%	21.3	1.38%	47.00%	142	0.389	57.40%	0.323	0.712	25.13%
Ľ.,	10.00%	38.30%	26.3	1.08%	47.20%	182	0.499	58.00%	0.342	0.841	23.42%
Ľ.,	10.00%	40.00%	18	1.67%	46.20%	107	0.293	55.80%	0.307	0.600	26.33%
Ľ.,	10.00%	38.10%	25.7	1.09%	46.60%	180	0.493	57.40%	0.375	0.868	22.22%
Ĺ	10.00%	43.50%	3.4	9.85%	47.10%	31	0.085	52.90%	0.112	0.197	47.65%
Ŀ	10.00%	44.00%	10.5	3.24%	49.10%	70	0.192	57.30%	0.195	0.386	34.43%
	10.00%	39.90%	13.4	2.23%	45.90%	94	0.258	55.30%	0.271	0.529	29.12%
	10.00%	36.40%	32.2	0.82%	47.00%	229	0.627	58.60%	0.395	1.022	21.72%
	10.00%	38.90%	21.2	1.36%	49.70%	195	0.534	58.20%	0.200	0.734	26.29%
Ľ	10.00%	37.80%	25.3	1.10%	50.60%	260	0.712	58.70%	0.200	0.912	22.91%
	10.00%	43.60%	10.5	3.20%	50.70%	110	0.301	57.50%	0.132	0.433	32.11%
	10.00%	42.70%	13.6	2.40%	51.20%	130	0.356	58.20%	0.148	0.504	30.75%
						Arres	st				
						Arres	st				
						Arres	st				
						Arres	st				
	6.03%	24.00%	1.2	14.97%	24.30%		0	33.10%	0.096	0.096	94.90%
						Arres	st				
	10.00%	49.90%	11.5	3.47%	52.30%		0	59.10%	0.118	0.118	78.09%
						Arres	st				
						Arres	st				
	9.74%	39.77%	16.8	3.31%	46.77%		0.337	55.62%	0.234	0.571	36.17%
	1.03%	5.53%	8.8	3.92%	6.55%		0.214	6.43%	0.102	0.288	21.66%
<u> </u>	10.00%	49.90%	32.2	14.97%	52.30%		0.712	59.10%	0.395	1.022	94.90%
	6 03%	24.00%	1.2	0.82%	24.30%		0.000	33.10%	0.096	0.096	21.72%

 Table
 E-3

 Summary of Base Case Crack Growth Results from Advanced FEA Project

Distribution Type	Complementary Cumulative Distribution	Values of Parameters	R²
Exponential	$Ce^{-x/b}$	1/b = 16.293, <i>C</i> = 0.1225	0.9052
Weibull	$e^{-(x/\eta)^{\beta}}$	β=0.2543, η=0.000539	0.9704
Log-Normal	$\frac{1}{2}\operatorname{erfc}\left[\frac{\ln(x/m)}{\sigma\sqrt{2}}\right]$	<i>m</i> = 0.0040365, = 2.775745	0.9704

Table E-4Parameters of the Fitted Distributions

Table E-5Results of Monte Carlo Simulation

Distribution/ Outage Season	Time (mos.)	Tìme Incr. (mos.)	Cum. Prob.	Incr. Prob. (p _i)	# Nozzles (N)	# Plants (NP)	Nozz Pro	le Failure bability
	·······						Total*	per Plant**
Weibull								
Fall-06	0		6.4380E-04		278	50		
Spring-07	6	6	1.3855E-03	7.42E-04	195	34	0.1347	0.0040
Fall-07	12	6	2.1573E-03	7.72E-04	121	21	0.0892	0.0042
Spring-08	18	6	2.8700E-03	7.13E-04	51	9	0.0357	0.0040
•								
Log Normal								
Fall-06	0		8.5860E-04		278	50		
Spring-07	6	6	1.7445E-03	8.86E-04	195	34	0.1587	0.0047
Fall-07	12	6	2.5585E-03	8.14E-04	121	21	0.0938	0.0045
Spring-08	18	6	3.2759E-03	7.17E-04	51	9	0.0359	0.0040
							1	
Exponential								
Fall-06	0		2.1000E-06		278	50		
Spring-07	6	6	3.1500E-05	2.94E-05	195	34	0.0057	0.0002
Fall-07	12	6	1.5300E-04	1.22E-04	121	21	0.0146	0.0007
Spring-08	18	6	4.4470E-04	2.92E-04	51	9	0.0148	0.0016
*Total Failur **Failure Prob.	e Prob. = 1 Per Plant =	- (1-p _i) ^N Total Prob	./NP					·





 a) Complementary Cumulative Distribution of Crack Area Fraction at Different Times, along with Complementary Cumulative Distribution of Critical Crack Area Fraction (CF, %)
 b) Enlargement of Low Probability Region of Figure E-1a

Appendix E: Evaluation of Pressurizer Alloy 82/182 Nozzle Failure Probability



Figure E-2 Plot of Indication Sizes along with 50th and 99.9th Percentiles of Fragility Curve



Figure E-3 Complementary Cumulative Distributions of CF Showing Each of the Three Fits along with the Data



Figure E-4

Compilation of Applied Stresses (Pm + Pb) in 51 Pressurizer Nozzles scheduled for Spring 2008 Inspection plus Wolf Creek, with and without SSE seismic stresses. Data for Spray, safety and relief nozzles include thermal expansion loads, data for surge nozzles include primary stresses only.







E-18



Log Normal Fit w/SSE

Figure E-6 Log-normal Fit and Parameters of Applied Load Distribution without Seismic Loads



Figure E-7

Illustration of Circumferential Flaw Types Tested in Degraded Piping Program Full Scale Pipe Tests





Figure E-8 Plot of Full Scale Pipe Test Data from Degraded Piping Program. Austenitic Materials Only; Various Flaw Types









Appendix E: Evaluation of Pressurizer Alloy 82/182 Nozzle Failure Probability

Figure E-10 Resulting Fragility Curve and Associated Log-Normal Fit

















Export Control Restrictions

Access to and use of EPRI Intellectual Property is granted with the specific understanding and requirement that responsibility for ensuring full compliance with all applicable U.S. and foreign export laws and regulations is being undertaken by you and your company. This includes an obligation to ensure that any individual receiving access hereunder who is not a U.S. citizen or permanent U.S. resident is permitted access under applicable U.S. and foreign export laws and regulations. In the event you are uncertain whether you or your company may lawfully obtain access to this EPRI Intellectual Property, you acknowledge that it is your obligation to consult with your company's legal counsel to determine whether this access is lawful. Although EPRI may make available on a case-by-case basis an informal assessment of the applicable U.S. export classification for specific EPRI Intellectual Property, you and your company acknowledge that this assessment is solely for informational purposes and not for reliance purposes. You and your company acknowledge that it is still the obligation of you and your company to make your own assessment of the applicable U.S. export classification and ensure compliance accordingly. You and your company understand and acknowledge your obligations to make a prompt report to EPRI and the appropriate authorities regarding any access to or use of EPRI Intellectual Property hereunder that may be in violation of applicable U.S. or foreign export laws or regulations.

The Electric Power Research Institute (EPRI), with major locations in Palo Alto, California; Charlotte, North Carolina; and Knoxville, Tennessee, was established in 1973 as an independent, nonprofit center for public interest energy and environmental research. EPRI brings together members, participants, the Institute's scientists and engineers, and other leading experts to work collaboratively on solutions to the challenges of electric power. These solutions span nearly every area of electricity generation, delivery, and use, including health, safety, and environment. EPRI's members represent over 90% of the electricity generated in the United States. International participation represents nearly 15% of EPRI's total research, development, and demonstration program.

Together...Shaping the Future of Electricity

Programs:

Nuclear Power Materials Reliability Program

© 2007 Electric Power Research Institute (EPRI), Inc. All rights reserved. Electric Power Research Institute, EPRI, and TOGETHER...SHAPING THE FUTURE OF ELECTRICITY are registered service marks of the Electric Power Research Institute, Inc.

Printed on recycled paper in the United States of America

1015400