

1B

APPROVED DESIGN MIX FORMULAS

G. A. T-2151G (3000) -4
 #57 Cement: 517 lbs.
 C. A.: 1800 "
 F. A.: 1237 "
 Dx: 4.0 ozs.
 Dtd.: 16.5 ozs.
 Water: 271 lbs.

G. A. T-2151G Mod. (3000) -4
 #57 Cement: 562 lbs.
 C. A.: 1800 "
 F. A.: 1220 "
 Dx: 4.0 ozs.
 Dtd.: 16.5 ozs.
 Water: 271 "

G. A. IM-5 (5000) -3
 #57 Cement: 625 lbs.
 C. A.: 1800 "
 F. A.: 1140 "
 Dx: 3.6 ozs.
 Dtd.: 21.0 ozs.
 Water: 276 lbs.

<p>IM-5 Mod. (5000) -3 #57 Cement: 632 lbs. C. A.: 1800 " F. A.: 1100 " Dx: 3.6 ozs. Dtd.: 21.0 ozs. Water: 275 lbs. - 33.1</p>	<p>APPROVED</p> <p>727550-2 (5000) -4 #57 Cement: 705 lbs. C. A.: 1800 " F. A.: 1080 " Dx: 4.5 ozs. Dtd.: 23.0 ozs. Water: 286 lbs.</p>	<p>USED FOR DOME</p> <p>727550-2 Mod. (5000) -4 #57 Cement: 752 lbs. C. A.: 1800 " F. A.: 1080 " Dx: 4.5 ozs. Dtd.: 23.0 ozs. Water: 286 lbs.</p>
---	--	--

IM-7 (5000 Chstt) -3
 #6 Cement: 825 lbs.
 C. A.: 1650 "
 F. A.: 1070 "
 Dx: 5.0 ozs.
 Dtd.: 25.0 ozs.
 Water: 335 lbs.

Darex (1500) -5

#6 Daratard
 Cement: 365 lbs.
 C. A.: 1700 "
 F. A.: 1180 "
 Dx: 1.3 ozs.
 Dtd.: 10.5 ozs.
 Water: 290 lbs.

IM-16 Mod. (1500) -5

#57 Cement: 413 lbs.
 C. A.: 1700 "
 F. A.: 1180 "
 Dx: 1.3 ozs.
 Dtd.: 10.5 ozs.
 Water: 290 lbs.

735001-4 1/2 (5000)

#7 Cement: 752 lbs.
 C. A.: 1650 "
 F. A.: 1185 "
 Dx: 4.5 ozs.
 Dtd.: 20 ozs.
 Water: 294 lbs.

0/11