

ATTACHMENT 1

Letter from C.R. Steinhardt (WPSC)

To

Document Control Desk (NRC)

Dated

August 28, 1996

Proposed Amendment 142a

Affected TS Pages:

TS 4.2-3

TS 4.2-4

TS 4.2-8

TS B4.2-5

F* Distance is the distance of the expanded portion of a tube which provides a sufficient length of undegraded tube expansion to resist pullout of the tube from the tubesheet. The F* distance is equal to 1.12 inches (plus an allowance for NDE uncertainty) and is measured downward from the bottom of the uppermost roll transition. The F* distance applies to roll expanded regions below the midpoint of the tubesheet.

F* Tube is a tube with degradation below the F* distance, equal to or greater than 50%, and has no indications of degradation within the F* distance.

EF* Distance is the distance of the expanded portion of a tube which provides a sufficient length of undegraded tube expansion to resist pullout of the tube from the tubesheet. The EF* distance is equal to 1.44 inches (plus an allowance for NDE uncertainty) and is measured downward from the bottom of the uppermost roll transition. The EF* distance applies to roll expanded regions above the midpoint of the tubesheet.

EF* Tube is a tube with degradation below the EF* distance, equal to or greater than 50%, and has no degradation within the EF* distance.

1. Steam Generator Sample Selection and Inspection

The in-service inspection may be limited to one steam generator on a rotating schedule encompassing the number of tubes determined in TS 4.2.b.2.a provided the previous inspections indicated that the two steam generators are performing in a like manner.

2. Steam Generator Tube Sample Selection and Inspection

The tubes selected for each in-service inspection shall:

- a. Include at least 3% of the total number of nonrepaired tubes, in both steam generators, and 3% of the total number of repaired tubes in both steam generators. The tubes selected for these inspections shall be selected on a random basis except as noted below and in TS 4.2.b.2.b.

Tubes left in service as a result of application of the tube support plate plugging criteria shall be inspected by bobbin coil probe during all future REFUELING outages.

- b. Concentrate the inspection by selection of at least 50% of the tubes to be inspected from critical areas where experience in similar plants with similar water chemistry indicates higher potential for degradation.

- c. Include the inspection of all non-plugged tubes which previous inspections revealed in excess of 20% degradation. The previously degraded tubes need only be inspected about the area of previous degradation indication if their inspection is not employed to satisfy 4.2.b.2.a and 4.2.b.2.b above.

Implementation of the steam generator tube support plate voltage-based plugging criteria requires a 100% bobbin coil inspection for hot leg and cold leg tube support plate intersections down to the lowest cold leg tube support plate with known outside diameter stress corrosion cracking (ODSCC) indications. The determination of tube support plate intersections having ODSCC indications shall be based on the performance of at least a 20% random sampling of tubes inspected over their full length.

- d. In addition to the sample required in 4.2.b.2.a through 4.2.b.2.c, all tubes which have had the F*, or EF*, criteria applied will be inspected each outage in the uppermost tubesheet roll expanded region. These tubes may be excluded from 4.2.b.2.c provided the only previous wall penetration of >20% was located below the F* or EF* distance. F* and EF* tubes will be inspected for a minimum of 2 inches below the bottom of the uppermost roll transition. The results of F* or EF* tube inspections are not to be used as a basis for additional inspection per Table TS 4.2-1.

- e. The second and third sample inspections during each in-service inspection may be less than the full length of each tube by concentrating the inspection on those areas of the tubesheet array and on those portions of the tubes where tubes with imperfections were previously found.

- f. If a tube does not permit the passage of the eddy current inspection probe the entire length and through the U-bend, this shall be recorded and an adjacent tube shall be inspected. The tube which did not allow passage of the eddy current probe shall be considered degraded.

The results of each sample inspection shall be classified into one of the following three categories, and actions taken as described in Table 4.2-2.

Where:

- V = measured voltage
- V_{BOC} = voltage at BOC
- Δt = time period of operation to unscheduled outage
- CL = cycle length (full operating cycle length where operating cycle is the time between two scheduled steam generator inspections)
- V_{SL} = 9.6 volt for 7/8 inch tubes

6. F* and EF* Tubesheet Crevice Region Plugging Criteria

The following criteria are to be used for disposition or repair of steam generator tubes experiencing degradation in the tubesheet crevice region.

- a. Tubes with indications of degradation within the roll expanded region below the midpoint of the tubesheet may remain in service provided the distance from the bottom of the uppermost roll transition to the tip of the crack is greater than 1.12" (plus an allowance for NDE uncertainty). This criteria is called the F* criteria and applies to the factory roll expansion, or to additional roll expansions formed as an extension of the original roll. Any degradation existing below the F* (plus an allowance for NDE uncertainty) is acceptable for continued service.
- b. Indications of degradation not repairable by 4.2.b.6.a may be repaired using the EF* criteria. The EF* region is located a minimum of 4" below the top of the tubesheet, and is formed by an additional roll expansion of the tube in the originally unexpanded length. Tubes with indications of degradation within the EF* region may remain in service provided the distance from the bottom of the uppermost roll transition to the tip of the crack is greater than 1.44" (plus an allowance for NDE uncertainty). Any degradation existing below EF* (including uncertainty) is acceptable for continued service.

7. Reports

- a. Following each in-service inspection of steam generator tubes, if there are any tubes requiring plugging or repairing, the number of tubes plugged or repaired shall be reported to the Commission within 30 days. This report shall include the tubes for which the F* or EF* criteria were applied.

is the ability to perform an additional roll expansion of the tube, either as an extension of the original factory roll expansion, in which case F* criteria applies, or in the area starting approximately 4" below the top of the tubesheet, in which case EF* criterion apply. The additional roll expansion procedure can be applied over existing degradation, provided the F* or EF* requirements for non-degraded roll expansion lengths of 1.12" (plus an allowance for NDE uncertainty) and 1.44" (plus an allowance for NDE uncertainty), respectively, are satisfied. The NDE uncertainty applied to the F* and EF* distance is a function of the eddy current probe and technique used. Current state-of-the art inspection technology will be used with implementation of the F* and EF* criteria. The uncertainty in such inspections has been shown to be as small as 0.06", however, for field application, an eddy current uncertainty of 0.20" will be applied. Any and all indications of degradation existing below the F* or EF* distance is acceptable for continued service.

Technical Specification 4.2.b.7

Category C-3 inspection results are considered abnormal degradation to a principal safety barrier and are therefore reportable under 10 CFR 50.72(b)(2)(i) and 10 CFR 50.73(a)(2)(ii).