







Lower Structure Beams (Full Height Design) (EVT-1)

Westinghouse MR-227-A Primary Scope

- Control Rod Guide Card wear inspections (VT-3)
- Lower Control Rod Guide Tube (CRGT) Lower Flange welds (EVT-1)

- Baffle Former Bolts (UT)
- Baffle Former Assembly (including seams) (VT-3)
- Baffle Former Edge Bolts (VT-3)
- Upper Core Barrel Flange to Shell Weld (EVT-1)
- Lower Core Barrel Flange Weld (EVT-1)
- Thermal Shield Flexures (VT-3)
- Core Barrel Cylinder Girth Welds (EVT-1)
- Internals Hold-Down Spring (if applicable material type) (measurement)









Inspection Implementation



Inspection Implementation

- Some inspections best performed with core barrel in vessel
- Others require core barrel removal
- Common to split inspections over two or more outages
- Typically integrated with ASME Section XI exams
- Special tooling often required
- Vendor crew of roughly 20 specialists required 24/7
- Vendor crew typically experienced on both PWRs and BWRs

© 2015 Electric Power Research Institute, Inc. All rights res

- Owner oversight



Inspections by Plant Design – as of Fall 2014

Design	Initial Ops	<u>Bfl Blts</u>	CB Bolts	CRGT Spc	<u>BMI Spdr</u>		
BW	1973	2012F	2012F	2012F	2012F		
BW	1973	2013S	2013S	2013S	2013S		
BW	1974	2014S	2014S	2014S	2014S		
3 of 6 tota	l						
		Bfl Blts	CRGT WId	CB Wlds	Gd Cards	LCS	
CE	1971		2014S	2014S	2014S	2014S	
1 of 12 total		Bfl Blts	CRGT WId	CB Wlds	Gd Cards		
W2	1969	2011S	2011S	2011S	2011S		
W2	1970	2013S	2013S	2013S	2013S		
W2	1973	2014S	2014S		2014S		
W2	1974	2014F		2014F			
W2	1974	2013F					
W3	1970	2013F		2013F	2012S		
W3	1972	2010F	2012S	2013F	2012S		
W3	1972			2014S			
W3	1973	2011S	2012S	2014S	2012S		
W3	1973			2014F			
11 of 48 total							

Results to Date

20

- Initial full inspections at W and B&W and partial CE NSSS designs have not identified any major issues of concern
- Current results reduce uncertainty in mechanism activity
- Issues of greatest concern not seen
 - SCC of austenitic welded components not observed
 - Cracking currently limited to high strength bolting
 - IASCC of welds not observed, indications limited to bolts
 - Macroscopic effect of void swelling not observed

By the Numbers*

- 15 units begun or completed MRP inspections
- 959 W guide tube flange welds inspected
- 2427 inches of irradiated welds inspected (approx.)
- 9125 inches of non-irradiated welds inspected (approx.)
- 2226 CASS items inspected
- 8887 baffle bolts UT inspected**
- 1654 B&W high strength bolts UT inspected**
- 108 B&W baffle plates inspected

* All numbers approximate. Includes reported inspections through Fall 2014; some data includes retired plant; additional data may affect results slightly

** Includes retired unit

By the Numbers*

22

- Zero Guide Tube Flange weld indications
- Zero irradiated girth weld indications
- One non-irradiated weld indication
- One CASS VT-3 indication
- 136 baffle bolt indications (1.5% of total)
- 20 B&W high strength bolt indications (1.2% of total)

* All numbers approximate. Includes reported inspections through Fall 2014 ; additional data may affect results slightly





