


LIMITING CONDITION FOR OPERATION	SURVEILLANCE REQUIREMENT						
<p>3.2.3 COOLANT CHEMISTRY</p> <p><u>Applicability:</u> Applies to the reactor coolant system chemical requirements.</p> <p><u>Objective:</u> To assure the chemical purity of the reactor coolant water.</p> <p><u>Specification:</u></p> <p>a. The reactor coolant water shall not exceed the following limits for > 24 hours with the coolant temperature \geq 200 degrees F and reactor thermal power \leq 10%, or a shutdown shall be initiated within 1 hour and the reactor shall be shutdown and reactor coolant temperature be reduced to $<$ 200 degrees F within 10 hours.</p> <table> <tr> <td>Conductivity</td> <td>1 μmho/cm</td> </tr> <tr> <td>Chloride ion</td> <td>100 ppb</td> </tr> <tr> <td>Sulfate ion</td> <td>100 ppb</td> </tr> </table>	Conductivity	1 μ mho/cm	Chloride ion	100 ppb	Sulfate ion	100 ppb	<p>4.2.3 COOLANT CHEMISTRY</p> <p><u>Applicability:</u> Applies to the periodic testing requirements of the reactor coolant chemistry.</p> <p><u>Objective:</u> To determine the chemical purity of the reactor coolant water.</p> <p><u>Specification:</u></p> <p>Samples shall be taken and analyzed for conductivity, chloride and sulfate ion content daily. In addition, if the conductivity becomes abnormal (other than short term spikes) as indicated by the continuous conductivity monitor, samples shall be taken and analyzed within 8 hours.</p> <p>When the continuous conductivity monitor is inoperable, a reactor coolant sample shall be taken and analyzed for conductivity, chloride and sulfate ion content at least once per 8 hours.</p>
Conductivity	1 μ mho/cm						
Chloride ion	100 ppb						
Sulfate ion	100 ppb						

9809100108 980903
PDR ADDCK 05000220
PDR




LIMITING CONDITION FOR OPERATION	SURVEILLANCE REQUIREMENT						
<p>b. The reactor coolant water shall not exceed the following limits for > 24 hours with reactor thermal power > 10%, or a shutdown shall be initiated within 1 hour and the reactor shall be shutdown and reactor coolant temperature be reduced to < 200 degrees F within 10 hours.</p> <table> <tr> <td>Conductivity</td> <td>1 $\mu\text{mho}/\text{cm}$</td> </tr> <tr> <td>Chloride ion</td> <td>20 ppb</td> </tr> <tr> <td>Sulfate ion</td> <td>20 ppb</td> </tr> </table> <p>c. In no case shall the reactor coolant exceed the following limits at the specified conditions or, a shutdown shall be initiated within 1 hour and the reactor shall be shutdown and reactor coolant temperature be reduced to < 200 degrees F within 10 hours.</p> <ol style="list-style-type: none"> 1. With reactor coolant temperature \geq 200 degrees F, the conductivity has a maximum limit of $5\mu\text{mho}/\text{cm}$, or 2. With reactor coolant temperature \geq 200 degrees F and reactor thermal power \leq 10%, the maximum limit of chloride or sulfate ion concentration is 200 ppb, or 3. With reactor thermal power > 10%, the maximum limit of chloride or sulfate ion concentration is 100 ppb. 	Conductivity	1 $\mu\text{mho}/\text{cm}$	Chloride ion	20 ppb	Sulfate ion	20 ppb	
Conductivity	1 $\mu\text{mho}/\text{cm}$						
Chloride ion	20 ppb						
Sulfate ion	20 ppb						



LIMITING CONDITION FOR OPERATION

SURVEILLANCE REQUIREMENT

- d. If the continuous conductivity monitor is inoperable for more than seven days, a shutdown shall be initiated within 1 hour and the reactor shall be shutdown and reactor coolant temperature be reduced to <200 degrees F within 24 hours.



BASES FOR 3.2.3 AND 4.2.3 COOLANT CHEMISTRY

In its May 8, 1997 letter, the NRC required that NMPC submit an application for amendment to address the differences between the current TS conductivity limits for reactor coolant chemistry and the analysis assumptions for the core shroud crack growth evaluations. The purpose of this specification is to limit intergranular stress corrosion cracking (IGSCC) crack growth rates through the control of reactor coolant chemistry. The LCO values ensure that transient conditions are acted on to restore reactor coolant chemistry values to normal in a reasonable time frame. Under transient conditions, potential crack growth rates could exceed analytical assumptions, however, the duration will be limited so that any effect on potential crack growth is minimized and the design basis assumptions are maintained. The plant is normally operated such that the average coolant chemistry for the operating cycle is maintained at the conservative values of < 0.19 $\mu\text{mho}/\text{cm}$ for conductivity and < 5 ppb for chloride ions and < 5 ppb for sulfate ions. This will ensure that the crack growth rate is bounded by the core shroud analysis assumptions. Since these are average values, there are no specific LCO actions to be taken if these values are exceeded at a specific point in time. The EPRI "BWR Water Chemistry Guidelines-1996 Revision" (EPRI TR-103515-R1, BWRVIP-29) action level 1 guidelines suggest that if conductivity is above 0.3 $\mu\text{S}/\text{cm}$, or chloride or sulfate ions exceed 5 ppb, that corrective action be initiated as soon as possible and to restore levels below level 1 within 96 hours. If the parameters are not reduced to below these levels within 96 hours, complete a review and implement a program and schedule for implementing corrective measures.

Specifications 3.2.3a, b, and c are consistent with NMPC's commitment to Table 4.4 of the BWR water chemistry guidelines. The 24 hour action time period for exceeding the coolant chemistry limits described in 3.2.3a and b ensures that prompt action is taken to restore coolant chemistry to normal operating levels. The requirement to commence a shutdown within 1 hour, and to be shutdown and reactor coolant temperature be reduced to < 200 degrees F within 10 hours minimizes the potential for IGSCC crack growth. Reactor water samples are analyzed daily to ensure that reactor water quality remains within the BWR water chemistry guidelines. These samples are analyzed and compared to action level 1 values.

The conductivity of the reactor coolant is continuously monitored. The continuous conductivity monitor is visually checked shiftly in accordance with procedures. The monitor alarms at the local panel. The recorder, which is located in the Control Room, alarms in the Control Room. The samples of the coolant which are analyzed for conductivity daily will serve as a comparison with the continuous conductivity monitor. The primary sample point for the reactor water conductivity samples is the non-regenerative heat exchanger in the reactor water cleanup system. An alternate sample point is the #11 recirculation loop. The reactor coolant samples will also be used to determine the chloride and sulfate concentrations. Therefore, the sampling frequency is considered adequate to detect long-term changes in the chloride and sulfate ion content. However, if the conductivity becomes abnormal (> 0.19 $\mu\text{mho}/\text{cm}$), other than short term spikes, chloride and sulfate measurements will be made within 8 hours to assure that the normal limits (< 5 ppb of chloride or sulfate ions) are maintained. A short term spike is defined as a rise in conductivity (> 0.19 $\mu\text{mho}/\text{cm}$) such as that which could arise from injection of additional feedwater flow for a duration of approximately 30 minutes in time. These actions will minimize the potential for IGSCC crack growth.

