NUCLEAR POWER SYSTEMS

COMBUSTION ENGINEERING, INC. COMPONENTS ENGINEERING Chattanooga, Tennessee

EVALUATION OF PALISADES

AUXILIARY FEEDWATER PIPING

FOR A POSTULATED WATER HAMMER EVENT

SS-801	·	29 66-B	
CALCULATION NO.	· · · · · · · · · · · · · · · · · · ·	CONTRACT NO.	•
	•	·	
		•	
PALISADES	·	TEAM GENERATOR	
CUSTOMER		COMPONENT	
•			
•		•	
P. L. anderson	Principal Engineer TITLE	4-19-84 DATE	
PREPARED	TITLE	DATE	
			•
J. P. Houstru	Principal Engineer	4-19-84	
CHECKED	TITLE	DATE	
(Full Review)			
0016			
With June	. Manager	4-19-54	
REVIEWED	TITLE	DATE	
	. •		
.,			
APPROVED	TITLE	DATE	
407110396 840709			
407110396 840709 DR ADDCK 05000255		•	

PDR

Attachment

PRETA	HEB	du	مند	*/	4-14. DAT	-:/	
1.1	1				1 .	a i	'n.

COMBUSTION ENGINEERING, INC. Chattanooga Nuclear Operations

OF 6 SHEET CALC. NO. 55-801

J. Houstup CHECKED

COMPONENT ENGINEERING

2966·B CONTRACT NO.

TITLE

SUMMARY AND CONCLUSIONS

The Palisades steam generator auxiliary feedwater piping is evaluated for a postulated water hammer event. The analysis addresses the axial stress resulting from a pressure pulse of 4000 psi lasting less than 0.001 sec. The predicted stress at the minimum cross-section is 31 ksi which slightly exceeds the minimum yield stress of 27.5 ksi at 532°F. This stress is significantly below the ultimate tensile stress of 60 ksi at temperature. In view of the ductility of the carbon steel material, the stress of 31 ksi (52% of S_{II}) is considered to be well below a damaging stress level.

A fatigue evaluation of 25 occurrences of the water hammer event indicates a negligible fatigue usage factor.

REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK

P. L. Circleson 4-17.54 COMBUSTION ENGINEERING, INC. DATE

Chattanooga Nuclear Operations

2. 0, 6 SHEET 55-801 CALC. NO.

2966-B

CHECKED

4-19-86 DATE

COMPONENT ENGINEERING

TITLE

INTRODUCTION


The purpose of this report is to evaluate a section of the . Palisades auxiliary feedwater piping for loads resulting from a postulated water hammer event. The piping section of concern consists of the horizontal run extending from the auxiliary nozzle to the first downturning elbow **external** to the generator. A water hammer event is postulated to produce a pressure pulse of 4000 psi in the horizontal pipe run. This analysis considers the stresses resulting from the 4000 psi pressure pulse assuming that the pipe and welds are in a virgin condition. Duration of the pulse is 0.00083 sec.

REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK

4-19? COMBUSTION ENGINEERING, INC. Chattanooga Nuclear Operations 4-19-84 CALC. NO. 55-801 **COMPONENT ENGINEERING** CHECKED CONTRACT NO. TITLE

GEOMETRY AND MATERIAL PROPERTIES

The minimum cross-section of the piping occurs at the piping to nozzle weld.



For the minimum section

$$R_i = 2.139$$
" (max)

$$t = .236''(min)$$

$$A_{\min} = 3.35 \text{ in}^2$$

For the SA-106 Gr. B material at 532°F the ASME Code (Ref. 1) allowables are

$$\sqrt{s_u} = 60 \text{ ksi}$$


REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK

Attachment (

P.L. Lovinson.	9-19-57 DATE	COMBUSTION ENGINEERING, INC. Chattanooga Nuclear Operations	SHEET 4 OF 6
J. Hous hup	4-19-84	COMPONENT ENGINEERING	CALC. NO. 55-801
CHECKED	DATE	COMPONENT ENGINEERING	CONTRACT NO. 2966-B
TITLE	,		,

EVALUATION OF WATER HAMMER LOAD

Reference 2 describes the postulated water hammer event and presents the resulting pressure pulse.



The short duration pulse results in an axial load

$$ARR = \frac{\pi (4.262 + 0.015)^2}{4.262 + 0.015} = 14.371$$

A = Area of Pipe =
$$\pi R^2 = 12.97 \text{ in}^2$$

Considering the load to be suddenly applied and applying a dynamic amplification factor of 2 results in an equivalent static load 14.37 = 115 keys

$$F_s = 2F = 2(4000)(12.97) = 104 \text{ kips}$$

The axial membrane stress at the minimum cross-section is $\frac{110}{500} = \frac{25}{500} \times \frac{25}{500}$

$$S = F_s/A_{min} = 104/3.25 = 31 \text{ ksi}$$

This stress slightly exceeds the yield stress of 27.5 ksi, but is significantly below the ultimate stress of 60 ksi at temperature. In view of the ductility of the carbon steel material, the stress level of 31 ksi (52% of $S_{\rm u}$) is considered to be well below a damaging stress level. ASME code rules for a faulted event, for example, permit a membrane stress of 70% of $S_{\rm u}$ with an adequate margin of safety.

 											
REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	ΒŸ	CHECK

4-19-86

P.L. Indian 4-17-17 COMBUSTION ENGINEERING, INC.
Chattanoona Nuclear Operations Chattanooga Nuclear Operations

COMPONENT ENGINEERING

SHEET 55-801 CALC. NO. 2966-8

CHECKED TITLE

FATIGUE EVALUATION

A conservative stress concentration factor of 4 applied to the 31 ksi stress results in an alternating stress of 62 ksi. Using the fatigue curves of Reference 1, the corresponding allowable number of cycles is approximately 2000. For a few cycles, for example 25 occurrecnes, the cumulative usage factor

that the system has specied a less than a country of the country o

REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK

P. L. Cenclosson 4.19.51
PREPARED DATE

1 Houstup 4-19-84

COMBUSTION ENGINEERING, INC. Chattanooga Nuclear Operations

COMPONENT ENGINEERING

SHEET 6 OF 6

CALC. NO. 55-801

CONTRACT NO. 2966-B

TITLE

REFERENCES

DATE

- 1. ASME B&PV Code, Section III for Nuclear Vessels and Addenda through Summer 1983.
- 2. CE Report 2966-PSAE-001, "Evaluation of Water Hammer within Steam Generator Feed Pipe", A. J. Sowers.

REV.	DATE	87	CHECK	REV.	DATE	BY	CHECK	REV.	DATE	BY	CHECK