

72

UNITED STATES
NUCLEAR REGULATORY COMMISSION
REGION I
631 PARK AVENUE
KING OF PRUSSIA, PENNSYLVANIA 19406

Docket Nos. 50-317
50-318

NOV 20 1979

Baltimore Gas and Electric Company
ATTN: Mr. A. E. Lundvall, Jr.
Vice President, Supply
P. O. Box 1475
Baltimore, Maryland 21203

Gentlemen:

The enclosed IE Bulletin 79-26 is forwarded to you for information. No written response is required. If you desire additional information regarding this matter, please contact this office.

Sincerely,

James W. Allan
for
Boyce H. Grier
Director

Enclosures:

1. IE Bulletin No. 79-26
2. List of Recently Issued IE Bulletins

CONTACT: D. L. Capton
(215-337-5266)

cc w/encls:

R. M. Douglass, Manager, Quality Assurance
L. B. Russell, Chief Engineer
W. Gibson, General Supervisor, Operational QA
R. C. L. Olson, Senior Engineer
K. H. Sebra, Principal Engineer

1500 095

Q 791205e 217

ENCLOSURE 1

UNITED STATES
NUCLEAR REGULATORY COMMISSION
OFFICE OF INSPECTION AND ENFORCEMENT
WASHINGTON, D.C. 20555

SSINS: 6820
Accession No.:
7910250475

IE Bulletin No. 79-26
Date: November 20, 1979
Page 1 of 4

BORON LOSS FROM BWR CONTROL BLADES

Description of Circumstances:

The General Electric Company (GE) has informed us of a failure mode for control blades which can cause a loss of boron poison material. Hot cell examinations of both foreign and domestic blades have revealed cracks near the upper end of stainless steel tubing and loss of boron from the tubes. The cracks and boron loss have so far been confined to locations in the poison tubes with more than 50 percent Boron-10 (B^{10}) local depletion. Observed crack sizes range from a quarter to a half inch in length and from one to two mils in width.

GE has postulated that the cracking is due to stress corrosion induced by solidification of boron carbide (B_4C) particles and swelling of the compacted B_4C as helium and lithium concentrations grow. Once primary coolant penetrates the cladding (i.e., the cracking has progressed through the cladding wall and the helium-lithium pressures are sufficient to open the crack), boron is leached out of the tube at locations with more than 50 percent B^{10} local depletion (local depletion is considered to be twice the average depletion). It was further found with similar cracking but with less than 50 percent local depletion of B^{10} , that leaching did not occur even though primary coolant had penetrated the cladding.

The cracking and boron loss shorten the design life of the control blade. According to the GE criteria the end of design life is reached when the reactivity worth of the blade is reduced by 10 percent, which corresponds to 42 percent B^{10} depletion averaged over the top quarter of the control blade. Because of the leaching mechanism, GE has reduced the allowance for B^{10} depletion averaged over the top quarter of the control blade from the 42 percent value to 34 percent.

The safety significance of boron loss is its impact on shutdown capability and scram reactivity. Although shutdown capability is demonstrated by shutdown margin tests after refueling, the calculation tests are based on the assumption that in scram reactivity due to boron loss could be compensated by Power Ratio (CPR) reductions during the shutdown. The consequences of control rod drop accidents are being studied.

1500 096

DUPLICATE DOCUMENT

Entire document previously
entered into system under:

ANO 7910250475

No. of pages: 5