

# NUCLEAR

# Code Case N-871-1 Status Update

Jim O'Sullivan Procon1, LLC

NRC Technical Exchange Meeting Rockville, MD January 16, 2020

 Image: Market state
 Image: Market state

 www.epri.com
 © 2020 Electric Power Research Institute, Inc. All rights reserved.

Code Case N-871, "Internal Repair of Class 2 & 3 Buried Piping Using Carbon Fiber Composite Materials"

- Scope of original Code Case:
  - Segments of hand lay-up carbon fiber reinforced polymer (CFRP) composite structurally replace the underlying degraded piping
  - Multiple in-process visual examinations to ensure structural integrity
  - Terminal ends of CFRP designed to provide complete structural load transfer to and from sound steel substrate
  - Volumetric examination of terminal ends required to verify soundness to ensure adequate load-transfer capability – acoustic tap method specified for examination of composite
  - Scope limited to internal application of CFRP composite for repair of degraded sections of large bore buried steel piping







## Code Case N-871-1, "Repair of Class 2 & 3 Piping Using Carbon Fiber Composite Materials"

- Scope of revision 1:
  - Volumetric examination of terminal ends initially revised to allow acoustic tap or dynamic response spectroscopy method
  - Scope expanded to include:
    - internal or external application of CFRP for repair of degraded sections of buried metallic piping
    - Internal or external application of CFRP for repair of degraded sections of aboveground metallic piping



#### Code Case N-871-1: Repair of Class 2 & 3 Metallic Piping using CFRC

- Recent Letter Ballot comments resulted in many improvements to the Code Case. These include:
  - Clarified how to evaluate degradation relative to design life.
  - Relocated inspection and examination acceptance criteria to Section 5000.
  - Revised installation and inservice examination to permit any equivalent volumetric technique that can qualify to the CC.
  - Refined volumetric demonstration and recording requirements.
  - Added requirement that Level III, SME and examination personnel experience be approved by the Owner.



#### Code Case N-871-1: Repair of Class 2 & 3 Metallic Piping using CFRC

- Improvements (cont'd):
  - Identified the rigor required for volumetric examination procedure qualification as defined by ASME Section V.
  - Added generic descriptions of required volumetric examination procedure essential variables.
  - Added background noise in decibels as essential variable for qualification of acoustic tap examination personnel.
  - Clarified mandatory training requirements for inspection and NDE personnel.





#### Code Case N-871-1: Repair of Class 2 & 3 Metallic Piping using CFRC

- Improvements (cont'd):
  - Clarified various CFRP Repair Procedure qualification requirements.
  - Clarified that users may set their own upper-bound test limits to broaden the potential applicability for a series of tests.
  - Changed acoustic tap and dynamic response spectroscopy examination mandatory appendices to nonmandatory.
  - Multiple changes in terminology for consistency and clarity throughout the Code Case.

#### Code Case N-871-1: Repair of Class 2 & 3 Metallic Piping using CFRC

- Some comments still require further discussion:

Design Related Comments

- 3131(c) (2) Are there data available to show that properties between Room Temperature and 125 F are reasonably close?
  - Third party testing currently underway
- 3131 (e) Need to verify this equation provides a conservative estimation for ultimate strength of multi-ply laminate.
  - Third party testing currently underway



Design Related Comments (cont'd)

 3131 (e) - 10 samples are not sufficient to provide the characteristic value; 50 samples are needed per ASTM D7290.

• Third party testing currently underway

 Maximum operating temperature should be based on Material Adjustment Factor testing above 140 F

• Third party testing currently underway

- Is the Miner's Rule approach applicable to unidirectional CFRP laminates?
  - Task Group is evaluating





#### Design Related Comments (cont'd)

- 3300 (c) Some guidance or a reference is needed for evaluating strains in CFRP materials.
  - Task Group is evaluating
- Misalignment of 5 degrees may have a considerable effect in reducing the ultimate strength of CFRP repair.
  - Third party testing currently underway
- Need verification that provisions for testing to establish stress intensification factors for CFRC fittings are adequate.
  - Prototype testing is being considered by EPRI



#### NDE Related Comments:

- 5212 addresses layer-by-layer visual exam, 5213 addresses final visual exam, but if you do the layer-by-layer, do you need a final?
  - The final visual includes the top coat and serves as preservice baseline examination.
- 5300 The technical criteria for flaw acceptance is based on carbon fiber wrap of reinforced structural concrete – not piping.
  - AWWA C305 (2018), CFRP Renewal of Precast Concrete Cylinder Pipe invokes the same acceptance criteria.
- 5410(e) term "representative of the configuration to be examined" needs clarification relative to demonstration test panels.
  - Means maximum composite thickness and same substrate diameter to NPS 24





#### *NDE Related Comments* (cont'd):

- 5410(h) need to identify retention requirements for NDE demonstration panels.
  - Open for discussion
- 5420 minimum essential variables (f), (g) and (h) relate to any variables that could affect signal transmission, receipt of signal response or evaluation of signal response... seems too broad.

• intended to be generic to apply to any examination method that is used.

- 5450(a)(3) optional in-process acoustic tap examinations, including optional personnel qualification method, should be removed.
  - Basic criteria: visual during installation, volumetric NDE of terminal ends



## **Questions or Comments?**





ELECTRIC POWER RESEARCH INSTITUTE

Welding and Repair Technology Center





### Together...Shaping the Future of Electricity



