



December 14, 2000
LIC-00-0102

U.S. Nuclear Regulatory Commission
ATTN: Document Control Desk
Mail Station P1-137
Washington, DC 20555-0001

References: 1. Docket No. 50-285
2. Letter from OPPD (W.G.Gates) to NRC (Document Control Desk) dated July 28, 2000 (LIC-00-0062)

SUBJECT: Application for Amendment of Facility Operating License No. DPR-40

Omaha Public Power District (OPPD) is submitting this "Application for Amendment of Facility Operating License" to permit the use of Leak Tight Sleeves, developed by Combustion Engineering, Inc. (CE), at Fort Calhoun Station (FCS). This submittal supercedes and replaces Attachments A and B of Reference 2, our previous Application for Amendment on the subject, in response to requests made by NRR during their review of Reference 2.

OPPD proposes to amend the applicable sections in the Fort Calhoun Station Unit No. 1 Technical Specifications to allow installation of tube sleeves as an alternative to plugging to repair defective steam generator tubes. Currently, FCS Technical Specifications only allow defective tubes to be plugged and removed from service. The proposed amendment will revise the applicable Technical Specifications to permit the use of Leak Tight Sleeves developed by Combustion Engineering, Inc. (CE). CE provides two types of Leak Tight Sleeves. The first type of repair sleeve spans the expansion transition zone of the tube at the top of the tubesheet. The second type of repair sleeve spans the degraded areas at a support location or in a free span section. The CE process has been in use since 1984 and has been implemented more than 24 times for the installation of over 4,200 sleeves. OPPD is also amending the Technical Specifications to reduce the primary to secondary leakage limit.

Attachment A contains a markup reflecting the proposed changes to the Table of Contents, Sections 2.1.4, 3.1, 3.17 and Tables 3-13 and 3-14, Technical Specifications of the Facility Operating License. Attachment B provides the "Discussion, Justification and No Significant Hazards Consideration." The detailed report on the specific qualifications of the repair sleeve for FCS application is contained in the proprietary CE report CEN-630-P, Revision 02, "Repair of 3/4" O.D. Steam Generator Tubes Using Leak Tight Sleeves," Attachment D of Reference 2. The proprietary affidavit for Attachment D of Reference 2 appears in Attachment C of Reference 2. The non-proprietary version of this report is included as Attachment E of Reference 2.

A001


U.S. Nuclear Regulatory Commission

LIC-00-0102

Page 2

OPPD wishes to have sleeving as an option to repair defective steam generator tubes at FCS during the 2001 refueling outage, scheduled to begin in March 2001. Therefore, OPPD requests the Nuclear Regulatory Commission review and approve the proposed amendment on or before February 1, 2001. OPPD respectfully requests 30 days to implement the proposed specifications following NRC approval. If you have additional questions, or require further information, please contact me or members of my staff.

Sincerely,



W. G. Gates
Vice President

WGG/RLJ

Enclosures
Attachments

c: E. W. Merschoff, NRC Regional Administrator, Region IV
L. R. Wharton, NRC Project Manager
W. C. Walker, NRC Senior Resident Inspector
B. E. Casari, Director - Environmental Health Division, State of Nebraska
Winston & Strawn

UNITED STATES OF AMERICA
NUCLEAR REGULATORY COMMISSION

In the Matter of	)	
	)	
Omaha Public Power District	)	Docket No. 50-285
(Fort Calhoun Station	)	
Unit No. 1)	)	

APPLICATION FOR AMENDMENT
OF
FACILITY OPERATING LICENSE

Pursuant to Section 50.90 of the regulations of the U. S. Nuclear Regulatory Commission ("the Commission"), Omaha Public Power District, holder of Facility Operating License No. DPR-40, herewith requests that the Technical Specifications Table of Contents, Bases of Technical Specifications 2.1.4, 3.1, and 3.17 and Technical Specifications set forth in Section 2.1.4, 3.17 and Table 3-13 of the Facility Operating License be amended and that Table 3-14 be added to allow installation of tube sleeves as an alternative to plugging to repair defective steam generator tubes. The proposed amendment will revise the applicable Technical Specifications to permit the use of Leak Tight Sleeves developed by Combustion Engineering, Inc. (CE). CE provides two types of Leak Tight Sleeves. The first type of repair sleeve spans the expansion transition zone of the tube at the top of the tubesheet. The second type of repair sleeve spans the degraded areas at a support location or in a free span section.

The proposed changes to the Technical Specifications are provided in Attachment A of this Application. A Discussion, Justification, and No Significant Hazards Consideration Analysis, which demonstrates the proposed changes do not involve significant hazards considerations, is appended in Attachment B. The proposed changes to Appendix A, Technical Specifications of the Facility Operating License, would not authorize any change in the types or any increase in the amounts of effluents or any change in the authorized power level of the facility.

WHEREFORE, Applicant respectfully requests that Appendix A of the Facility Operating License be amended hereto as Attachment A.

A copy of this Application, including its attachments, has been submitted to the Director - Nebraska State Division of Environmental Health, as required by 10 CFR 50.91.

OMAHA PUBLIC POWER DISTRICT

By *M Gary Tate*
Vice President

Subscribed and sworn to before me this 14 day of December 2000

Amy S. Hansen
Notary Public



UNITED STATES OF AMERICA
NUCLEAR REGULATORY COMMISSION

In the Matter of

Omaha Public Power District
(Fort Calhoun Station
Unit No. 1)

)
)
)
)
)

Docket No. 50-285

AFFIDAVIT

W. G. Gates, being duly sworn, hereby deposes and says that he is the Vice President in charge of all nuclear activities of the Omaha Public Power District; that he is duly authorized to sign and file with the Nuclear Regulatory Commission the attached information concerning the Application for Amendment of the Facility Operating License dated December 14, 2000, regarding the change to allow installation of tube sleeves as an alternative to plugging to repair defective steam generator tubes; that he is familiar with the content thereof; and that the matters set forth therein are true and correct to the best of his knowledge, information, and belief.


W. G. Gates
W. G. Gates
Vice President

STATE OF NEBRASKA)
) ss
COUNTY OF DOUGLAS)

Subscribed and sworn to me, a Notary Public in and for the State of Nebraska on this

14th day of December 2000

Amy S. Hansen
Notary Public



LIC-00-0102
Attachment A
Requested Changes of Technical Specifications Set Forth in Appendix A of the
Facility Operating License
No. DPR-40

TECHNICAL SPECIFICATIONS

TECHNICAL SPECIFICATIONS - TABLES

TABLE OF CONTENTS

<u>TABLE</u>	<u>DESCRIPTION</u>	<u>PAGE</u>
3-3	Minimum Frequencies for Checks, Calibrations, and Testing of Miscellaneous Instrumentation and Controls	3-13
		3-14
		3-15
		3-16
		3-16a
		3-16b
		3-16c
3-3a	Minimum Frequency for Checks, Calibrations and Functional Testing of Alternate Shutdown Panels (AI-185 and AI-212) and Emergency Auxiliary Feedwater Panel (AI-179) Instrumentation and Control Circuits	3-16d
		3-16e
3-4	Minimum Frequencies for Sampling Tests	3-18
		3-19
3-5	Minimum Frequencies for Equipment Tests	3-20
		3-20a
		3-20b
		3-20c
		3-20d
3-6	Reactor Coolant Pump Surveillance	3-27
3-13	Steam Generator Tube Inspection	3-90
3-14	Steam Generator Tube Sleeve Inspection	3-90a
5.2-1	Minimum Shift Crew Composition	5-2

TECHNICAL SPECIFICATIONS

TECHNICAL SPECIFICATIONS - TABLES

TABLE OF CONTENTS (ALPHABETICAL ORDER)

Continued

<u>TABLE</u>	<u>DESCRIPTION</u>	<u>PAGE</u>
3-5	Minimum Frequencies for Equipment Tests	3-20
		3-20a
		3-20b
		3-20c
		3-20d
3-4	Minimum Frequencies for Sampling Tests	3-18
		3-19
5.2-1	Minimum Shift Crew Composition	5-2
2-10	Post-Accident Monitoring Instrumentation Operating Limits	2-98
		2-98a
		2-98b
2-9	RCS Pressure Isolation Valves	2-2d
3-6	Reactor Coolant Pump Surveillance	3-27
1-1	RPS LSSS	1-10
		1-10a
3-13	Steam Generator Tube Inspection	3-90
3-14	Steam Generator Tube Sleeve Inspection	3-90a
2-11	Toxic Gas Monitoring Operating Limits	2-100

TECHNICAL SPECIFICATIONS

2.0 **LIMITING CONDITIONS FOR OPERATION**

2.1 Reactor Coolant System (Continued)

2.1.4 Reactor Coolant System Leakage Limits

Applicability

Applies to the leakage rates of the reactor coolant system whenever the reactor coolant temperature (T_{cold}) is greater than 210 °F.

Objective

To specify limiting conditions of the reactor coolant system leakage rates.

Specifications

To assure safe reactor operation, the following limiting conditions of the reactor coolant system leakage rates must be met:

- (1) If the reactor coolant system leakage exceeds 1 gpm and the source of leakage is not identified within 12 hours, the reactor shall be placed in the hot shutdown condition. If the source leakage exceeds 1 gpm and is not identified within 24 hours, the reactor shall be placed in the cold shutdown condition.
- (2) If leakage exceeds 10 gpm, the reactor shall be placed in the hot shutdown condition within 12 hours. If the leakage exceeds 10 gpm for 24 hours, the reactor shall be placed in the cold shutdown condition.
- (3) Primary-to-secondary leakage through the steam generator tubes shall be limited to 150 gallons per day per steam generator and 300 gallons per day 4-gpm total for both steam generators. When primary-to-secondary leakage has been determined to be in excess of the limit, the leakage rate shall be reduced to within limits in 4 hours or the reactor shall be placed in the cold shutdown condition within the next 36 hours.
- (4) To determine leakage to the containment, a containment atmosphere radiation monitor (gaseous or particulate) or dew point instrument, and a containment sump level instrument must be operable.
 - a. With no containment sump level instrument operable, verify that a containment atmosphere radiation monitor is operable, and restore the containment sump level instrument to operable status within 30 days.
 - b. With no containment atmosphere radiation monitor and no dewpoint instrument operable, restore either a radiation monitor or dewpoint instrument to operable status within 30 days.
 - c. With only the dewpoint instrument operable, or with no operable instruments, enter Specification 2.0.1 immediately.

TECHNICAL SPECIFICATIONS

2.0 LIMITING CONDITIONS FOR OPERATION

2.1 Reactor Coolant System (Continued)

2.1.4 Reactor Coolant System Leakage Limits (Continued)

Limiting primary to secondary leakage is important to ensure steam generator tube integrity. The plant is expected to be operated in a manner such that the secondary coolant will be maintained within those chemistry limits found to result in negligible corrosion of the steam generator tubes. If the secondary coolant chemistry is not maintained within these limits, localized corrosion may likely result in stress corrosion cracking. The extent of cracking during plant operation would be limited by the limitation of steam generator tube leakage between the primary coolant system and the secondary coolant system (primary-to-secondary leakage = 150 gallons per day through any one steam generator or 300 gallons per day total) ~~1-gallon-per-minute, total~~. The safety analysis assumes a 1 gpm primary to secondary leak as the initial condition. The Technical Specification requirement to limit primary to secondary leakage through any one steam generator to less than 150 gallons per day is significantly less than the initial condition for the safety analysis. This limit is based on industry operating experience as an indication of one or more propagating tube leak mechanisms. This leakage rate provides reasonable assurance against tube burst at normal and faulted conditions and provides reasonable assurance that flaws will not propagate to burst prior to detection by leakage monitoring and commencement of plant shutdown. ~~Cracks having a primary-to-secondary leakage less than this limit during operation will have an adequate margin of safety to withstand the loads imposed during normal operation and by postulated accidents. Operating plants have demonstrated that primary-to-secondary leakage of 150 gallons per day 1-gallon-per-minute can readily be detected by radiation monitors. Leakage from any one steam generator in excess of this limit will require plant shutdown and an unscheduled inspection, during which the leaking tubes will be located and plugged or repaired.~~

References

(1) USAR, Section 11.2.3

(2) USAR, Page G.16-1

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.1 **Instrumentation and Control** (Continued)

Substantial calibration shifts within a channel (essentially a channel failure) will be revealed during routine checking and testing procedures.

The minimum calibration frequencies of once-per-day (heat balance adjustment only) for the power range safety channels, and once each refueling shutdown for the process system channels, are considered adequate.

The minimum testing frequency for those instrument channels connected to the Reactor Protective System and Engineered Safety Features is based on ABB/CE probabilistic risk analyses and the accumulation of specific operating history. The quarterly frequency for the channel functional tests for these systems is based on the analyses presented in the NRC approved topical report CEN-327-A, "RPS/ESFAS Extended Test Interval Evaluation," as supplemented, and OPPD's Engineering Analysis EA-FC-93-064, "RPS/ESF Functional Test Drift Analysis."

The low temperature setpoint power operated relief valve (PORV) CHANNEL FUNCTIONAL TEST verifies operability of the actuation circuitry using the installed test switches. PORV actuation could depressurize the reactor coolant system and is not required.

Calculation of the Reactor Coolant System (RCS) total flow rate by performance of a precision calorimetric heat balance once every 18 months verifies that the actual RCS flow rate is greater than or equal to the minimum required RCS flow rate (Table 3-3, Item 15, Reactor Coolant Flow).

The frequency of 18 months reflects the importance of verifying flow after a refueling outage when the core has been altered, Steam Generator tubes plugged or repaired, or other activities, which may have caused an alteration of flow resistance.

This requirement is modified by a footnote that requires the surveillance to be performed within 24 hours after $\geq 95\%$ reactor thermal power (RTP) following power escalation from a refueling outage. The footnote is necessary to allow measurement of the flow rate at normal operating conditions at power in MODE 1.

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes**

Applicability

Applies to in-service surveillance of steam generator tubes.

Objective

To ensure the integrity of the steam generator tubes.

Specifications

Each steam generator shall be demonstrated OPERABLE by performance of the following in-service inspection program.

(1) **Steam Generator Sample Selection and Inspection Methods**

The in-service inspection shall be performed on each steam generator on a rotating schedule. Under some circumstances, the operating conditions in one steam generator may be found to be more severe than those in the second steam generator. Under such circumstance, the sample sequence shall be modified to inspect the steam generator with the most severe conditions.

(2) **Steam Generator Tube Sample Selection and Inspection**

The steam generator tube minimum sample size, inspection result classification, and the corresponding action required shall be as specified in Table 3-13. The in-service inspection of steam generator tubes shall be performed according to Specification 3.17(4)(i), "Tube Inspection," and at the frequencies specified in Specification 3.17(3). The inspected tubes shall be verified acceptable per the acceptance criteria of Specification 3.17(4). When applying the exceptions of (i), (ii) and (iii) below, previous degradation, imperfections, or defects in the area of the tube repaired by sleeving are not considered an area requiring reinspection or inspection of adjacent tubes. The tubes selected for each in-service inspection shall include at least 3% of the total tubes in the steam generators and the tubes selected for these inspections shall be selected on a random basis, except:

- (i) If the tube is recorded as a degraded tube, then an adjacent tube shall be inspected.
- (ii) The first sample inspection during each in-service inspection of each steam generator shall include all non-plugged tubes that previously had detectable wall penetrations (>20%) and shall also include tubes in those areas where experience has indicated potential problems.
- (iii) The second and third sample inspections, if required, may be less than an entire tube length inspection provided the inspection concentrates on those areas of the tube sheet array and on those portions of the tubes where

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes (Continued)**

defects were previously detected.

- (iv) To the extent practical, where experience in similar plants with similar water chemistry indicates critical areas to be inspected, then at least 50% of the tubes inspected shall be from these critical areas.

The results of each sample inspection shall be classified into one of the following three categories (this classification shall apply to the inspection of tubes and is exclusive of the sleeve inspection requirements in Specification 3.17(2a)).

<u>Category</u>	<u>Inspection Results</u>
C-1	No more Less than 5% of the tubes inspected are degraded and none of the inspected tubes are defective.
C-2	No more Less than 1% of the tubes inspected are defective, or between 5% and 10% of the tubes inspected are degraded.
C-3	More than 1% of the tubes inspected are defective, or more than 10% of the tubes inspected are degraded.

NOTE: In all inspections, previously degraded tubes must exhibit growth of greater than 10% through wall or growth of greater than 25% of the repair limit ~~significant (>10%) further wall penetrations~~ to be included in the above calculations.

(2a) **Steam Generator Tube Sleeve Sample Selection and Inspection**

The steam generator tube sleeve minimum sample size, inspection result classification, and the corresponding action required shall be as specified in Table 3-14. The in-service inspection of steam generator tube sleeves shall be performed according to Specification 3.17(4)(i), "Tube Sleeve Inspection," and at the frequencies specified in Specification 3.17(3). The inspected tube sleeves shall be verified acceptable per the acceptance criteria of Specification 3.17(4). The tube sleeves selected for each in-service inspection shall include at least 20% of the total number of tube sleeves in the steam generators and the tube sleeves selected for these inspections shall be selected on a random basis, except:

- (i) If the tube sleeve is recorded as a degraded tube sleeve and an adjacent tube sleeve exists, then an adjacent tube sleeve shall be inspected.

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes (Continued)**

- (ii) The first sample inspection during each in-service inspection of each steam generator shall include all tube sleeves in non-plugged tubes that previously had detectable wall penetrations (>20%) and shall also include tube sleeves in those areas where experience has indicated potential problems.
- (iii) To the extent practical, where experience in similar plants with similar water chemistry indicates critical areas to be inspected, then at least 50% of the tube sleeves inspected shall be from these critical areas. Where the number of sleeves in the critical areas represent less than 50% of the initial sample, all sleeves in the critical areas shall be inspected.

The results of each sample inspection shall be classified into one of the following three categories (this classification shall apply to the inspection of sleeves and is exclusive of the tube inspection requirements in Specification 3.17(2)).

<u>Category</u>	<u>Inspection Results</u>
C-1	No more than 5% of the tube sleeves inspected are degraded and none of the inspected tube sleeves are defective.
C-2	No more than 1% of the tube sleeves inspected are defective, or between 5% and 10% of the tube sleeves inspected are degraded.
C-3	More than 1% of the tube sleeves inspected are defective, or more than 10% of the tube sleeves inspected are degraded.

NOTE: In all inspections, previously degraded tube sleeves must exhibit growth of greater than 10% through wall or growth of greater than 25% of the repair limit to be included in the above calculations.

(3) **Inspection Frequencies**

The above required in-service inspections of steam generator tubes and tube sleeves shall be performed at the following frequencies (inspections shall be performed, unless otherwise specified, coincident with refueling outages or any scheduled cold shutdown for plant repair and maintenance):

- (i) In-service inspections shall be performed at intervals of not less than 12 nor more than 24 calendar months after the previous inspection, subject to the following clarifications and exceptions ~~with one exception.~~

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes** (Continued)

1. If a plant operating cycle is less than 12 months, inspections may be performed at the end of that cycle
2. If two consecutive tube inspections following service under all volatile treatment conditions result in all inspection results falling into the C-1 category or if two consecutive tube inspections demonstrate that previously observed degradation has not continued and no additional degradation has occurred, the tube inspection interval may be extended to a maximum of once per 40 months.
3. The inspections of tube sleeves shall be configured to ensure that each individual tube sleeve is inspected at least once in 60 months, with the following exception: if the 60 month time frame falls during an operating cycle, completion of that cycle is acceptable prior to meeting this requirement.

(ii) Increased Inspection Frequencies

1. If results of the in-service inspection of the steam generator tubes conducted in accordance with Table 3-13 at 40-month intervals fall in Category C-3, the inspection frequency shall be increased to at least once per 20 months. The increase in inspection frequency shall apply until a subsequent inspection meets the conditions specified in Section 3.17(3)(i)2.(i) above, at which time the interval can be extended to a 40-month period.
2. If results of the inservice inspection of tube sleeves conducted in accordance with Table 3-14 fall into Category C-3, the inspection frequency shall be increased such that 100% of the tube sleeves in the affected steam generator are inspected during subsequent inspections. The increase in inspection frequency shall apply until two consecutive tube sleeve inspections meet the conditions for Category C-1 or two consecutive tube sleeve inspections demonstrate that previously observed degradation has not continued and no additional degradation has occurred, at which time the inspection frequency of Specification 3.17(3)(i)3. shall again apply.

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes** (Continued)

- (iii) Unscheduled in-service inspections shall be performed on each steam generator in accordance with the first sample inspection specified in Tables 3-13 and 3-14 during the shutdown subsequent to any of the following conditions:
 - 1. Primary-to-secondary tube leaks (not including leaks originating from tube-to-tube sheet welds) in excess of the limits of Section 2.1.4 of the Technical Specifications,
 - 2. A seismic occurrence greater than the Operating Basis Earthquake,
 - 3. A loss-of-coolant accident requiring actuation of the engineered safeguards, or
 - 4. A main steam line or main feedwater line break.

(4) **Acceptance Criteria**

- (i) As used in this specification:

Imperfection means an exception to the dimensions, finish or contour of a tube or sleeve from that required by fabrication drawings or specifications. Eddy-current testing indications below 20% of the nominal tube or sleeve wall thickness, if detectable, may be considered as imperfections.

Degradation means a service-induced cracking, wastage, wear or general corrosion occurring on either inside or outside of a tube or sleeve.

Degraded Tube or Sleeve means a tube or sleeve containing imperfections $\geq 20\%$ of the nominal wall thickness caused by degradation. Any tube which does not permit the passage of the eddy-current inspection probe through its entire length and U-bend shall be deemed a degraded tube. Any tube sleeve which does not permit the passage of the eddy current inspection probe through its entire length shall be deemed a degraded sleeve.

% Degradation means the percentage of the tube or sleeve wall thickness affected or removed by degradation.

Defect means an imperfection of such severity that it exceeds the plugging or repair limit. ~~A tube containing a defect is defective.~~

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes (Continued)**

Plugging or Repair Limit means the imperfection depth at or beyond which the tube shall be removed from service by plugging or repaired by sleeving in the affected area because it may become unserviceable prior to the next inspection. Plugging or repair limit and is equal to 40% of the nominal tube wall thickness for the original tube wall. Sleeved tubes shall be plugged upon detection of unacceptable degradation in the pressure boundary region of the sleeve.

Unserviceable describes the condition of a tube or sleeve if it leaks in excess of analyzed limits or contains a defect large enough to affect its structural integrity in the event of an Operating Basis Earthquake, a loss-of-coolant accident, or a steam line or feedwater line break.

Tube or Tubing means that portion of the tube which forms the primary system to the secondary system pressure boundary.

Tube Inspection means an inspection of the steam generator tube from the point of entry (hot leg side) completely around the U-bend to the top support of the cold leg, excluding any areas defined under "Tube Sleeve Inspection".

Tube Repair or Sleeve refers to a process that re-establishes tube serviceability. Acceptable tube repairs will be performed using the Combustion Engineering, Inc. Leak Tight Sleeve as described in the proprietary Combustion Engineering, Inc. Report, CEN-630-P, Revision 02, "Repair of 3/4" O.D. Steam Generator Tubes Using Leak Tight Sleeves," June 1997.

Tube repair includes the removal of plugs that were previously installed as a corrective or preventive measure for the purpose of sleeving the tube. A tube inspection as defined herein is required prior to returning previously plugged tubes to service.

Tube Sleeve Inspection refers to inspection of the section of the steam generator tube repaired by sleeving. This includes the pressure retaining portions of the parent tube in contact with the sleeve, the sleeve-to-tube weld, and the pressure retaining portion of the sleeve.

- (ii) The steam generator shall be determined OPERABLE after completing the corresponding actions (plug or repair all tubes exceeding the plugging or repair limit and all tubes containing through-wall cracks; plug all tubes with sleeves containing defects) required by Tables 3-13 and 3-14.

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes** (Continued)

(5) **Reporting Requirements**

- (i) Following each in-service inspection of steam generator tubes, the number of tubes plugged or repaired in each steam generator shall be reported to the Commission within 30 days.
- (ii) The complete results of the steam generator tube in-service inspection shall be reported to the Commission within 6 months following completion of the inspection. This report shall include:
 - 1. Number and extent of tubes and tube sleeves inspected.
 - 2. Location and percent of wall thickness penetration for each imperfection.
 - 3. Identification of tubes plugged.
 - 4. Identification of tubes repaired by sleeving.
- (iii) Results of steam generator tube inspections which fall into Category C-3 and require prompt notification of the Commission shall be reported pursuant to Section 5.6 of the Technical Specifications prior to resumption of plant operation. The written followup of this report shall provide a description of investigations conducted to determine cause of the tube degradation and corrective measures taken to prevent recurrence.

TECHNICAL SPECIFICATIONS

TABLE 3-13

STEAM GENERATOR TUBE INSPECTION

1st Sample Inspection			2nd Sample Inspection		3rd Sample Inspection	
Sample Size	Result	Action Required	Result	Action Required	Result	Action Required
A minimum of 300 tubes per S.G.	C-1	None	N/A	N/A	N/A	N/A
	C-2	Plug or repair defective tubes and inspect additional 600 tubes in this S.G.	C-1	None	N/A	N/A
			C-2	Plug or repair defective tubes and inspect additional 1200 tubes in this S.G.	C-1	None
					C-2	Plug or repair defective tubes
			C-3	Perform action for C-3 result of first sample	C-3	Perform action for C-3 result of first sample
	C-3	Inspect all tubes in this S.G., plug or repair defective tubes and inspect 600 tubes in other S.G. Prompt notification to NRC pursuant to specification 5.6	The second S.G. is C-1	None	N/A	N/A
			The second S.G. is C-2	Perform action for C-2 result of second sample	N/A	N/A
			The second S.G. is C-3	Inspect all tubes in the second S.G. and plug or repair defective tubes. Prompt notification to NRC pursuant to specification 5.6	N/A	N/A

N/A - Not applicable

3-90

Amendment No. 46,99,104

TECHNICAL SPECIFICATIONS

TABLE 3-14

STEAM GENERATOR TUBE SLEEVE INSPECTION

1st Sample Inspection			2nd Sample Inspection	
Sample Size	Result	Action Required	Result	Action Required
A minimum of 20% of the installed tube sleeves	C-1	None	N/A	N/A
	C-2	Plug tubes containing defective sleeves and inspect all remaining installed sleeves in this S.G.	C-1	None
			C-2	Plug tubes containing defective sleeves
			C-3	Perform action for C-3 result of first sample
	C-3	Inspect all installed sleeves in this S.G., plug tubes containing defective sleeves, and inspect a minimum of 20% of the installed sleeves in other S.G. Add the tubes with defective sleeves to the number of defective tubes list for NRC notification per Table 3-13	The second S.G. is C-1	None
			The second S.G. is C-2	Perform action for C-2 result of first sample
			The second S.G. is C-3	Inspect all sleeves in the second S.G. and plug tubes containing defective sleeves. Add the tubes with defective sleeves to the number of defective tubes list for NRC notification per Table 3-13

N/A - Not applicable

3-90a

Amendment No. 46,99,104

TECHNICAL SPECIFICATIONS

3.0 **SURVEILLANCE REQUIREMENTS**

3.17 **Steam Generator Tubes (Continued)**

Basis

The surveillance requirements for inspection of the steam generator tubes and tube sleeves ensure that the structural integrity of this portion of the RCS will be maintained. The program for in-service inspection of the steam generator tubes is based on a modification of Regulatory Guide 1.83, Revision 1, dated July 1975. The program for in-service inspection of steam generator tube sleeves is based on a modification of EPRI PWR Steam Generator Examination Guidelines, Revision 5, Dated September 1997. In-service inspection of steam generator tubing and tube sleeves is essential in order to maintain surveillance of the conditions of the tubes and sleeves in the event that there is evidence of mechanical damage or progressive degradation due to design, manufacturing errors, or in-service conditions that lead to corrosion.

In-service inspection of steam generator tubing and tube sleeves also provides a means of characterizing the nature and cause of any tube or sleeve degradation so that corrective measures can be taken.

~~Wastage type defects are unlikely with proper chemistry treatment of the secondary coolant. However, even if a defect should develop in service, it will be found during scheduled in-service steam generator tube examinations. Plugging will be required for all tubes with imperfections exceeding the plugging limit of 40% of the tube nominal wall thickness. Steam generator tube inspections of operating plants have demonstrated the capability to reliably detect degradation that has penetrated 20% of the original tube wall thickness.~~

Tubes with defects may be repaired by a Combustion Engineering, Inc. Leak Tight Sleeve. The technical bases for sleeving repair are described in the Proprietary Combustion Engineering, Inc. Report CEN-630-P, Revision 02, "Repair of 3/4" O.D. Steam Generator Tubes Using Leak Tight Sleeves," June 1997.

Whenever the results of any steam generator tubing in-service inspection fall into Category C-3, these results will be promptly reported to the Commission pursuant to Section 5.6 of the Technical Specifications prior to the resumption of plant operation. Such cases will be considered by the Commission on a case-by-case basis and may result in a requirement for analysis, laboratory examinations, tests, additional eddy-current inspection, and revision of the Technical Specifications, if necessary.

LIC-00-0102
Attachment B
Discussion, Justification and No Significant Hazards Consideration

DISCUSSION, JUSTIFICATION AND NO SIGNIFICANT HAZARDS CONSIDERATION

DISCUSSION

Background

Pressurized water reactor (PWR) steam generators have experienced tube degradation related to corrosion phenomena, such as wastage, pitting, intergranular attack, stress corrosion cracking, and crevice corrosion, along with other phenomena such as denting and vibration wear. Tubes that experience excessive degradation reduce the integrity of the primary-to-secondary pressure boundary. Eddy current examination is used to measure the extent of tube degradation. When the reduction in tube wall thickness reaches a calculated value commonly known as the plugging criteria, the tube is considered defective and corrective action is taken.

Currently, the corrective action taken at many PWRs, including FCS, is to remove the degraded tube from service by installing plugs at both ends of the tube. The installation of steam generator tube plugs removes the heat transfer surface of the plugged tube from service and leads to a reduction in the primary coolant flow available for core cooling.

An alternative to plugging tubes is to repair defective steam generator tubes using Combustion Engineering, Inc. (CE) Leak Tight Sleeves. sleeving is a steam generator tube repair method where a length of tubing (sleeve) having an outer diameter slightly smaller than the inside of the steam generator tube is installed inside the parent tube spanning the degraded region. Installation of steam generator tube sleeves does not greatly affect the heat transfer capability or the primary coolant flow rate through the tube being sleeved; therefore, a large number of sleeves can be installed without significantly affecting the operation of the reactor coolant system. The sleeve spans the degraded section of the tube and maintains the structural integrity of the steam generator tube under normal and accident conditions and prevents primary-to-secondary leakage through the sleeved section of the tube should the degradation progress through-wall. This repair method has been approved for use at several other U.S. Nuclear Power Plants, including Calvert Cliffs, Palo Verde, and Prairie Island.

Description of Amendment Request

The Omaha Public Power District proposes to revise the Technical Specifications Table of Contents, Bases of Technical Specifications 2.1.4, 3.1, and 3.17 and Technical Specifications set forth in Sections 2.1.4, 3.17 and Table 3-13, and proposes to add Technical Specification Table 3-14 for the Fort Calhoun Nuclear Station. This revision will allow installation of tube sleeves as an alternative to plugging to repair defective steam generator tubes. This revision will allow removal of plugs that were previously installed as a corrective or preventive measure for the purpose of sleeving the tube. A tube inspection will be required prior to returning previously plugged tubes to service.

Tube inspection in accordance with Technical Specification 3.17, means an inspection of the steam generator tube from the point of entry (hot leg side) completely around the U-bend to the top support of the cold leg. The proposed amendment will permit FCS to use Leak Tight Sleeves developed by Combustion Engineering, Inc. (CE). The proposed amendment also reduces the allowable primary to secondary leakage through the steam generator tubes during operation from 1 gallon per minute total to 150 gallons per day per steam generator.

There are two major types of CE Leak Tight Sleeves for steam generator tube repair. Attachment D of Reference 2, CE Report CEN-630-P, Revision 02, "Repair of $\frac{3}{4}$ " O.D. Steam Generator Tubes Using Leak Tight Sleeves," dated June 1997, describes in detail the design and testing of these sleeves for FCS applicability. The analysis was performed for CE designed steam generators with $\frac{3}{4}$ inch outer diameter, 0.048-inch wall, Alloy 600 tubes. Attachment D of Reference 2 provides a detailed description of the design, installation, and testing associated with the CE Leak Tight Sleeves. The sleeve material is thermally treated Alloy 690. The first type of sleeve spans the parent steam generator tube at the top of the tube sheet. This sleeve is welded to the tube near the upper end of the sleeve and is hard rolled into the tube within the steam generator tube sheet. A shorter sleeve of the same design is used to span defective areas of a steam generator tube, which exists just above the tube sheet. The second type of sleeve spans degraded areas of the steam generator tube at a tube support plate or in a free span section of tube. This leak tight sleeve is welded to the steam generator tube near each end of the sleeve. The steam generator tube with the installed welded and/or hard rolled sleeve meets the structural requirements of tubes that are not degraded.

Currently, FCS Technical Specifications only allow defective tubes to be plugged and removed from service. The Technical Specifications marked-up in Attachment A provide the details of the proposed changes.

JUSTIFICATION

OPPD has determined that operation with the proposed amendment would not result in any significant change in the types, or significant increases in the amounts, of any effluents that may be released offsite, nor would it result in any significant increase in individual or cumulative occupational radiation exposure.

These proposed changes to the Technical Specifications and our determination of no significant hazards have been reviewed by our Plant Review Committee and Safety Audit and Review Committee. They have concluded that implementation of these changes will not result in an undue risk to the health and safety of the public.

The principal accident associated with this proposed change is the steam generator tube rupture (SGTR) accident. The consequences associated with the SGTR event are discussed in Fort Calhoun Station's Updated Safety Analysis Report Section 14.14, "Steam Generator Tube Rupture." The SGTR event is a breach of the barrier between the reactor coolant system and the main steam system. The integrity of this barrier is significant from the standpoint of radiological safety in that a leaking steam generator tube allows the transfer of reactor coolant into the main steam system. In the event of a SGTR, radioactivity contained in the reactor coolant mixes with water in the shell side of the affected steam generator. This radioactivity is transported by steam to the turbine and then to the condenser, or directly to the condenser via the turbine bypass valves, or directly to the atmosphere via the atmospheric dump valves, main steam safety valves, or the auxiliary feedwater pump turbine exhaust. Non-condensable radioactive gases in the condenser are removed by the condenser evacuation system and discharged to the plant vent. The use of CE Leak Tight Sleeves will allow the repair of degraded steam generator tubes such that the function and integrity of the tube is maintained; therefore, the SGTR accident is not affected. The consequences of a hypothetical failure of a CE Leak Tight Sleeve and/or associated steam generator tube would be bounded by the current SGTR analysis described above. Due to the slight reduction in diameter caused by the sleeve wall thickness, primary coolant release rates would be slightly less than assumed for the SGTR analysis (depending on break location), and therefore, would result in lower total primary fluid mass release to the secondary system. A main steam line break (MSLB) or feed line break (FLB) will not cause a SGTR since the sleeves are analyzed for a maximum accident differential pressure greater than that predicted in the Fort Calhoun Station safety analysis. The impact of sleeving on steam generator performance, heat transfer, and flow restriction is minimal and insignificant compared to plugging.

The proposed technical specification change to allow the use of CE Leak Tight Sleeves does not adversely impact any other previously evaluated design basis accident. The structural analyses of the sleeves demonstrate that their design meets all applicable American Society of Mechanical Engineers Boiler and Pressure Vessel Code (ASME Code) criteria for the steam generator pressure, temperature, and flow design conditions, and establishes the minimum reactor coolant pressure boundary wall thickness requirements. As described in detail in Attachment D of Reference 2, the results of the

analyses and testing, as well as plant operating experience, demonstrate that CE Leak Tight Sleeves are an acceptable means of maintaining tube integrity. Sleeved tube plugging limit criteria are established using the guidance of Regulatory Guide (RG) 1.121, "Basis for Plugging Degraded PWR Steam Generator Tubes." Furthermore, per Regulatory Guide 1.83, "Inservice Inspection of Pressurized Water Reactor Steam Generator Tubes" recommendations, the sleeved tube can be monitored through periodic inspections with present eddy current techniques. These measures ensure that installation of sleeves spanning degraded areas of the tube will restore the tube to a condition consistent with its original design basis.

The material selected for both types of sleeves is thermally treated Alloy 690 due to its corrosion resistance properties. Historically, thermally treated Alloy 690 has been used successfully for steam generator tubes, tube plugs, and tube sleeves. ABB Combustion Engineering (ABB/CE) conducted a number of bench and autoclave tests to evaluate the corrosion resistance of the welded sleeve joint. Of particular interest is the effect of the mechanical expansion/weld residual stresses and the condition of the weld and weld heat affected zone. Tests have been performed on welded joints with and without a post-weld heat treatment. There was no detectable indication of sleeve or joint corrosion or aggravated tube corrosion. The specific details of the corrosion performance of the thermally treated Alloy 690 material are contained in Section 6 of Attachment D of Reference 2.

The sleeve dimensions, materials, and joints were designed to the applicable ASME Code. An extensive analysis and test program was undertaken to prove the adequacy of both the welded and welded-hard rolled sleeve. This program determined the effect of normal operating and postulated accident conditions on the sleeve-tube assembly, as well as the adequacy of the assembly to perform its intended function. The proposed sleeving provides for a substitution in kind for a portion of a steam generator tube.

Installation of CE Leak Tight Sleeves has no significant effect on the configuration of the plant and does not affect the way in which the plant is operated. Design criteria were established prior to performing the analysis and test program which, if met, would prove that both sleeve types are acceptable repair techniques. These criteria conformed to the stress limits and margins of safety of Section III of the ASME Code. The safety factors of 3 for normal operating conditions and 1.5 for accident conditions were applied. Based upon the results of the analytical and test programs described in Attachment D of Reference 2, the two sleeve types fulfill their intended function as leak tight structural members and meet or exceed the established design criteria.

Evaluation of the sleeved tubes indicates no detrimental effects on the sleeve-tube assembly resulting from reactor coolant system flow, coolant chemistries, or thermal and pressure conditions. The sleeves are designed to be leak tight and therefore have no impact on steam generator leakage limits. Structural analyses of the sleeve-tube assembly, using the demonstrated margins of safety, have established its integrity under normal and accident conditions. The structural analyses performed are applicable to shorter sleeves installed at the top of the tubesheet and the tube support sleeves, which

may be installed at FCS. The detailed analyses for the different sleeve types and lengths are included in Section 8 of Attachment D of Reference 2.

Welding development has been performed on clean tubing, dirty tubing which has been taken from potboiler tests, and contaminated tubing taken from a steam generator. CE installed their first welded sleeves in a demonstration program at Ringhals Unit 2 in May 1984. CE's sleeving history is shown in Table 2-1 of Attachment D of Reference 2. Since 1985, no sleeve that has been accepted based on nondestructive examination (NDE) has been removed from service due to degradation.

Mechanical tests using ASME Code stress allowables were performed on mockup steam generator tubes containing sleeves to provide qualified test data describing the basic properties of the completed assemblies. These tests determined axial load, collapse, burst, and thermal cycling capability. A minimum of three tests of each type was performed. The demonstrated load capacity of the assemblies provided an adequate safety factor for normal operating and postulated accident conditions. The load capability of the upper and lower sleeve joints is sufficient to withstand thermally induced stresses in the weld resulting from the temperature differential between the sleeve and the tube, and pressure-induced stresses resulting from normal operating and postulated accident conditions. The burst and collapse pressures of the sleeve provide a large safety factor over limiting pressure differential. Mechanical testing revealed that the installed sleeve would withstand the cyclical loading resulting from power changes in the plant and other transients.

The effects of sleeve installation on steam generator heat removal capability and reactor coolant system flow rate are discussed in Attachment D of Reference 2. Heat removal capability and reactor coolant system flow rate were considered for installation of one to three sleeves in a steam generator tube. After sleeves are installed, an ultrasonic and eddy current examination is performed. The ultrasonic examination is used to confirm fusion of sleeve to the tube after welding. The eddy current examination serves as baseline to determine if there is sleeve degradation in later operating years. The steam generator tube will be plugged if the sleeve installation is not successful or if there is unacceptable degradation of a sleeve or sleeved steam generator tube. Standard steam generator tube plugs may be used to remove a sleeved tube from service.

Based on past usage and extensive testing, the CE Leak Tight Sleeves provide satisfactory repair of defective steam generator tubes. Design criteria were established based on the requirements of ASME Code and Regulatory Guide 1.121. Qualified nondestructive examination will be used to perform necessary repair sleeve and tube inspections for defect detection and to verify proper installation of the repair sleeve. In-service inspection requirements for the sleeves are being added to the Technical Specifications consistent with current industry practices.

Reduction of the limit for primary to secondary leakage through the steam generator tubes during operation from 1 gallon per minute total to 150 gallons per day per steam

generator is consistent with current industry guidance found in NEI 97-06, "Steam Generator Program Guidelines," and is a conservative change in operational limits.

NO SIGNIFICANT HAZARDS CONSIDERATION

The proposed change has been evaluated against the standards in 10 CFR 50.92, "Issuance of Amendment," and has been determined to not involve a significant hazards consideration. In support of this determination, a discussion of each of the significant safety hazards consideration factors with respect to the proposed license amendment is provided.

1. *The proposed amendment would not involve a significant increase in the probability or consequences of an accident previously evaluated.*

The CE Leak Tight Sleeves are designed using the applicable American Society of Mechanical Engineers (ASME) Boiler and Pressure Vessel Code and, therefore, meet the design objectives of the original steam generator tubing. The applicable design criteria for the sleeves conform to the stress limits and margins of safety of Section III of the ASME code. Mechanical testing has shown that the structural strength of repair sleeves under normal, upset, and faulted conditions provides margin to the acceptance limits. These acceptance limits bound the most limiting (three times normal operating pressure differential) burst margin recommended by Regulatory Guide 1.121. Burst testing of sleeved tubes has demonstrated that no unacceptable levels of primary-to-secondary leakage are expected during any plant condition.

Evaluation of the repaired steam generator tubes indicates no detrimental effects on the sleeve or sleeve-tube assembly from reactor coolant system flow, primary or secondary coolant chemistries, thermal conditions or transients, or pressure conditions as may be experienced at Fort Calhoun Station. Corrosion testing of sleeve-tube assemblies indicates no evidence of sleeve or tube corrosion considered detrimental under anticipated service conditions.

The installation of the proposed sleeves is controlled via the sleeving vendor's proprietary processes and equipment. The CE process has been in use since 1984 and has been implemented more than 24 times for the installation of over 4,200 sleeves. The FCS steam generator design was reviewed and found to be compatible with the installation processes and equipment.

The implementation of the proposed amendment has no significant effect on either the configuration of the plant or the manner in which it is operated. The consequences of a hypothetical failure of the sleeved tube is bounded by the current steam generator tube rupture analysis described in Fort Calhoun Station's USAR, Section 14.14. Due to the slight reduction in diameter caused by the sleeve wall thickness, primary coolant release rates would be slightly less than assumed for the steam generator tube rupture analysis, depending on the break location, and therefore, would result in lower total primary fluid mass release to the secondary system. A main steam line break or feed line break will not cause a SGTR since the sleeves are analyzed for a maximum accident differential pressure greater than that

predicted in the Fort Calhoun Station safety analysis. The proposed reduction of the steam generator primary to secondary operational leakage limit provides added assurance that leaking flaws will not propagate to burst prior to commencement of plant shutdown.

In conclusion, based on the discussion above, these changes will not significantly increase the probability or consequences of an accident previously evaluated.

2. *The proposed amendment would not create the possibility of a new or different kind of accident from any other accident previously evaluated.*

As discussed above, the CE Leak Tight Sleeves are designed using the applicable ASME Code as guidance; therefore, they meet the objectives of the original steam generator tubing. As a result, the functions of the steam generators will not be significantly affected by the installation of the proposed sleeves. The proposed repair sleeves do not interact with any other plant systems. Any accident as a result of potential tube or sleeve degradation in the repaired portion of the tube is bounded by the existing tube rupture accident analysis. The continued integrity of the installed sleeve is periodically verified by the Technical Specification requirements.

The implementation of the proposed amendment has no significant effect on either the configuration of the plant or the manner in which it is operated. As discussed above, the reduced primary to secondary leakage limit is a conservative change in the plant limiting conditions for operation. Therefore, Omaha Public Power District concludes that this proposed change does not create the possibility of a new or different kind of accident from any previously evaluated.

3. *The proposed amendment would not involve a significant reduction in a margin of safety.*

The repair of degraded steam generator tubes with CE Leak Tight Sleeves restores the integrity of the degraded tube under normal operating and postulated accident conditions. The design safety factors utilized for the repair sleeves are consistent with the safety factors in the ASME Code used in the original steam generator design. The portions of the installed sleeve assembly that represents the reactor coolant pressure boundary can be monitored for the initiation and progression of sleeve/tube wall degradation. Use of the previously identified design criteria and design verification testing assures that the margin of safety is not significantly different from the original steam generator tubes. The proposed sleeve inspection requirements are more stringent than existing requirements for inspection of the steam generator tubes, and the reduction in the operational limit for primary to secondary leakage through the steam generator tubes is more conservative than current requirements. Therefore, OPPD concludes that the proposed change does not involve a significant reduction in a margin of safety.

Based on the above considerations, OPPD concludes that the proposed amendment to FCS Technical Specifications does not involve a significant hazards consideration as defined by 10 CFR 50.92 and that the proposed amendment will not result in a condition which significantly alters the impact of the station on the environment. Thus, the proposed amendment meets the eligibility criteria for categorical exclusion set forth in 10 CFR 51.22 (c) (9), and pursuant to the 10 CFR 51.22 (b), no environment assessment need be prepared.